

PRODUCT NAME = MOLYBDATE ORANGE

NON-BLEEDING

6/22/82

CG 01 CODE YE-698-D PKG

 PROCESSES APPROVED BY
 YE-698-D (S) F.POST 06/22/82
 ALTERNATE
 TYPED BY JMH

LOT G2H46

JUN 30 1982

MAKING NOTES

EST. WT. 5527* LBS.

JOB NAME: 01YE698DPS

INSTRUCTIONS			PRESSING		RECORD																		
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 500 M MHOS WITH 35-75* WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	M MHOS	HRS. WASHED	M MHOS	HRS. WASHED	M MHOS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES	
242	7-22	3:22	A. C.	2	54	54	54			352	3:22	54	9PM	5	150						5		

 SAMPLES 8 OZ
 DELIVER TO CTL.

 SAMPLED BY
 RELEASED BY

 (EXTRUDED) DRY 10 HRS AT 240 DEG F
 (NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE

NO CARS PULLED

 NO DRUMS 18
 LUMP WGT 5410

DELIVER

 SAMPLED BY
 RELEASED BY

CO-GROUND PER CTL INSTRUCTIONS

GRINDING

MILL MIKROATOMIZE SCREEN

RPM

SCREEN

MAX. TEMP DEG F

MAX. TEMP.

 SET ROOF BLAST - GATE AT "9" FOR
 HIGH AIR FLOW

EXPLAIN LOSSES

SAMPLE

DATE MIXED

 SAMPLES 1 ENV IF GROUND SEPARATELY
 DELIVER TO CTL

 SAMPLED BY
 RELEASED BY

N32780

41
46
267

0.00 *

3.25 +
0.12 -/
3.15 +
0.12 -/
3.15 +
0.12 -/
3.25 +
0.12 -/
3.16 +
0.12 -/
3.09 +
0.12 -/
3.38 +
0.12 -/
3.33 +
0.12 -/
3.34 +
0.12 -/
3.16 +
0.12 -/
3.20 +
0.12 -/
3.34 +
0.12 -/
3.46 +
0.12 -/
3.15 +
0.12 -/
3.34 +
0.12 -/
2.95 +
0.12 -/
3.31 +
0.12 -/
1.25 +
0.12 -/
54.10 *

N32780.01

DUP050464283