CODE KY-908-D PKG ____ KY-908-D (G) FWP 06/30/82

LOT L2J13 NOV 2 1982

EST. WT. 4226* LBS

MAKING NOTES

JOB NAME: 03KY908DPG

INSTRUCTIONS				PRESSING =	RECORD				
VAT				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE				STARTED					
TIME				CAKES USED					
RELEASED BY				WATER ON					
PRESS	2	22	23	HRS. WASHED					
NO. OF CAKES	46	46	46	M MHOS					
PRESS WITH AGITATION				HRS. WASHED					
WASH TO 500 M MHOS - 135-145 F WATER				M MHOS					
TEST AFTER 2 HOURS				HRS. WASHED					
LOAD ON 7 CARS				M MHOS					
				CAKE CONDITION					
				NO. CARS LOADED					
				EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

DRY 24 HOURS AT 180 F
NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT

= GRINDING =

MILL 939 HSP 3/32"RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE W/O MIXING 1 ENV & 2 PT CANS
IF PACKED IN BAGS SAMPLE AS FOLLOWS:
FIRST BAG: 1 ENV.
40TH BAG: 1 ENV. & 2 PINT CANS
LAST BAG: 1 ENV.
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

13
41
16

0.00 *

2.34 +
0.12
2.35 +
0.12
2.34 +
0.12
2.43 +
0.12
2.36 +
0.12
2.42 +
0.12
2.53 +
0.12
2.56 +
0.12
2.46 +
0.12
2.53 +
0.12
2.45 +
0.12
2.48 +

0.12
2.48 +
0.12
2.25 +
0.12

2.45 +
0.12
2.52 +
0.12
2.27 +
0.12
2.31 +
0.12
2.43 +
0.12
1.09 +
0.12
44.65 *

DUP050059854