SANTICIZER 794

Established: December 23, 1964

For: Dewey & Almy

Composition:

50.0% Aroclor 1248
50.0% Aroclor 1260

Specifications:

Properties	Limits	Procedures
Acidity	0.021 meq/100 grams max. (= 0.012 mg. KOH/gram)	4-A
Appearance	Clear, oily liquid	16-B
Color	APHA 125 maximum	38-D
Moisture (By KF in methanol)	50 ppm maximum	78-B
Refractive index @ 25°C	1.6375 to 1.6395	104-A
Specific gravity @ 65/15.5°C	1.488 to 1.500	116-A

Blending Conditions:

The components (especially Arochlor 1260) must be heated to reduce the viscosity before blending. Temperatures in the range of 50-90° are suitable. Stirring should be continued until the mixture is homogenous. This will normally require at least 30 minutes.

Toxicity and Hazards:

Normal Precautions

Issue #1: 12-24-64

Developed by: R. H. Mills

Approved by: O. DeGarmo

DSW 329711

Original Assignment: W. G. Krummrich Plant

STLCOPCB4076354