

NO. 3-A

# PACKAGE TICKET

CODE

BT 425

LOT

L2H95

PO 20

NET WT/PKG.

NO. PKG.

PACK WT.

LOCATION

19

2769

40

STUMP

TOTAL NET WT.

2769

LUMP WT.

2787

PKG. N-CODE

PROD. SUPV.

DATE

OPERATOR

*[Signature]*

11.4.1

292

C

1.55 +  
1.45 +  
1.53 +  
1.54 +  
1.54 +  
1.49 +  
1.42 +  
1.46 +  
1.46 +  
1.51 +  
1.54 +  
1.53 +  
1.54 +  
1.52 +  
1.60 +  
1.50 +  
1.48 +  
1.32 +  
0.71 +

019

27.69 1

PRODUCT NAME = MONASTRAL BLUE BF

DATE PRINTED: 1/26/82

CG 20 CODE BT-425-D PKG

PROCESSES | APPROVED BY  
BT-425-D (F) | BBK 11/25/81  
TYPED BY: JMH

NOV 1 1982  
( DATE )

L2H95  
( LOT )

37  
200

NOTES:

TOTAL EST'D WGT = 2751\* LBS

JOB NAME: 20BT425DPF

| INSTRUCTIONS |        |       |             |       |              | = PRESSING =         | RECORD                            |                    |                |           |         |            |          |             |      |             |      |             |      |                |                |                |
|--------------|--------|-------|-------------|-------|--------------|----------------------|-----------------------------------|--------------------|----------------|-----------|---------|------------|----------|-------------|------|-------------|------|-------------|------|----------------|----------------|----------------|
| VAT          | DATE   | TIME  | RELEASED BY | PRESS | NO. OF CAKES | PRESS WITH AGITATION | WASH TO 5000 OHMS - 35-75°F WATER | TEST AFTER 3 HOURS | LOAD ON 8 CARS | PRESSLOAD | STARTED | CAKES USED | WATER ON | HRS. WASHED | OHMS | HRS. WASHED | OHMS | HRS. WASHED | OHMS | CAKE CONDITION | NO CARS LOADED | EXPLAIN LOSSES |
|              | 1/2-82 | 6:30A |             | 20    | 21           | 26                   | 35                                | 36                 | 60             | 62        |         |            |          |             |      |             |      |             |      |                |                |                |
|              |        |       |             |       |              |                      |                                   |                    |                |           |         |            |          |             |      |             |      |             |      |                |                |                |

SAMPLES JAR  
DELIVER TO

SAMPLED BY  
RELEASED BY

= DRYING =

DRY 14 HOURS AT 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES  
DELIVER TO

NO CARS PULLED  
SAMPLED BY  
RELEASED BY

NO DRUMS 19  
LUMP WGT 2787

= GRINDING =

MILL 7 OR 8LSP 3/32" RP SCREEN 1750RPM

MAX. TEMP 140 DEG F

INERT MILL WITH CO2 WHEN GRINDING

PER OP #0043.

SCREEN  
MAX. TEMP.  
RPM  
F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING  
SAMPLES 1 ENV & 2 PT CANS  
DELIVER TO CTL

DATE MIXED  
SAMPLED BY  
RELEASED BY

95  
51  
371

0.00 \*

1.74 +

0.12 ✓

1.65 +

0.12 ✓

1.80 +

0.12 ✓

1.63 +

0.12 ✓

1.64 +

0.12 ✓

1.73 +

0.12 ✓

1.64 +

0.12 ✓

1.69 +

0.12 ✓

1.67 +

0.12 ✓

1.72 +

0.12 ✓

1.65 +

0.12 ✓

1.74 +

0.12 ✓

1.73 +

0.12 ✓

1.56 +

0.12 ✓

0.94 +

0.12 ✓

22.73 \*

95  
124  
51

1.58 +

0.14 ✓

1.59 +

0.14 ✓

1.58 +

0.14 ✓

0.95 +

0.14 ✓

22.73 +

27.87 \*

9 cars