MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KO·909 LOT 34017

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2510	1	T310		
2590	1	T145		
	STUMP			

TOTAL NET WT. 5100 PKG. N–CODE

PROD. SRVR. DM DATE 2,1,80 WHSE. OPER.

N28558

24
246

CG 04 CODE KO-909-D PKG. ____

→ JAN 26 27 34017

EST. WGT. 1674 / 5130 LBS. OK AP

5130

TOTAL WGT. 5274 (Req ____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KO-909-D (C)	EWK 1-27-78
	DCG 1-30-78
TYPED BY	
NSA 3-13-78	

MAKING NOTES

REMARKS

NAME: KROLOR® ORANGE Y — NON-BLEEDING

INSTRUCTIONS

VAT	246				
DATE	1-30-80				
TIME	6:15 PM				
RELEASED BY	C.M				
PRESS	2	22	23	24	25 / 18
NO. OF CAKES	46	46	46	52	

PRESS with AGITATION
WASH TO 2000 OHMS with 135-145° water
TEST AFTER HOURS
LOAD on 6 cars

SAMPLES 1-8 oz
DELIVER TO CTL for color

-PRESSING- RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	7 PM				
CAKES USED	48				
WATER ON	9:30 PM				
HRS. WASHED	6				
OHMS	4060				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	7				
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY #52 RELEASED BY

-DRYING-

DRY 22 HOURS AT 180°F

LUMP: OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS: 18

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 5062
SAMPLED BY RELEASED BY

-GRINDING-

MILL 938 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050095080

34017
41
17

0.00 *

2.95 +
0.12 -
3.03 +
0.12 -
2.95 +
0.12 -
2.90 +
0.12 -
2.92 +
0.12 -
2.97 +
0.12 -
2.88 +
0.12 -
2.86 +
0.12 -
2.98 +
0.12 -
3.03 +
0.12 -
2.99 +
0.12 -
3.03 +
0.12 -
2.92 +
0.12 -
3.10 +
0.12 -
2.81 +
0.12 -
2.95 +
0.12 -
2.81 +
0.12 -
2.70 +
0.12 =
50.62 *

DUP050095081