MD-3-A

PACKAGE TICKET

CODE YE 698 LOT G2J16

PO	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
	50	~~36~~	~~1800~~	
		37	1850	
	STUMP	1850		
		~~1800~~		

TOTAL NET WT.

LUMP WT. 1944 PKG. N-CODE 1000

PROD. SUPV. DATE 7 28 OPERATOR

N32775

PRODUCT NAME = MOLYBDATE ORANGE

CG 01 CODE H YE-698-D PKG ____

LOT G2J16

EST. WT. ~~5027~~ 1500 LBS.

FLOP

NON-BLEEDING 6/22/82

PROCESSES APPROVED BY

YE-698-D (S) F.POST 06/22/82

ALTERNATE

TYPED BY JMH

MAKING NOTES SPLIT OFF 1500# FROM LOT G2H41

JOB NAME: 01YE698DPS

= INSTRUCTIONS = PRESSING = RECORD

							1ST	2ND	3RD	4TH	5TH
VAT						PRESSLOAD					
DATE						STARTED					
TIME						CAKES USED					
RELEASED BY						WATER ON					
PRESS	2	92	93			HRS. WASHED					
NO.OF CAKES	54	54	54			M MHOS					
PRESS WITH AGITATION						HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER						M MHOS					
TEST AFTER 2 HOURS						HRS. WASHED					
LOAD ON 7 CARS						M MHOS					
						CAKE CONDITION					
						NO CARS LOADED	2				

EXPLAIN LOSSES

SAMPLES 8 OZ

DELIVER TO CTL

SAMPLED BY

RELEASED BY AK

FLOP

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F

(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

Flop batch

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 6

LUMP WGT 1944

SAMPLE

NO CARS PULLED

SAMPLED BY

DELIVER

RELEASED BY

CO-GRIND PER CTL INSTRUCTIONS GRINDING

MILL MIKROATOMIZE SCREEN RPM

MAX. TEMP DEG F

SET ROOF BLAST - GATE AT "9" FOR HIGH AIR FLOW

SCREEN RPM

MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE

SAMPLES 1 ENV IF GROUND SEPARATELY

DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

FLOP

N32775.01

DUP050464270



N32775.02

DUP050464271