

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 117 788 LOT 34419

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>50</u>	<u>72</u>	<u>3600</u>		

STUMP

TOTAL NET WT. 3600 PKG. N-CODE 1130

PROD. SPVR.	DATE	WHSE. OPER.
<u>2P</u>	<u>2121180</u>	

95
262

CG 03 CODE KY-788-D PKG.
FEB 15 34419
EST. WGT. 960 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KY-788-D (K)
Alternate

APPROVED BY
ENK 9/22/76
DGG 9/27/76

TYPED BY
NE 2/24/76

MAKING NOTES

REMARKS

Total Wgt 3560#

NAME: "KROLOR" YELLOW - LIGHT

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	262					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	2-17					STARTED	3:30				
TIME	2:40P					CAKES USED	40				
RELEASED BY	JDL					WATER ON	7.P.M				
PRESS	22	23	84	24	95	HRS. WASHED	3				
NO. OF CAKES	46	46	15	52	40	OHMS	2500				
PRESS. with						HRS. WASHED					
WASH TO	2000					OHMS					
TEST AFTER	2					HRS. WASHED					
LOAD on 6 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

FDS

SAMPLES 1- 8oz JAR
DELIVER TO CTL for color

SAMPLED BY #58 RELEASED BY

-DRYING-

Dry 12 hrs at 220 °F
Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

m

No. Drums (15)

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 3614
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES Env & Pt. Can
DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050094836

34419
41
324

0.00 *

2.52 +
0.14 -
2.63 +
0.14 -
2.61 +
0.14 -
2.57 +
0.14 -
2.52 +
0.14 -
2.55 +
0.14 -
2.58 +
0.14 -
2.47 +
0.14 -
2.51 +
0.14 -
2.63 +
0.14 -
2.44 +
0.14 -
2.52 +
0.14 -
2.68 +
0.14 -
2.52 +
0.14 -
2.49 +
0.14 -
36.14 *