MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE K0909 LOT 37935

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2654	1		T-216	
2590	1		T 188	
	STUMP	LUMP		

TOTAL NET WT. 5244 PKG. N—CODE

PROD. SPVR.	DATE	WHSE. OPER.

N34628

24/247

CG 04 CODE KO-909-D PKG. ____

→ NOV 18 80 37935

EST. WGT. ~~1674~~ LBS.

OK / 59

TOTAL WGT. ~~5274~~ 5296 (Req _____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KO-909-D (C)	EWK 1-27-78
	DCG 1-30-78
TYPED BY	
NSA 3-13-78	

MAKING NOTES

REMARKS

AME: KROLOR® ORANGE Y

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
AT				247		PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE				11-19-80		STARTED	1 30				
IME				10:10		CAKES USED	150				
ELEASED BY				MK		WATER ON	6 AM				
RESS	2	22	23	24		HRS. WASHED	4				
O. OF CAKES	46	46	46	52		OHMS	2500				
RESS with		AGITATION				HRS. WASHED					
ASH TO 2000		OHMS with 135-145° water				OHMS					
EST AFTER		HOURS				HRS. WASHED					
OAD on 6 cars						OHMS					
						CAKE CONDITION	7				
						NO. CARS LOADED					
						EXPLAIN LOSSES					

AMPLES 1-8 oz

ELIVER TO CTL for color

SAMPLED BY #469 RELEASED BY AK

-DRYING-

~~22~~ 24

RY ~~24~~ HOURS AT 180°F

Dry on first stage only.

Re-set every 5 hours til dry

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 18

MPLES

NO. CARS PULLED

LUMP WGT. 5382

LIVER TO

SAMPLED BY

RELEASED BY QC

-GRINDING-

3/32

LL 938 HSP ~~1/8"~~ RP SCREEN 3500 RPM

X. TEMP. 170°F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

PLE / WITHOUT MIXING

PLES 1 ENV & 1 PT CAN

IVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050104687

37935

41

58

0

333
12.
299
12.
314
12.
320
12.
306
12.
301
12.
302
12.
316
12.
313
12.
310
12.
316.
12
317
12.
339
12.
313
12.
325
12.
324
12.
372
12.
178
12.
5312

18
/ DRUMS

DUP050104688