MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KO-786 LOT 36252

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
2660	1	T	291	
2370	1	T	234	
	LUMP STUMP	5,002#		

TOTAL NET WT. 5030 PKG. N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	7/1/80	

N34537

DUP050104341

25
V247 → JUL 24 20252

CG 04 CODE KO-786-D PKG. ____

EST. WGT. 862 LBS.

OK
KP

TOTAL WEIGHT 4962 (Req. _____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KO-786-D (P)	EWK 9-21-76
	DCG 9-21-76
TYPED BY	
jlc 11-15-76	

MAKING NOTES.

REMARKS

NAME: "KROLOR" ORANGE R

NON-BLEEDING

INSTRUCTIONS -PRESSING- RECORD

VAT			247		
DATE			6-24-76		
TIME			1655A		
RELEASED BY			SJ		
PRESS	22	23	24	25	
NO. OF CAKES	46	46	52	48	

PRESS with AGITATION
WASH TO 5000 OHMS with 35-75°F water
TEST AFTER 6 HOURS
LOAD on 6 cars

SAMPLES 1-8 oz. jar
DELIVER TO CTL for color

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	7:15 PM				
CAKES USED	52				
WATER ON	4:00 PM				
HRS. WASHED	12 ½				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	5				
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY #469 RELEASED BY J.K.

-DRYING-

DRY 16 HOURS AT 220°F L.V. I.V.
TEMP. °F °F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS: 17

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 5002
SAMPLED BY RELEASED BY BKL

-GRINDING-

MILL 938 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 210 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 Env. + 1 Pint Can
DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050104342

36252
4100
18

0.00 *

3.11 +
0.14 -
3.32 +
0.14 -
3.22 +
0.14 -
3.21 +
0.14 -
3.13 +
0.14 -
3.06 +
0.14 -
3.09 +
0.14 -
3.30 +
0.14 -
3.11 +
0.14 -
3.36 +
0.14 -
3.20 +
0.14 -
3.26 +
0.14 -
3.12 +
0.14 -
3.46 +
0.14 -
3.13 +
0.14 -
2.91 +
0.14 -
1.41 +
0.14 -
50.02 *

DUP050104343