PLAINTIFF'S EXHIBIT

BEA-119

THE SARANAC LABORATORY

OF THE EDWARD L. TRUDEAU FOUNDATION

SARANAC LAKE, N.Y.

ARTHUR J. VORWALD, M.D.
DIRECTOR

August 5, 1952

THE INDUSTRIAL COMMISSION

(Sample of Thiemold non-sil parting compound, manufactured by Thiem Products Inc., 9800 Rogers St., Milwaukee 14, Wisconsin - submitted under Don Ferna's letter dated July 21, 1952).

X-Ray Diffraction and Petrographic Analysis

Portion of sample taken for X-ray diffraction was first treated with hydrochloric acid for purposes of concentration. All figures reported below are in terms of the material as received.

Quartz	1.4% ±
Mica	trace
Loss on treatment (Principally calcite)	[illegible]

Donald Bailey
Petrographer

DD:lmf

3

SC-BE-00975