| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | JOINT COMPOUND<br>CASEIN BASE | BULLETIN NO: J-6008<br>DATE: 1/30/70<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT<br>DELANCO | CANCELS: 3P-10<br>DATE: 4/25/68 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 220 | Whiting | 65.62 | 1380 | |
| 266 | Mineralite 260 | 2.38 | 50 | |
| 251 | Mica P80F | 11.89 | 250 | |
| 045 | Asbestos 7RF10 | 10.46 | 220 | |
| 084 | Casein | 7.13 | 150 | |
| 025 | Ammonium Oxalate | 1.04 | 22 | |
| 216 | Hydrated Lime | .28 | 6 | |
| 430 | Sodium Tripolyphosphate | .48 | 10 | |
| 456 | Troysan CAP-10SEP | .24 | 5 | |
| 079 | Cellosize T JC McKinney 22F | .48 | 10 | |
| | TOTAL | | 2103 | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin J-3008.
2. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm cylinder @ 5 sec.<br>200 gm to 150 cc water | 38 - 40 mm |
| TM-3 | Tape Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

ALL-STATE LEGAL
PLAINTIFF'S EXHIBIT
KG-321

EXHIBIT 9
Deponent Kirk
Date 1/05/06 Rptr. MAJ
WWW.DEPOBOOK.COM



EXHIBIT 8
hg Litigation Services

| PRODUCT BULLETIN DRYWALL ACCESSORY PRODUCTS | ONE DAY JOINT COMPOUND | BULLETIN NO: 6368<br>DATE: (9/22/69)<br>PAGE: 1 of 3 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT<br>DELANCO | CANCELS: 1P-60<br>DATE: 9/1/68 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 082 | Calcined Gypsum | 25.74 | 500 | |
| 251 | Mica, P80F | 7.72 | 150 | |
| 330 | Polyvinyl Alcohol, Coval 9702 | .76 | 15 | |
| 045 | Asbestos 7RF 10 | 3.35 | 65 | |
| 325 | Polyvinyl Acetate, D702 | 4.12 | 80 | |
| 279 | Natrosol 250 HHXR | .36 | 7 | |
| 430 | Sodium Tripolyphosphate (STPP) | .05 | 1.0 | |
| 456 | Troysan CMP 10SEP | .08 | 1.5 | |
| 320 | Dibutyl Phthalate (Dry liquid | | | |
| | Concentrate) | .38 | 7.5 | |
| 332 | Potassium Sulphate, $K_2SO_4$ | | | |
| | (98% -100 mesh) | .76 | 10-15 | |
| 417 | Sodium Citrate (98% -100 mesh) | .05 | 1.0 | |
| 220 | Whiting | 25.74 | 500 | |
| 186 | Hydrite Flat D Clay | 5.15 | 100 | |
| 082 | Calcined Gypsum | 25.74 | 500 | |
| | TOTAL BATCH WEIGHT | 100.00 | 1943 lbs. | |

MANUFACTURING INSTRUCTIONS:

1. A thorough clean-out with whiting must be made before and after each production run.
2. Wall Texture or Joint Compounds are to be run immediately after a run of this product.
3. Mixing time shall be 8 minutes minimum and 12 minutes maximum.
4. Special orders of SLOW SET One Day Joint Compound can be made by reducing the amount of potassium sulfate (Bulletin No. 332) from 10-15 pounds to 2.5 to 5.0 pounds per batch.

EXHIBIT
KG-210

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | ONE DAY JOINT<br>COMPOUND | BULLETIN NO: 6368<br>DATE: (9/22/69)<br>PAGE: 2 of 3 |
|---|---|---|
| APPROVALS: | DELANCO | CANCELS: 1P-60<br>DATE: 9/1/68 |

QUALITY CONTROL:

Test Method

| | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm cylinder @ 5 sec.<br>200 gm to 120 cc water | 38 - 40 mm |
| TM-1A | Viscosity, Brookfield<br>200 gm to 120 cc water | 188,000 to 220,000 cps |
| TM-3 | Bond @ 70°F and 40°F 50% RH | 9 - 10 |
| TM-7 | Workability | Equal to Standard |
| TM-27 | Vicat Set Time, 300 gm needle (hrs) | 1-1/2 - 2 |

NOTE: For Slow Set as follows:

| | |
|---|---|
| Vicat, 11 gm needle (hrs) | 2 - 2-1/2 |
| 300 gm needle (hrs) | 2-1/2 - 3 |
| Δ t (300 m -11 gm) | 10 - 30 minutes |

SPECIFICATIONS:

| | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm cylinder @ 5 sec.<br>200 gm to 120 cc water | 38 - 40 mm |
| TM-1A | Viscosity, Brookfield<br>200 gm to 120 cc water | 188,000 - 220,000 cps |
| TM-27 | Vicat Set, 300 gm needle | |
| | (a) Fast Set (hrs) | 1 - 1-1/2 |
| | (b) Slow Set (hrs) | |
| | 11 gm needle (hrs) | 2 - 2-1/2 |
| | 300 gm needle (hrs) | 2-1/2 - 3 |
| | Δ t (300 gm -11 gm) | 10 - 30 minutes |
| TM-3 | Tape Bond @ 70F @ 40-70% RH | 9 - 10 |
| | @ 40F @ 50-90% RH | 9 - 10 |
| TM-4 | Slope Bond @ 110F | Excellent |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | ONE DAY JOINT<br>COMPOUND | BULLETIN NO: 6368<br>DATE: (9/22/69)<br>PAGE: 3 of 3 |
|---|---|---|
| APPROVALS: | DELANCO | CANCELS: 1P-60<br>DATE: 9/1/68 |

SPECIFICATIONS: (cont.)

| | | |
|---|---|---|
| TM-9 | Cup Shrinkage @ 70F @ the Set<br>@110F (Dry) | 2% maximum<br>6% maximum |
| TM-10 | Edge Cracking @ 110°F (normal test) | None |
| TM-11 | Voids | Equal to Standard |
| TM-15 | Mixing | Equal to Standard (no lumps or dry agglomerates) |
| TM-21 | Reaction to Iodine | Light Red |
| TM-26 | Paste Density (gms/cc) | 1.40 - 1.50 |

NOTE: One batch of One Day Joint Compound shall be used as a standard for a maximum of 6 months. The code of the Standard Batch shall be recorded in laboratory test records.

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | JOINT COMPOUND<br>CASEIN BASE | BULLETIN NO: 3P-10<br>DATE: (4/25/68)<br>PAGE: 1 of 3 |
|---|---|---|
| | | CANCELS: NEW<br>DATE: |

PRODUCING PLANT: Delanco

FORMULA:

| | Item | Amount per Batch | Bulletin |
|---|---|---|---|
| 1. | Mineralite 260 | 50.0 lbs. | RM-J9A |
| 2. | Mica, P80F | 250.0 lbs. | RM-J7B |
| 3. | Asbestos, Type 7RF10 | 200.0 to 220.0 lbs. | RM-J3A |
| 4. | Methocel 228 | 8.0 lbs. | RM-J26B |
| 5. | Hydrated Lime | 6.0 lbs. | RM-J12 |
| 6. | Ammonium Oxalate | 22.0 lbs. | RM-J1 |
| 7. | Sodium Tripolyphosphate | 10.0 lbs. | RM-J19 |
| 8. | Casein, 2% Surfactol | 150.0 lbs. | RM-J3 |
| 9. | Marblewhite 325 | 1300.0 to 1400.0 lbs. | RM-J17 |
| 10. | Troysan CMP-10SEP | 5.0 lbs. | RM-J10B |
| | Total Batch Weight | 2101.0 lbs. | |

ANG0012004:0004

| | | |
|---|---|---|
| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | FINISHING COMPOUND<br>CASEIN BASE | BULLETIN NO: 3P-20<br>DATE: (4/25/68)<br>PAGE: 1 of 2 |
| | | CANCELS: NEW<br>DATE: |

PRODUCING PLANT: Delanco

FORMULA:

| ITEM | AMOUNT PER BATCH | BULLETIN |
|---|---|---|
| 1. Mica, P80F | 250.0 lbs. | RM-J7B |
| 2. Asbestos, Type 7TF1 | 200.0 lbs. | RM-J2A |
| 3. Asbestos, Grade SG210 | 30.0 lbs. | RM-J2D |
| 4. Methocel 228 | 7.0 lbs. | RM-J26B |
| 5. Ammonium Oxalate | 12.0 lbs. | RM-J1 |
| 6. Sodium Tripolyphosphate | 6.0 lbs. | RM-J19 |
| 7. Casein, 2% Surfactol | 90.0 lbs. | RM-J3 |
| 8. Mineralite 260 | 400.0 lbs. | RM-J9A |
| 9. Yellow Oxide | 2.0 lbs. | RM-J5 |
| 10. Troysan CMP-10SEP | 3.0 lbs. | RM-J10B |
| 11. Marblewhite 325 | 1100.0 lbs. | RM-J17 |
| Total Batch Weight | 2100.0 lbs. | |

| RAW MATERIAL BULLETIN<br>DRYWALL ACCESSORY | ASBESTOS<br>(FINE FIBER) | BULLETIN NO: RM-J2D<br>DATE: 1/15/69<br>PAGE: 1 of 1 |
|---|---|---|
| | | CANCELS: NEW<br>DATE: |

APPROVED SOURCES: UNION CARBIDE
(SG 210)

SPECIFICATIONS:

| | |
|---|---|
| 1. Magnetite | 2% Maximum |
| 2. Reflectance (GE Photovolt) | 68% |
| 3. Dry Bulk | 5 - 6 Pounds/Cubic Foot |
| 4. Wet Bulking, 10 gm in 250 ml at 1 hour | 220 Ml. Settled Volume |
| 5. Wet Screen, Cumulative, Retained on: | |
| 20 Mesh | 0% |
| 35 Mesh | 0% |
| 100 Mesh | 1% |
| 200 Mesh | 3% |
| 325 Mesh | 12 % |

WARNING

Employees should wear respirators when handling, weighing and batching asbestos.

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE<br>COMPOUND | BULLETIN NO: J-6408<br>DATE: 11-21-74<br>PAGE: 1 of 3 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT:<br>DELANCO | CANCELS: J-6408<br>DATE: 2-28-73 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 220 | Whiting | 67.56 | 1350 | |
| 251 | Mica AMC | 12.51 | 250 | |
| 442 | Talc | 7.51 | 150 | |
| 045 | Asbestos 7RF10 | 5.01 | 100 | |
| 431 | Starch Staramic 747 | 5.01 | 100 | |
| 084 | Casein | 1.25 | 25 | |
| 025 | Ammonium Oxalate | .30 | 6 | |
| 430 | Sodium Tri Poly Phosphate | .15 | 3 | |
| 244 | Thickner M/C 228 | .30 | 6 | |
| 453A | Preservative (PMA-10-SEP) | .15 | 3 | |
| 454 | Defoamer | .15 | 3 | |
| 200 | Keltose | .10 | 2 | |
| | | | | |
| | TOTAL | 100.00 | 1998 | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin No. J-308.
2. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, Brookfield 200 gm to 130 cc water | 190,000 - 210,000 CPS |
| TM-3 | Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

135 cc.

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE<br>COMPOUND | BULLETIN NO: J-6408<br>DATE: 11-21-74<br>PAGE: 2 of 3 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT:<br>DELANCO | CANCELS: J-6408<br>DATE: 12-22-72 |

PRODUCT SPECIFICATIONS:

| Test Method | | |
|---|---|---|
| TM-1A | Viscosity (mixing water of 135cc/200 gm) | 190,000 - 210,000 CPS |
| TM-2 | pH (Beckman meter) | 8.0 - 8.5 |
| TM-3A | Bond @ 65-80°F | 9 - 10 minimum |
| TM-4 | Slope Checking @ 110°F | Lt. checking on thick end. No fissures or cracks. |
| TM-5 | Open Time @ 65-80°F (mins) | 15 minimum |
| TM-7 | Workability (hand or Ames tools) | Equal to Standard |
| TM-9 | Shrinkage (cup method) | 27% maximum |
| TM-12 | Grit (total) | 0.05% maximum. All passing 80 mesh. |
| TM-14 | Voids | Equal to Standard |
| TM-15 | Mixing | Equal to Standard (no lumps or dry agglomerates) |
| TM-16 | Rate of Wetting (secs) | 30 maximum |
| TM-18 | Water Resistance (mins) | 2 minimum |
| TM-21 | Iodine Test | light blue |
| TM-25 | Normal Application Consistency (cc/100 gm) | 65 - 70 |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE<br>COMPOUND | BULLETIN NO.: J-6408<br>DATE: 11-21-74<br>PAGE: 3 of 3 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT:<br>DELANCO | CANCELS:<br>DATE: |

PRODUCT SPECIFICATIONS:

| Test Method | | Requirement | Lab Test Batch | Factory Batch # D6-18-1-3PCX |
|---|---|---|---|---|
| TM-1A | Viscosity (mixing water of 130 cc/200 gm) | 190,000 - 210,000 CPS | 200,000 | 205,000 |
| TM-2 | pH (Beckman meter) | 8.2 - 9.2 | 8.4 | 8.4 |
| TM-3A | Bond @ 64-80°F | 9 - 10 | 9 - 10 | 10 |
| | @ 44°F after recovery at 75°F | 9 - 10 | 9 - 10 | 9 - 10 |
| TM-4 | Slope Checking @ 110°F | Lt. checking on thick end. No fissures or cracks. | Passes | Passes |
| TM-5 | Open Time @ 65-80°F (mins) | 15 minimum | 16 | 17 |
| TM-7 | Workability (hand or Ames tools) | Equal to Standard | Standard | Standard |
| TM-9 | Shrinkage (cup method) | 27% maximum | 23.2 | 24.2 |
| TM -10 | Edge Cracking | None | Passes | Passes |
| TM-12 | Grit (total) | 0.05% maximum. All passing 80 mesh. | Passes | Passes |
| TM-14 | Voids | Equal to Standard | Standard | Standard |
| TM-15 | Mixing | Equal to Standard (no lumps or dry agglomerates) | Standard | Standard |
| TM-18 | Water Resistance (seconds) | 2 minimum | 3 | 3 |
| TM-21 | Iodine Test | Light Blue | Light Blue | Light Blue |
| TM-25 | Normal Application Consistency | 65 - 70 | 65 | 66 |

USG-PUUC-PUCJNA

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | PREMIX TOPPING<br>COMPOUND | BULLETIN NO: J-6808<br>DATE: 12-20-74<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT:<br>DELANCO | CANCELS: J-6808<br>DATE: 12-19-72 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 221 | Whiting | 60.94 | 4000 | |
| 047 | Asbestos SG 210 | .92 | 60 | |
| 442 | Talc, Nytal 200 | 1.52 | 100 | |
| 086 | Celite 434 | 1.52 | 100 | |
| 244 | Methocel 228 | 0.27 | 18 | |
| 330 | PV Alcohol | .15 | 10 | |
| 453 | Preservative | .06 | 4 | |
| 470 | PVA Emulsion 4.40% on solids | 5.06 | 332 | 36 |
| | Water | 26.66 | 1750 | 210 max. |
| 284 | Oleic Acid | .37 | 24 | |
| 450 | Triethanolamine | .18 | 12 | |
| 267 | Odorless Mineral Spirits | 1.22 | 80 | 12.5 |
| 130 | Ethylene Glycol | 1.14 | 75 | 8 |
| | | | | |
| | TOTAL | 100.00 | 6565 | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin J-206.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, Brookfield | 275,000 to 325,000 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | PREMIX TOPPING<br>COMPOUND | BULLETIN NO: J-6808<br>DATE: 12-20-74<br>PAGE: 2 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT:<br>DELANCO | CANCELS: J-6808<br>DATE: 12-19-72 |

PRODUCT SPECIFICATIONS:

| Test Method | | |
|---|---|---|
| TM-1A | Viscosity, Brookfield, (cps) | 275,000 to 325,000 |
| TM-2 | pH, Beckman | 8.0 to 9.5 |
| TM-4 | Slope Checkint at 100°F | 8 minimum |
| TM-5 | Open Time @ 65-80°F (minutes) | 15 minimum |
| TM-7 | Workability | 9 - 10 |
| TM-9 | Shrinkage (cup method) | 20% maximum |
| TM-11 | Voids | 9 - 10 |
| TM-34 | Hardness @ 48°F | 8 - 13. No chalking. |
| TM-39 | Paintability Test | Equal to Standard |

| | | |
|---|---|---|
| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | PREMIX JOINT COMPOUND<br>DUAL PURPOSE<br>VINYL BASE | BULLETIN NO: 08-069 ~~3F-12~~<br>DATE: (4/25/68)<br>PAGE: 1 of 4 |
| | | CANCELS: NEW<br>DATE: |

PRODUCING PLANT: Delanco JACKSONVILLE

FORMULA:

| | ITEM | AMOUNT PER BATCH | BULLETIN |
|---|---|---|---|
| 1. | Asbestos 7TF1 | 150.0 lbs. | RM-J2A |
| 2. | Methocel 228 | 12.0 lbs. | RM-J26B |
| 3. | Marblewhite 325 | 1100.0 lbs. | RM-J17 |
| 4. | Mica, P80F | 250.0 lbs. | RM-J7B |
| 5. | Sericite, Narvon CEF2 | 175.0 lbs. | RM-J9 |
| 6. | ~~Hydrite Clay~~ | 50.0 lbs. | RM-J4A |
| 7. | ~~Asbestine~~ FT | 100.0 lbs. | RM-J11A |
| 8. | Yellow Oxide | 0.0 to 3.0 lbs. | RM-J5 |
| 9. | Troysan CMP-10SEP | 3.0 lbs. | RM-J10B |

Dry blending time shall be 8 minutes minimum and 12 minutes maximum.

| | | | | |
|---|---|---|---|---|
| 10. | Water (maximum) | 140 | lbs. | |
| 11. | Ethylene Glycol | 0 to 2 | gals. | RM-J21 |
| 12. | ~~Daxad 30 (dispersant)~~ | ~~1200 to 2400 cc.~~ | | RM-J35 |
| 13. | PVAc Emulsion (Union Carbide WC-130) WC431 | 24 | gals. | RM-J25 |
| 14. | Defoamer (liquid) | 0 to 3 | lbs. | RM-J15 |
| 15. | Dibutyphthalate | 0 to 10 | lbs. | RM-J24 |

NOTES: USE - 475- 525

1. Adjust water as required to maintain proper paste consistency.
2. Adjust dispersant (item 12) and defoamer (item 14) as required to maintain proper paste consistency and blending without air entrainment.
3. Adjust glycol (item 11) as required to maintain open time and workability.
4. Adjust yellow oxide as required for specific customer acceptance.
5. Adjust dibutyl phthalate (item 15) as required to maintain bond and water resistance.

MIXING CYCLE:

1. Add 110 gallons of water to mixer, followed by items 11, 12, 13, 14 and 15.
2. Start paste mixer and start dry powder addition. Continue paste mixing until all dry powder has been added.
3. Stop paste mixer and clean sides of mixer.
4. Start mixer and run for five minutes, add five to 10 gallons water, mix one minute and start recirculation of paste.

ANG042004 0012

| | | |
|---|---|---|
| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCT: | PREMIX JOINT COMPOUND<br>DUAL PURPOSE<br>VINYL BASE | BULLETIN NO: JP-12<br>DATE: (4/29/68)<br>PAGE: 4 of 4 |
| | | CANCELS: NEW<br>DATE: |

QUALITY CONTROL: (cont.)

D. Standard Batch

Daily production samples shall be directly compared ( Product Tests) with the Standard Batch at least once per month.

Job problem samples shall be directly compared to the Standard Batch, using all Product Tests. If necessary, because of special job conditions or use of material, additional laboratory testing should be done to duplicate job conditions and to compare problem material with the Standard Batch and with competitive materials.

A new Standard Batch shall be selected by a direct comparison with the Standard Batch, using all Product Tests.

ANIC042004 0013

| | | |
|---|---|---|
| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE JOINT COMPOUND<br>(CASEIN BASE) | BULLETIN NO: ~~3P-15~~ 4P-15<br>DATE: (12/3/68)<br>PAGE: 1 of 2 |
| | | CANCELS: NEW<br>DATE: |

PRODUCING PLANT: Delanco JACKSONVILLE

FORMULA:

| | Item | Amount per Batch | Bulletin |
|---|---|---|---|
| 1. | Mica, P80F | 250.0 lbs. | RM-J7B |
| 2. | Asbestos, Type 7TF1 | 230.0 lbs. | RM-J2A |
| 3. | ~~Methocel 228~~ 7JC | 7.0 lbs. | RM-J26B |
| 4. | Ammonium Oxalate | 8.0 lbs. | RM-J1 |
| 5. | Sodium Tripolyphosphate | 4.0 lbs. | RM-J19 |
| 6. | Casein, ~~2% Surfactol~~ (WOCO) | 90 ~~100.0~~ lbs. | RM-J3 |
| 7. | Sericite, Narvon CEF 2 | 400.0 lbs. | RM-J9 |
| 8. | Titanium Pigment | ~~0 to 50.0 lbs.~~ | RM-J14 |
| 9. | Troysan CMP-10SEP | 3.5 lbs. | RM-J10B |
| 10. | Talc, Asbestine FT | 100.0 lbs. | RM-J11A |
| 11. | Marblewhite 325 | 1000.0 lbs. | RM-J17 |
| 12. | ~~Petro AA~~ | ~~1.0 lbs.~~ | - |
| | Total Batch Weight | 2103.5 lbs. | |

Mixing time shall be 8 minutes minimum and 12 minutes maximum.

PRODUCT SPECIFICATIONS:

| | | |
|---|---|---|
| 1. | Normal Application Consistency (cc. per 100 grams) | 74-82 |
| | a. Viscosity (Mixing water of 150 cc/200 gm) | 150,000 to 275,000 cps |
| 2. | pH (meter) | 8.2 to 9.5 |
| 3. | Open Time @ 65-80°F (minutes) | 15 minimum |
| 4. | Shrinkage (cup method) | 30% maximum |
| 5. | Rate of Wetting (seconds) | 30 maximum |
| 6. | Foaming (area covered) | 50% maximum |
| 7. | Slope Checking @ 100°F | Light checking on thick end. No fissures or cracks. |
| 8. | Grit (total) | 0.05% maximum |
| 9. | a. Tape Bond @ 65-80°F | 3/4" peel (maximum) |
| 10. | Mixing | Equal to Standard (no lumps or dry agglomerates) |
| 11. | Voids | Equal to Standard (8.0 minimum) |
| 12. | Workability | Equal to Standard (8.0 minimum) |

ANG042004 0014

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | PREMIX JOINT COMPOUND<br>DUAL PURPOSE<br>VINYL BASE | BULLETIN NO: J 6908<br>DATE: 12/5/72<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT<br>DELANCO | CANCELS: J 6908<br>DATE: 12/10/71 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 045 | Asbestos 7RF 10 | 2.47 | 150 | |
| 252 | Mica P 85 | 9.87 | 600 | |
| 220 | Whiting | 44.42 | 2700 | |
| 245 | Thickener M/C 228 | 0.39 | 24 | |
| 200 | Keltose | .19 | 12 | |
| 453 | PMA 20SEP | 0.05 | 3 | |
| 470 | UCAR 131 6.23% PVA | 6.35 | 386 | 42 |
| 082 | Carbitol | .56 | 34 | 4 |
| 090 | Colloids #60 | .10 | 6 | |
| | Water | 35.60 | 2164 | 260 max |
| | TOTAL | 100.00 | 6079 | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin J -2.
2. For PMG, add 6 lbs yellow oxide. (RM Bulletin 190).
3. For summer conditions, add 4 gallons of ethylene glycol and adjust thickener to 26 lbs.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity 150 gm cylinder @ 5 sec | 14 - 16 mm |
| TM-31 | Standard Test Viscosity, 150 gm cylinder @ 5 sec., 15 cc per 250 gm paste. | 35 - 38 mm |
| TM-3 | Tape Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY PRODUCTS | JOINT COMPOUND<br>CASEIN BASE | BULLETIN NO: J-6008<br>DATE: 1/30/70<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT<br>DELANCO | CANCELS: 3P-10<br>DATE: 4/25/68 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 220 | Whiting | 65.62 | 1380 | |
| 266 | Mineralite 260 | 2.38 | 50 | |
| 251 | Mica P8OF | 11.89 | 250 | |
| 045 | Asbestos 7RF10 | 10.46 | 220 | |
| 084 | Casein | 7.13 | 150 | |
| 025 | Ammonium Oxalate | 1.04 | 22 | |
| 216 | Hydrated Lime | .28 | 6 | |
| 430 | Sodium Tripolyphosphate | .48 | 10 | |
| 456 | Troysan CMP-10SEP | .24 | 5 | |
| 079 | ~~Cellosize T JC~~ Methocel 228 | .48 | 10 | |
| | TOTAL | | 2103 | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin J-308.
2. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm cylinder @ 5 sec. 200 gm to 150 cc water | 38 - 40 mm |
| TM-3 | Tape Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | JOINT COMPOUND<br>CASEIN BASE | BULLETIN NO: J-6008<br>DATE: 1/30/70<br>PAGE: 2 of 2 |
|---|---|---|
| APPROVALS: | DELANCO | CANCELS: 3P-10<br>DATE: 4/25/68 |

PRODUCT SPECIFICATIONS:

Test Method

| | | |
|---|---|---|
| TM-1 | Viscosity 150 gm cylinder @ 5 sec 200 gm to 150 cc water | 38 - 40 mm |
| TM-1A | Viscosity (Mixing water of 150 cc/200 gm) (Sq. T.C., @ 5 rpm, Helipath motor on) | 150,000 to 325,000 cps |
| TM-2 | pH (Beckman meter) q | 8.3 to 9.3 |
| TM-3 | Tape Bond @ 70°F, @ 40-70% R.H. | 9 - 10 |
| TM-3 | Tape Bond @ 42°F, @ 50-90% R.H. | 8 minimum |
| TM-5 | Open Time @ 70°F (minutes) | 18 minimum |
| TM-9 | Shrinkage (cup method), maximum | 35% |
| TM-10 | Edge Cracking @ 110°F (normal test) | None |
| TM-12 | Grit - percent total | All passing 80 mesh screen 0.05% |
| TM-16 | Rate of Wetting (seconds) | 30 maximum |
| TM-18 | Water Resistance (minutes) | 1 minimum |
| TM-25 | Normal Application Consistency, cc | 76 - 81 |

| PRODUCT BULLETIN DETAIL ACCESSORY PROCESSES | FINISHING COMPOUND CASEIN BASE | BULLETIN NO: J 6128<br>DATE: 2/2/70<br>PAGE: 1 of 1 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT DELANCO | CANCELS: 3F-23<br>DATE: 4/25/65 |

| BULLETIN | DESCRIPTION | % | POUNDS | FILTERS |
|---|---|---|---|---|
| 220 | Whiting | 52.31 | 1100 | |
| 010 | Asbestos 7TF1 | 9.51 | 200 | |
| 203 | Mica P 80F | 11.89 | 250 | |
| 017 | Asbestos SS 210 | 1.43 | 30 | |
| 079 | ~~Pfizite~~ Methocel 228 | .48 | 10 | |
| 121 | Sodium Tripolyphosphate | .28 | 6 | |
| 425 | Ammonium Oxalate | .57 | 12 | |
| 456 | Troysan CXP 10SEP | .14 | 3 | |
| 084 | Casein | 4.28 | 90 | |
| 260 | Mineralite 260 | 19.02 | 400 | |
| 190 | Yellow Oxide | .09 | 2 | |
| | TOTAL | 100.00 | 2103 | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin J 308.
2. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm cylinder @ 5 sec. 200 gm to 150 cc water | 38 - 40 mm |
| TM-3A | Bond | 6 - 7 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to St |

| PRODUCT BULLETIN DRYWALL ACCESSORY PRODUCTS | FINISHING COMPOUND CASEIN BAS... | BULLETIN NO: J 6[illegible]<br>DATE: 2/2.70<br>PAGE: 2 of 2 |
|---|---|---|
| APPROVALS: [illegible] | DELANCO | CANCELS: 3[illegible]-20<br>DATE: 4/25/68 |

PRODUCT SPECIFICATIONS:

| Test Method | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm Cylinder @ 5 sec., 200 gm per 150 cc water | 38 - 4[illegible] mm |
| TM-1A | Viscosity, Brookfield, 200 gm per 150 cc water | 195,000 to 210,000 cps |
| TM-2 | pH (meter) | 8.2 to 9.5 |
| TM-3A | Bond @ 65 - 80°F | 6 - 7 |
| TM-4 | Slope Checking @ 110°F | Light checking on thick end. No fissures or cracks. |
| TM-5 | Open Time @ 65-80°F (minutes) | 18 minimum |
| TM-7 | Workability | Equal to Standard |
| TM-9 | [illegible] | [illegible] maximum |
| TM-11 | Voids | Equal to Standard |
| TM-12 | Grit (total) | 0.05% maximum |
| TM-14 | Foaming (area covered) | 50% maximum |
| TM-15 | Mixing | Equal to Standard (no lumps or dry agglomerates) |
| TM-16 | Rate of Wetting (seconds) | 30 maximum |
| TM-25 | Normal Application Consistency (cc per 100 grams) | 76 to 82 |

BEST COPY OBTAINABLE

ANC042004 0010

| PRODUCT BULLETIN DRYWALL ACCESSORY PRODUCTS | ONE DAY JOINT COMPOUND | BULLETIN NO: J-6368<br>DATE: 9/22/69<br>PAGE: 1 of 3 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT<br>DELANCO | CANCELS: 1P-60<br>DATE: 9/1/68 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 082 | Calcined Gypsum | 25.74 | 500 | |
| 251 | Mica, P80F | 7.72 | 150 | |
| 330 | Polyvinyl Alcohol, Coval 9702 | .76 | 15 | |
| 045 | Asbestos 7RF 10 | 3.35 | 65 | |
| 325 | Polyvinyl Acetate, D702 | 4.12 | 80 | |
| 279 | Natrosol 250 HHXR | .36 | 7 | |
| 430 | Sodium Tripolyphosphate (STPP) | .05 | 1.0 | |
| 456 | Troysan CMP 10SEP | .08 | 1.5 | |
| 320 | Dibutyl Phthalate (Dry liquid | | | |
| | Concentrate) | .38 | 7.5 | |
| 332 | Potassium Sulphate, $K_2SO_4$ | | | |
| | (98% -100 mesh) | .76 | 10-15 | |
| 417 | Sodium Citrate (96% -100 mesh) | .05 | 1.0 | |
| 220 | Whiting | 25.74 | 500 | |
| 186 | Hydrite Flat D Clay | 5.15 | 100 | |
| 082 | Calcined Gypsum | 25.74 | 500 | |
| | TOTAL BATCH WEIGHT | 100.00 | 1943 lbs. | |

MANUFACTURING INSTRUCTIONS:

1. A thorough clean-out with whiting must be made before and after each production run.
2. Wall Texture or Joint Compounds are to be run immediately after a run of this product.
3. Mixing time shall be 8 minutes minimum and 12 minutes maximum.
4. Special orders of SLOW SET One Day Joint Compound can be made by reducing the amount of potassium sulfate (Bulletin No. 332) from 10-15 pounds to 2.5 to 5.0 pounds per batch.

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | ONE DAY JOINT<br>COMPOUND | BULLETIN NO: J-6368<br>DATE: 9/22/69<br>PAGE: 2 of 3 |
|---|---|---|
| APPROVALS:<br>BGK CHF PJF | DELANCO | CANCELS: 1P-60<br>DATE: 9/1/68 |

QUALITY CONTROL:

Test Method

| | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm cylinder @ 5 sec.<br>200 gm to 120 cc water | 38 - 40 mm |
| TM-1A | Viscosity, Brookfield<br>200 gm to 120 cc water | 188,000 to 220,000 cps |
| TM-3 | Bond @ 70°F and 40°F 50% RH | 9 - 10 |
| TM-7 | Workability | Equal to Standard |
| TM-27 | Vicat Set Time, 300 gm needle (hrs) | 1-1/2 - 2 |
| NOTE: | For Slow Set as follows: | |
| | Vicat, 11 gm needle (hrs) | 2 - 2-1/2 |
| | 300 gm needle (hrs) | 2-1/2 - 3 |
| | Δ t (300 m -11 gm) | 10 - 30 minutes |

SPECIFICATIONS:

| | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm cylinder @ 5 sec.<br>200 gm to 120 cc water | 38 - 40 mm |
| TM-1A | Viscosity, Brookfield<br>200 gm to 120 cc water | 188,000 - 220,000 cps |
| TM-27 | Vicat Set, 300 gm needle | |
| | (a) Fast Set (hrs)<br>(b) Slow Set (hrs) | 1 - 1-1/2 |
| | 11 gm needle (hrs) | 2 - 2-1/2 |
| | 300 gm needle (hrs) | 2-1/2 - 3 |
| | Δ t (300 gm -11 gm) | 10 - 30 minutes |
| TM-3 | Tape Bond @ 70F @ 40-70% RH | 9 - 10 |
| | @ 40F @ 50-90% RH | 9 - 10 |
| TM-4 | Slope Bond @ 110F | Excellent |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | ONE DAY JOINT<br>COMPOUND | BULLETIN NO: J-6368<br>DATE: 9/22/69<br>PAGE: 3 of 3 |
|---|---|---|
| APPROVALS:<br>BRK SKK RJF | DELANCO | CANCELS: 1P-60<br>DATE: 9/1/68 |

SPECIFICATIONS: (cont.)

| | | |
|---|---|---|
| TM-9 | Cup Shrinkage @ 70F @ the Set<br>@110F (Dry) | 2% maximum<br>6% maximum |
| TM-10 | Edge Cracking @ 110°F (normal test) | None |
| TM-11 | Voids | Equal to Standard |
| TM-15 | Mixing | Equal to Standard (no lumps or dry agglomerates) |
| TM-21 | Reaction to Iodine | Light Red |
| TM-26 | Paste Density (gms/cc) | 1.40 - 1.50 |

NOTE: One batch of One Day Joint Compound shall be used as a standard for a maximum of 6 months. The code of the Standard Batch shall be recorded in laboratory test records.

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | ONE DAY<br>JOINT COMPOUND | BULLETIN NO: J-6308<br>DATE: 1-27-75<br>PAGE: 1 of 3 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT:<br>DELANCO | CANCELS: J-6308<br>DATE: 3-26-74 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 076 | Calcined Gypsum | 74.93 | 1500 | |
| 417 | Sodium Citrate (98% - 100M) | .05 | 1 | |
| 332 | Potassium Sulfate ($K_2SO_4$) | | | |
| | (98% - 100M) | 0.34 | 7 | |
| 045 | Asbestos 7RF10 | 2.50 | 50 | |
| 245 | Methocel 228 | 0.50 | 10 | |
| 430 | Sodium Tripolyphosphate | 0.05 | 1 | |
| 252 | Mica P65 | 9.99 | 200 | |
| 453 | Preservative | 0.05 | 1 | |
| 166 | Hemaco 277 | 0.80 | 16 | |
| 330 | Polyvinyl Alcohol | 0.80 | 16 | |
| 186 | Hydrite Flat D | 9.99 | 200 | |
| | | | | |
| | TOTAL | 100.00 | 2002 | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. A thorough clean-out with whiting must be made before and after each production run.
2. Wall Texture or Joint Compounds are to be run immediately after a run of this product.
3. Mixing time shall be 8 minutes minimum and 12 minutes maximum.
4. Special orders of SLOW SET One Day Joint Compound can be made by reducing the amount of potassium sulfate (Bulletin No. 332) from 7 pounds to 3 pounds per batch.

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | PREMIX JOINT<br>COMPOUND<br>DUAL PURPOSE<br>VINYL BASE | BULLETIN NO: J 6908<br>DATE: 2/3/70<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: BJF | PRODUCING PLANT<br>DELANCO | CANCELS: 3P-12<br>DATE: 4/25/68 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 050 | Asbestos 7TF 1 | 4.85 | 150 | |
| 079 | Cellosize T JC | .39 | 12 | |
| 220 | Whiting | 35.58 | 1100 | |
| 251 | Mica P8OF | 8.08 | 250 | |
| 261 | Mica, Marvon CEF 2 | 5.67 | 175 | |
| 186 | Clay Hydrite Flat D | 1.62 | 60 | |
| 442 | Asbestine FT | 3.23 | 100 | |
| 456 | Troysan CMP 10SEP | .13 | 4 | |
| 130 | Ethylene Glycol | .74 | 23 | 2.5 |
| 098 | Daxad 30 | .19 | 6 | |
| 470 | PVA Emulsion (6.42% solids) | 7.18 | 222 | 24 |
| | Water | 32.34 | 1000 | 120 |
| | TOTAL | 100.00 | 3092 | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin J 203.
2. For PMG add 3 lbs. yellow oxide. RM Bulletin No. 190.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity 150 gm cylinder @ 5 sec. | 10 - 12 mm |
| TM-31 | Standard Test Viscosity, 150 gm cylinder @ 5 sec, 15 cc per 250 gr paste | 35 - 38 mm |
| TM-3 | Tape Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

| | | |
|---|---|---|
| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | PREMIX JOINT<br>COMPOUND<br>DUAL PURPOSE<br>VINYL BASE | BULLETIN NO: J 6908<br>DATE: 2/3/70<br>PAGE: 2 of 2 |
| APPROVALS | DELANCO | CANCELS: NEW<br>DATE: |

PRODUCT SPECIFICATIONS:

| Test Method | | |
|---|---|---|
| TM-1 | Viscosity Cylinder 150 gm @ 5 sec. | 10 to 12 mm |
| TM-1A | Viscosity, Brookfield, cps | 400,000 to 500,000 |
| TM-2 | pH (Beckman meter) | 7.5 to 9.0 |
| TM-3 | Bond @ 70°F & 40-70% RH (peel) | 9 to 10 |
| TM-5 | Open Time @ 65-80°F (minutes) | 15 minimum |
| TM-5 | Open Time @110-110°F (minutes) | 4 minimum |
| TM-6 | Application | No lumps |
| TM-7 | Workability (Hand or Ames tools) | Equal to Standard |
| TM-9 | Shrinkage (Cup method) | 28% maximum |
| TM-10 | Edge Cracking Test | None |
| TM-12 | Grit (total) | 0.05% maximum. All passing 80 mesh |
| TM-14 | Voids | Equal to Standard |
| TM-18 | Water Resistance (minutes) | 3 minimum |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | PREMIX JOINT COMPOUND<br>DUAL PURPOSE<br>VINYL BASE | BULLETIN NO: J 6908<br>DATE: 11/3/70<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT<br>DELANCO | CANCELS: J 6908<br>DATE: 4/8/70 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 045 | Asbestos 7 RF 10 | 2.48 | 75 | |
| 252 | Mica - P 85 | 9.88 | 300 | |
| 220 | Whiting | 44.49 | 1350 | |
| 079 | Cellosize T JC | .33 | 10 | |
| 200 | Keltose | .16 | 5 | |
| 453 | PMA 20SEP | .05 | 1½ | |
| 470 | UCAR 131 6.23% PVA | 6.36 | 193 | 21 |
| 078 | Carbitol | .49 | 17 | 2 |
| 090 | Colloids #60 | .10 | 3 | |
| | Water | 35.66 | 1082 | 130 ma: |
| | TOTAL | 100.00 | 3036.5 | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin J 203.
2. For PMG add 3 lbs. yellow oxide. RM Bulletin No. 190.
3. For summer conditions, add 2 gals of ethylene glycol and adjust Cellosize to 12 lbs.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity 150 gm cylinder @ 5 sec. | 14 - 16 mm |
| TM-31 | Standard Test Viscosity, 150 gm cylinder @ 5 sec, 15 cc per 250 gm paste. | 35 - 38 mm |
| TM-3 | Tape Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | PREMIX JOINT COMPOUND<br>DUAL PURPOSE<br>VINYL BASE | BULLETIN NO: J 6908<br>DATE: 12/10/71<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT<br>DELANCO | CANCELS: J 6908<br>DATE: 11/3/70 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 045 | Asbestos 7 RF 10 | 2.48 | 75 | |
| 252 | Mica - P 85 | 9.88 | 300 | |
| 220 | Whiting | 44.49 | 1350 | |
| 244 | Methocel 228 | 0.33 | 10 | |
| 200 | Keltose | 0.16 | 5 | |
| 453 | PMA 20SEP | 0.05 | 1.5 | |
| 470 | UCAR 131 6.23% PVA | 6.36 | 193 | 21 |
| 078 | Carbitol | 0.49 | 17 | 2 |
| 090 | Colloids #60 | 0.10 | 3 | |
| | Water | 35.66 | 1082 | 130 max. |
| | TOTAL | 100.00 | 3036.5 | |

## MANUFACTURING INSTRUCTIONS

1. See Process Bulletin J-203.
2. For PMG, add 3 lbs. yellow oxide. (RM Bulletin 190)
3. For summer conditions, add 2 gallons of ethylene glycol and adjust Cellosize to 12 lbs.

## QUALITY CONTROL

| | | |
|---|---|---|
| TM-1 | Viscosity 150 gm cylinder @ 5 sec. | 14 - 16 mm |
| TM-31 | Standard Test Viscosity, 150 gm cylinder @ 5 sec., 15 cc per 250 gm paste. | 35 - 38 mm |
| TM-3 | Tape Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE<br>COMPOUND<br>(POLYMERIC BASE) | BULLETIN NO: J 6416<br>DATE: 7/26/72<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT<br>DELANCO | CANCELS: J 6418<br>DATE: 10/29/71 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 220 | Whiting | 61.24 | 1250 | |
| 251 | AMC Mica | 12.25 | 250 | |
| 260 | Sericite (Narvon) | 12.25 | 250 | |
| 045 | Asbestos 7RF 10 | 4.90 | 100 | |
| 186 | Hydrite Flat D Clay | 4.90 | 100 | |
| 166 | Hamaco 277 Gum | 2.45 | 50 | |
| 330 | Polyvinyl Alcohol | 1.47 | 30 | |
| 244 | Methocel 228 | .48 | 10 | |
| 453 | Preservative | .06 | 1.5 | |
| | TOTAL | 100.00 | 2041.5 | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin No.J308.
2. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, Brookfield 200 gm to 140 cc water | 160,000 - 190,000 cps |
| TM-3 | Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

| | | |
|---|---|---|
| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE<br>COMPOUND<br>(POLYMERIC BASE) | BULLETIN NO: J 6418<br>DATE: 7/26/72<br>PAGE: 2 of 2 |
| APPROVALS: | | CANCELS: J 6418<br>DATE: 10/29/71 |

PRODUCT SPECIFICATIONS:

| Test Method | | |
|---|---|---|
| TM-1A | Viscosity, (mixing water of 140 cc/ 200 gm) | 160,000-190,000 cps |
| TM-2 | pH (Beckman meter) | 8.0-9.2 |
| TM-3A | Bond @ 65-80 F<br>@ 44 F | 9 - 10<br>9 - 10 |
| TM-4 | Slope Checking @ 110 F | Lt checking on thick end. No fissures or cracks. |
| TM-5 | Open Time @ 65-80 F (mins) | 15 minimum |
| TM-7 | Workability (Hand or Ames tools) | Equal to Standard |
| TM-9 | Shrinkage (cup method) | 27% maximum |
| TM-10 | Edge Cracking | Equal to Standard |
| TM-12 | Grit (total) | 0.05% maximum. All passing 80 mesh. |
| TM-14 | Voids | Equal to Standard |
| TM-15 | Mixing | Equal to Standard (no lumps or dry agglomerates) |
| TM-18 | Water Resistance (seconds) | 2 minimum |
| TM-21 | Iodine Test | Light Blue |
| TM-25 | Normal Application Consistency | 68 - 72 |

| PRODUCT BULLETIN DRYWALL ACCESSORY PRODUCTS | 3-PURPOSE COMPOUND (POLYMERIC BASE) | BULLETIN NO: J 6418<br>DATE: 12/22/72<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT DELANCO | CANCELS: J 6418 and J 6408<br>DATE: 7/26/72 and 2/3/70 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 220 | Whiting | 58.63 | 1250 | |
| 251 | AMC Mica | 12.22 | 250 | |
| 260 | Sericite (Narvon) | 12.22 | 250 | |
| 045 | Asbestos 7RF 10 | 4.89 | 100 | |
| 186 | Hydrite Flat D Clay | 4.89 | 100 | |
| 166 | Hamaco 277 | 2.44 | 50 | |
| 330 | Polyvinyl Alcohol | 1.47 | 50 | |
| 244 | Methocel 228 | .48 | 10 | |
| 453 | Preservative | .07 | 1.5 | |
| 164 | Glyoxal | .24 | 5.0 | |
| | TOTAL | 100.00 | 2046.5 | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin J 308.
2. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, Brookfield 200 gm to 140 cc water | 160,000 - 190,000 cps |
| TM-3 | Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |
| TM-35 | 0.25% Boric Acid Test | No firm gel after 1 min. |

| | | |
|---|---|---|
| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE<br>COMPOUND<br>(POLYMERIC BASE) | BULLETIN NO: J 6418<br>DATE: 12/22/72<br>PAGE: 2 of 2 |
| APPROVALS: | | CANCELS: J 6418 and J 6408<br>DATE: 7/26/72 2/3/70 |

PRODUCT SPECIFICATIONS:

Test Method:

| | | |
|---|---|---|
| TM-1A | Viscosity, (mixing water of 140 cc/ 200 gm) | 160,000 - 190,000 cps |
| TM-2 | pH (Beckman meter) | 8.0 - 9.2 |
| TM-3A | Bond @ 65-80 F | 9 - 10 |
| | @ 44 F | 9 - 10 |
| TM-4 | Slope Checking @ 110 F | Lt checking on thick end. No fissures or cracks. |
| TM-5 | Open Time @ 65-80 F (mins) | 15 minimum |
| TM-7 | Workability (hand or Ames tools) | Equal to Standard |
| TM-9 | Shrinkage (cup method) | 27% maximum |
| TM-10 | Edge Cracking | Equal to Standard |
| TM-12 | Grit (total) | 0.05% maximum. All passing 80 mesh |
| TM-14 | Voids | Equal Standard |
| TM-15 | Mixing | Equal to Standard (no lumps or dry agglomerates) |
| TM-18 | Water Resistance (secs) | 2 minimum |
| TM-21 | Iodine Test | Light blue |
| TM-25 | Normal Application Consistency | 68 - 72 |
| TM-35 | 0.25% Boric Acid Test | No firm gel after 1 min. |

ANG042004-0031

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE<br>COMPOUND<br>STARCH BASE | BULLETIN NO: J-6418<br>DATE: 10/29/71<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: EHH<br>BCK 10-13-71 | PRODUCING PLANT<br>DELANCO | CANCELS: NEW<br>DATE: |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 220 | Whiting | 67.59 | 1350 | |
| 251 | Mica AMC | 12.55 | 250 | |
| 442 | Asbestine F-T | 7.53 | 150 | |
| 045 | Asbestos 7RF 10 | 5.02 | 100 | |
| 434 | Starch 50-5453 | 5.02 | 100 | |
| 084 | Casein | 1.26 | 25 | |
| 025 | Ammonium Oxalate | .30 | 6 | |
| 430 | Sodium Tripolyphosphate | .15 | 3 | |
| 244 | Methocel 228 | .35 | 7 | |
| 453 | PMA 20SEP | .08 | 1.5 | |
| 454 | Nopco PD #1 | .16 | 3 | |
| | TOTAL | 100.00 | 1995.5 | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin No. J 308.
2. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, Brookfield 200 gm to 140 cc water | 160,000 - 190,000 cps |
| TM-3 | Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE<br>COMPOUND<br>STARCH BASE | BULLETIN NO: J-6418<br>DATE: 10/29/71<br>PAGE: 2 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT<br>DELANCO | CANCELS: NEW<br>DATE: |

PRODUCT SPECIFICATIONS:

| Test Method | | |
|---|---|---|
| TM-1A | Viscosity, (mixing water of 140 cc/ 200 gm) | 160,000 - 190,000 cps |
| TM-2 | pH (Beckman meter) | 8.2 - 9.2 |
| TM-3A | Bond @ 65-80°F<br>@ 40°F | 9 - 10<br>9 - 10 |
| TM-4 | Slope Checking @ 110°F | Lt checking on thick end. No fissures or cracks |
| TM-5 | Open Time @ 65 - 80°F (mins) | 15 minimum |
| TM-7 | Workability (hand or Ames tools) | Equal to standard |
| TM-9 | Shrinkage (cup method) | 27% maximum |
| TM-10 | Edge Cracking | Equal to standard |
| TM-12 | Grit (total) | 0.05% maximum. All passing 80 mesh |
| TM-14 | Voids | Equal to standard |
| TM-15 | Mixing | Equal to standard (no lumps or dry agglomerates) |
| TM-18 | Water Resistance (seconds) | 2 minimum |
| TM-21 | Iodine Test | Light blue |
| TM-25 | Normal Application Consistency | 68 - 72 |

| RAW MATERIAL BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | ASBESTOS<br>7RF10 | BULLETIN NO: RM-J045<br>DATE: 6/20/72<br>PAGE: 1 of 1 |
|---|---|---|
| APPROVALS: | | CANCELS: RM-J045<br>DATE: 12/4/69 |

USES: Joint and Finish Compounds, Texture Paints

APPROVED SOURCE: Philip Carey

ALTERNATE SOURCE *: Johns-Manville

SPECIFICATIONS:

| | | |
|---|---|---|
| 1. | Mixing Water Requirement | 480 to 550 |
| 2. | Free moisture (200°F) | 2.0% |
| 3. | Color | Light Gray |
| 4. | Grit | 0.05% maximum. All passing 80 mesh screen |
| 5. | Calcium carbonate ($CO_2$ method) | 1.0% maximum |
| 6. | Canadian screen | 0.0-0.0-0.0-16.0 |
| 7. | pH (10% dispersion) | 7-8 |
| 8. | Wet bulking | 250-350 |

The following information is for Kaiser Gypsum Company personnel only:

Testing Schedule: Take a minimum of one 1/2 pound sample from each pallet in shipment, with a maximum of 20 samples. Test two random samples for grit and wet bulking. Test 10 samples for mixing water requirements. Retain a representative sample from each shipment for one year.

SAFETY: Employees should wear respirators when handling, weighing and batching asbestos.

* Use Alternate Source in emergency only due to color. For regular use, Alternate Source must be rechecked by Research and "approved."

| RAW MATERIAL BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | ASBESTOS<br>7TF1 | BULLETIN NO: RM-J050<br>DATE: 6/20/72<br>PAGE: 1 of 1 |
|---|---|---|
| APPROVALS: | | CANCELS: RM-J050<br>DATE: 1/26/71 |

USES: Joint and Finish Compounds, Texture Paints

APPROVED SOURCE: Philip Carey

ALTERNATE SOURCE *: Johns-Manville

SPECIFICATIONS:

| | | |
|---|---|---|
| 1. | Mixing Water Requirement | 330 to 370 |
| 2. | Free moisture (200°F) | 2.0% maximum |
| 3. | Color | Light Gray |
| 4. | Grit | 0.05% maximum. All passing 80 mesh screen |
| 5. | Calcium carbonate ($CO_2$ method) | 1.0% maximum |
| 6. | Canadian screen | 0.0-0.0-0.0-16.0 |
| 7. | pH (10% dispersion) | 7.5-8.5 |
| 8. | Wet bulking | 100-130 |

The following information is for Kaiser Gypsum Company personnel only:

Testing Schedule: Take a minimum of one 1/2 pound sample from each pallet in shipment, with a maximum of 20 samples. Test two random samples for grit and wet bulking. Test 10 samples for mixing water requirements. Retain a representative sample from each shipment for one year.

SAFETY: Employees should wear respirators when handling, weighing and batching asbestos.

* Use Alternate Source in emergency only due to color. For regular use, Alternate Source must be rechecked by Research and "approved."

| RAW MATERIAL BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | ASBESTOS<br>SG 210 | BULLETIN NO: RMJ-047<br>DATE: 6/20/72<br>PAGE: 1 of 1 |
|---|---|---|
| APPROVALS: | | CANCELS: RM-J2D<br>DATE: 9/15/69 |

APPROVED SOURCES: Union Carbide (SG-210)

SPECIFICATIONS:

| | | |
|---|---|---|
| 1. | Magnetite (%) | 2.5 maximum |
| 2. | Reflectance, G. E. Photovolt (%) | 68.0 minimum |
| 3. | Dry Bulk Density, lbs/cu.ft. | 5-6 |
| 4. | Wet Screen, Retain on | |
| | 80 mesh (%) | 0.8 maximum |
| | 325 mesh | 15.0 maximum |

WARNING

Employees should wear respirators when handling, weighing and batching asbestos.

| | | |
|---|---|---|
| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | PREMIX JOINT COMPOUND<br>DUAL PURPOSE<br>VINYL BASE | BULLETIN NO: 3P-12<br>DATE: (4/25/68)<br>PAGE: 1 of 4<br>CANCELS: NEW<br>DATE: |

PRODUCING PLANT: Delanco

FORMULA:

| | ITEM | AMOUNT PER BATCH | BULLETIN |
|---|---|---|---|
| 1. | Asbestos 7TF1 | 150.0 lbs. | RM-J2A |
| 2. | Methocel 228 | 12.0 lbs. | RM-J26B |
| 3. | Marblewhite 325 | 1100.0 lbs. | RM-J17 |
| 4. | Mica, P80F | 250.0 lbs. | RM-J7B |
| 5. | Sericite, Marvon CEF2 | 175.0 lbs. | RM-J9 |
| 6. | Hydrite Clay | 50.0 lbs. | RM-J4A |
| 7. | Asbestine FT | 100.0 lbs. | RM-J11A |
| 8. | Yellow Oxide | 0.0 to 3.0 lbs. | RM-J5 |
| 9. | Troysan CMP-10SEP | 3.0 lbs. | RM-J10B |
| | Dry blending time shall be 8 minutes minimum and 12 minutes maximum. | | |
| 10. | Water (maximum) | 140 lbs. | |
| 11. | Ethylene Glycol | 0 to 2 gals. | RM-J21 |
| 12. | Daxad 30 (dispersant) | 1200 to 2400 cc. | RM-J35 |
| 13. | PVAc Emulsion (Union Carbide WC-130) | 24 gals. | RM-J25 |
| 14. | Defoamer (liquid) | 0 to 3 lbs. | RM-J15 |
| 15. | Dibutyphthalate | 0 to 10 lbs. | RM-J24 |

| | | |
|---|---|---|
| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE JOINT COMPOUND (CASEIN BASE) | BULLETIN NO: 3P-15<br>DATE: (12/3/68)<br>PAGE: 1 of 2<br><br>CANCELS: NEW<br>DATE: |

PRODUCING PLANT: Delanco

FORMULA:

| | Item | Amount per Batch | Bulletin |
|---|---|---|---|
| 1. | Mica, P8OF | 250.0 lbs. | RM-J7B |
| 2. | Asbestos, Type 7TF1 | 230.0 lbs. | RM-J2A |
| 3. | Methocel 228 | 7.0 lbs. | RM-J26B |
| 4. | Ammonium Oxalate | 8.0 lbs. | RM-J1 |
| 5. | Sodium Tripolyphosphate | 4.0 lbs. | RM-J19 |
| 6. | Casein, 2% Surfactol | 100.0 lbs. | RM-J3 |
| 7. | Sericite, Narvon CEF 2 | 400.0 lbs. | RM-J9 |
| 8. | Titanium Pigment | 0 to 50.0 lbs. | RM-J14 |
| 9. | Troysan CMP-10SEP | 3.5 lbs. | RM-J10B |
| 10. | Talc, Asbestine FT | 100.0 lbs. | RM-J11A |
| 11. | Marblewhite 325 | 1000.0 lbs. | RM-J17 |
| 12. | Petro AA | 1.0 lbs. | - |
| | Total Batch Weight | 2103.5 lbs. | |

| PRODUCT BULLETIN DRYWALL ACCESSORY PRODUCTS | 3-PURPOSE JOINT COMPOUND | BULLETIN NO: J 640S<br>DATE: 2/3/70<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT DELANCO | CANCELS: 3P-15<br>DATE: 4/25/68 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALLONS |
|---|---|---|---|---|
| 220 | Whiting | 52.12 | 1100 | 1200 |
| 050 | Asbestos 7TF1 | 9.47 | 200 | 100 |
| 251 | Mica, P80F | 11.84 | 250 | |
| 047 | Asbestos SG 210 | 1.42 | 30 | 100 |
| 280 | Natrosol 16A | .47 | 10 | 8 |
| 430 | Sodium Tripolyphosphate | .28 | 6 | |
| 025 | Ammonium Oxalate | .57 | 12 | |
| 456 | Troysan CMP-10SEP | .14 | 3 | |
| 084 | Casein | 4.74 | 100 | |
| 266 | Mineralite 260 | 18.95 | 400 | |
| | TOTAL | 100.00 | 2111 | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin No. J 30S.
2. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm cylinder @ 5 sec.<br>200 gm to 150 cc water | 38 - 40 mm |
| TM-3 | Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE JOINT<br>COMPOUND | BULLETIN NO: J 6408<br>DATE: 2/3/70<br>PAGE: 2 of 2 |
|---|---|---|
| APPROVALS: | DELANCO - | CANCELS:<br>DATE: |

PRODUCT SPECIFICATIONS:

| Test Method | | |
|---|---|---|
| TM-1 | Viscosity 150 gm cylinder @ 5 sec. | 38 - 40 mm |
| TM-1A | Viscosity (mixing water of 142 cc/ 200 gm) | 150,000 to 275,000 cps |
| TM-2 | pH (Beckman meter) | 8.2 - 9.2 |
| TM-3A | Bond @ 65-80°F | 9 - 10 |
| TM-4 | Slope Checking @ 110°F | Light checking on thick end. No fissures or cracks. |
| TM-5 | Open Time @65-80F (minutes) | 15 minimum |
| TM-7 | Workability (Hand or Ames tools) | Equal to Standard |
| TM-9 | Shrinkage (cup method) | 27% maximum |
| TM-11 | Foaming (area covered) | 50% maximum |
| TM-12 | Grit (total) | 0.05% maximum. All passing 80 mesh |
| TM-14 | Voids | Equal to Standard |
| TM-15 | Mixing | Equal to Standard (No lumps or dry agglomerates) |
| TM-16 | Rate of Wetting (seconds) | 30 maximum |
| TM-18 | Water Resistance (seconds) | 2 minimum |
| TM-25 | Normal Application Consistency | 74 - 80 |

| PROCESS BULLETIN DETAIL ACCESSORY PRODUCTS | FINISHING COMPOUND CASEIN BASE | BULLETIN NO: J 6103<br>DATE: 2/2/70<br>PAGE: 1 of 1 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT DELANCO | CANCELS: 3T-20<br>DATE: 4/25/68 |

| BULLETIN | DESCRIPTION | % | POUNDS | PARTIALS |
|---|---|---|---|---|
| 220 | Whiting | 52.31 | 1100 | |
| 018 | Asbestos 7TF1 | 9.51 | 200 | |
| 2[illegible] | Mica P 80F | 11.89 | 250 | |
| 017 | Asbestos SG 210 | 1.43 | 30 | |
| 079 | ~~Alkaline [illegible]~~ Method 1224 | .48 | 10 | |
| [illegible] | Sodium Tripolyphosphate | .28 | 6 | |
| 025 | Ammonium Oxalate | .57 | 12 | |
| 456 | Troysan CMP 10SEP | .14 | 3 | |
| 084 | Casein | 4.28 | 90 | |
| 266 | Mineralite 260 | 19.02 | 400 | |
| 190 | Yellow Oxide | .09 | 2 | |
| | TOTAL | 100.00 | 2103 | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin J 308.
2. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm cylinder @ 5 sec. 200 gm to 150 cc water | 38 - 40 mm |
| TM-3A | Bond | 6 - 7 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | FINISHING COMPOUND<br>CASEIN BASE | BULLETIN NO: J 6[illegible]<br>DATE: 2/2/70<br>PAGE: 2 of 2 |
|---|---|---|
| APPROVALS: [illegible] | DELANCO | CANCELS: 3[illegible]-20<br>DATE: 4/25/65 |

PRODUCT SPECIFICATIONS:

| Test Method | | |
|---|---|---|
| TM-1 | Viscosity, 150 gm Cylinder @ 5 sec. 200 gm per 150 cc water | 38 - 4[illegible] mm |
| TM-1A | Viscosity, Brookfield, 200 gm per 150 cc water | 195,000 to 2[illegible]0,000 cp. |
| TM-2 | pH (meter) | 8.2 to 9.5 |
| TM-3A | Bond @ 65 - 80°F | 6 - 7 |
| TM-4 | Slope Checking @ 110°F | Light checking on thick end. No fissures or cracks. |
| TM-5 | Open Time @ 65-80°F (minutes) | 18 minimum |
| TM-7 | Workability | Equal to Standard |
| TM-9 | Shrinkage (one method) | [illegible]% maximum |
| TM-11 | Voids | Equal to Standard |
| TM-12 | Grit (total) | 0.05% maximum |
| TM-14 | Foaming (area covered) | 50% maximum |
| TM-15 | Mixing | Equal to Standard (no lumps or dry agglomerates) |
| TM-16 | Rate of Wetting (seconds) | 30 maximum |
| TM-25 | Normal Application Consistency (cc per 100 grams) | 76 to 82 |

BEST COPY OBTAINABLE

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE<br>COMPOUND<br>(POLYMERIC BASE) | BULLETIN NO: J 6416<br>DATE: 2/28/73<br>PAGE: 1 of 2 |
|---|---|---|
| APPROVALS: | PRODUCING PLANT<br>DELANCO | CANCELS: J 6418<br>DATE: 12/22/72 |

| BULLETIN | DESCRIPTION | % | POUNDS | GALL |
|---|---|---|---|---|
| 220 | Whiting | 60.95 | 1250 | |
| 251 | AMC Mica | 12.20 | 250 | |
| 260 | Sericite (Narvon) | 12.20 | 250 | |
| 045 | Asbestos 7RF 10 | 4.88 | 100 | |
| 186 | Hydrite Flat D Clay | 4.88 | 100 | |
| 166 | Hemaco 277 | 2.44 | 50 | |
| 330 | Polyvinyl Alcohol | 1.47 | 30 | |
| 244 | Thickener | .48 | 10 | |
| 453 | Preservative | .07 | 1.5 | |
| 164 | Glyoxal | .24 | 5.0 | |
| 454 | Nopco-PD1 | .15 | 3.0 | |
| | TOTAL | 100.00 | 2049.5 | |
| | | | | |
| | | | | |
| | | | | |

MANUFACTURING INSTRUCTIONS:

1. See Process Bulletin J 308.
2. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

| | | |
|---|---|---|
| TM-1 | Viscosity, Brookfield 200 gm to 140 cc water | 160,000 - 190,000 cps |
| TM-3 | Bond | 9 - 10 |
| TM-6 | Application | Equal to Standard |
| TM-7 | Workability | Equal to Standard |
| TM-35 | 0.25% Boric Acid Test | No firm gel after 1 mi |

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | 3-PURPOSE<br>COMPOUND<br>(POLYMERIC BASE) | BULLETIN NO: J 6418<br>DATE: 12/22/72<br>PAGE: 2 of 2 |
|---|---|---|
| APPROVALS: | | CANCELS: J 6418 and J 6408<br>DATE: 7/26/72 2/3/70 |

PRODUCT SPECIFICATIONS:

Test Method:

| | | |
|---|---|---|
| TM-1A | Viscosity, (mixing water of 140 cc/ 200 gm) | 160,000 - 190,000 cps |
| TM-2 | pH (Beckman meter) | 8.0 - 9.2 |
| TM-3A | Bond @ 65-80 F | 9 - 10 |
| | @ 44 F | 9 - 10 |
| TM-4 | Slope Checking @ 110 F | Lt checking on thick end. No fissures or cracks. |
| TM-5 | Open Time @ 65-80 F (mins) | 15 minimum |
| TM-7 | Workability (hand or Ames tools) | Equal to Standard |
| TM-9 | Shrinkage (cup method) | 27% maximum |
| TM-10 | Edge Cracking | Equal to Standard |
| TM-12 | Grit (total) | 0.05% maximum. All passing 80 mesh |
| TM-14 | Voids | Equal Standard |
| TM-15 | Mixing | Equal to Standard (no lumps or dry agglomerates |
| TM-18 | Water Resistance (secs) | 2 minimum |
| TM-21 | Iodine Test | Light blue |
| TM-25 | Normal Application Consistency | 68 - 72 |
| TM-35 | 0.25% Boric Acid Test | No firm gel after 1 min. |

| RAW MATERIAL BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | ASBESTOS FLOATS<br>7TF1 | BULLETIN NO: RM-J 050<br>DATE: 12/9/69<br>PAGE: 1 of 1 |
|---|---|---|
| APPROVALS:<br>EJK CJB PJF | | CANCELS: NEW<br>DATE: |

USES: Joint and Finish Compounds, Texture Paints

APPROVED SOURCE: Johns Manville (7TF1)
PHILIP CAREY (7TF12)

SPECIFICATIONS:

| | | |
|---|---|---|
| 1. | Mixing Water Requirement | 330 to 370 |
| 2. | Free Moisture (200°F) | 2.0% maximum |
| 3. | Color | Light Gray |
| 4. | Grit | 0.05% maximum. All passing 80 mesh screen |
| 5. | Calcium carbonate ($CO_2$ method) | 1.0% maximum |
| 6. | Canadian screen | 0.0-0.0-0.0-16.0 |
| 7. | pH (10% Dispersion) | 7.5 - 8.5 |
| 8. | Wet Bulking | 110 - 130 |

The following information is for Kaiser Gypsum Company personnel only:

Testing Schedule: Take a minimum of one 1/2 pound sample from each pallet in shipment, with a maximum of 20 samples. Test two random samples for grit and wet bulking. Test 10 samples for mixing water requirements. Retain a representative sample from each shipment for one year.

SAFETY: Employees should wear respirators when handling, weighing and batching asbestos.

| PRODUCT BULLETIN<br>DRYWALL ACCESSORY<br>PRODUCTS | PREMIX JOINT COMPOUND<br>DUAL PURPOSE<br>VINYL BASE | BULLETIN NO: J 6908<br>DATE: 11/3/70<br>PAGE: 2 of 2 |
|---|---|---|
| APPROVALS: | DELANCO | CANCELS: J 6908<br>DATE: 2/3/70 |

PRODUCT SPECIFICATIONS:

Test Method

| | | |
|---|---|---|
| TM-1 | Viscosity Cylinder 150 gm @ 5 sec. | 14 - 16 mm |
| TM-1A | Viscosity, Brookfield, cps | 340,000 to 375,000 |
| TM-2 | pH (Beckman meter) | 7.5 to 9.0 |
| TM-3 | Bond @ 70°F & 40-70% RH (peel) | 9 - 10 |
| TM-5 | Open Time @ 65-80°F (minutes) | 15 minimum |
| TM-5 | Open Time @100-110°F (minutes) | 4 minimum |
| TM-6 | Application | No lumps |
| TM-7 | Workability (hand or Ames tools) | Equal to Standard |
| TM-9 | Shrinkage (cup method) | 28% maximum |
| TM-10 | Edge Cracking Test | None |
| TM-12 | Grit (total) | 0.05% maximum. All passing 80 mesh |
| TM-14 | Voids | Equal to Standard |
| TM-18 | Water Resistance (minutes) | 3 minimum |