



SOUTHWESTERN LABORATORIES

Materials, environmental and geotechnical engineering, nondestructive, metallurgical and analytical services

222 Cavalcade St. • P.O. Box 8768, Houston, Texas 77249 • 713/692-9151

Client
Brownsville Technical Park, Inc.
Mr. Terry L. Entrekin
P.O. Box 5611
Brownsville, Texas 78523-5611

PLAINTIFF'S EXHIBIT

UC-1993

Client No. 2-5335-02
Report No. 88-1878
Report Date 8/16/88

Project Bulk samples submitted for asbestos content analysis. Sampled by the client and received at SwL-Houston on 8/15/88. Analyzed on 8/16/88

RESULTS

<u>Sample I.D.</u>	<u>SwL Lab No.</u>	<u>Asbestos Type</u>	<u>% Asbestos*</u>
P-1	1878-1	None	--
P-2	1878-2	Amosite ¹	40%
P-3	1878-3	None	--
P-4	1878-4	None	--
P-5	1878-5	None	--
P-6	1878-6	None	--
P-7	1878-7	Amosite ¹	45%
P-8	1878-8	Chrysotile	15%
P-9	1878-9	Amosite	40%
P-10	1878-10	None ¹	--
P-11	1878-11	None	--
P-12	1878-12	None	--
P-13	1878-13	None	--
P-14	1878-14	None	--
P-15	1878-15	Chrysotile	1%
P-16	1878-16	Chrysotile	5%

SOUT-WESTERN LABORATORIESClient: **BROWNSVILLE TECHNICAL PARK, INC.**File No.: **2-5335-02**Report No.: **88-1878**Report Date: **8/17/88**

<u>Sample L.D.</u>	<u>SWL Lab No.</u>	<u>Asbestos Type</u>	<u>% Asbestos*</u>
P-17	1878-17	Chrysotile	10%
P-18	1878-18	Amosite	35%
P-19	1878-19	Amosite	35%
P-20	1878-20	Amosite	40%
V-1	1878-21	Amosite	35%
V-2	1878-22	Chrysotile	5%
V-3	1878-23	Chrysotile	10%
V-4	1878-24	None	--
V-5	1878-25	None	--
V-6	1878-26	Chrysotile	2-3%
V-7	1878-27	Amosite	35%
V-8	1878-28	None	--
V-10	1878-29	Chrysotile	10%
V-11	1878-30	None	--
V-12	1878-31	None	--
V-13	1878-32	None	--
V-14	1878-33	Amosite	55%
V-15	1878-34	Chrysotile	2-3%

SOUTHWESTERN LABORATORIES

Client: **BROWNSVILLE TECHNICAL PARK, INC.**

File No.: 2-5335-02

Report No.: 88-1878

Report Date: 8/17/88

<u>Sample C.D.</u>	<u>SwL Lab No.</u>	<u>Asbestos Type</u>	<u>% Asbestos*</u>
V-16	1878-35	Chrysotile	2-3%
V-17	1878-36	None	--

¹ Quality control analysis performed by second analyst.

Technician: Philip Yokley/Martin Gibson

Copies: 3-Locals Chemical Equipment Company

Philip Yokley
Reviewed By

jh

SOUTHWESTERN LABORATORIES

Russell J. Di Raimo
Russell J. Di Raimo, P.E. Manager
Environmental Services

Our letters and reports are for the exclusive use of the client to whom they are addressed. The letters and reports shall not be reproduced except in full without the approval of the testing laboratory. The use of our name must receive our prior written approval.

**SOUTHWESTERN LABORATORIES***Materials, environmental and geotechnical engineering, nondestructive, metallurgical and analytical services*

222 Cavalcade St. • P.O. Box 8788, Houston, Texas 77248 • 713/832-8151

Client Brownsville Technical Park, Inc.
Mr. Terry L. Entrekin
P.O. Box 5611
Brownsville, Texas 78523-5611

Client No. 2-5335-02
Report No. 88-2146
Report Date 9/16/88
P.O. No. 31128

Project Bulk samples submitted for asbestos content analysis. Sampled by the client and received at SWL-Houston on 9/14/88. Analyzed on 9/14/88

RESULTS


<u>Sample I.D.</u>	<u>SWL Lab No.</u>	<u>Asbestos Type</u>	<u>% Asbestos*</u>
36150	2146-1	None	--
36179	2146-2	Amosite	40%
36183	2146-3	None	--
36251 ✓	2146-4	None	--
36289	2146-5	Chrysotile	10%
36406	2146-6	Amosite	40%

Method of Analysis: CFR-47, No. 103, Appendix A (Polarized Light Microscopy)


* The percentage of asbestos is visually estimated.

Technician: Cheryl Remond

Coolest: B. Lander - Chemical Equipment Company

Reviewed By 

SOUTHWESTERN LABORATORIES


Russell J. Di Martino, P.E. Manager
Environmental Services


Our letters and reports are for the exclusive use of the client to whom they are addressed. The letters and reports shall not be reproduced except in full without the approval of the testing laboratory. The use of our name must receive our prior written approval.

11/17/89
Called Southwestern
Lab. for results
Will call me
back today.
233-4478
Called again 11/22/89
msg. left she will
call & call bk.

Sample taken
to Lake - 10/11/89

E

RED = PSI SAMPLE PTS.
BLACK = UCC SAMPLE PTS.



Sample 1 - Liner paper from inside of pipe covering, Tar paper covering, loose pieces of insulation

Sample 2 - Insulation adhering to paper liner of metal pipe covering & paper liner from pipe covering

Sample 3 - Two pieces metal pipe covering with insulation clinging to them, piece of mesh weather barrier paper from lining of pipe covering

Sample 4 - Pieces of metal pipe covering with liner paper & insulation adhering to it, piece of mesh pipe cover, piece of tar paper with insulation

Sample 5 - Metal, paper & mesh pipe covering with insulation residues adhering

Sample 6 - Mesh pipe covering, tar paper & paper liner with insulation adhering

Sampled 11⁰⁰/A to 11²⁰/AM Oct. 2, 1989



SOUTHWESTERN LABORATORIES

Materials, environmental and geotechnical engineering, nondestructive, metallurgical and analytical services

222 Cavalcade St. • P.O. Box 8788, Houston, Texas 77249 • 713/692-8151

Client Union Carbide Corporation
Belia Cortez
Star Rt. Box 90
Brownsville, Texas 78521

Client No.
Report No. 89-11-374
Report Date 12/4/89

Project Bulk samples submitted for asbestos content analysis. Received from SwL-Los Fresnos at SwL-Houston on November 30, 1989. Analyzed on November 30, 1989.

RESULTS

Sample I.D.	Sample Description	SwL Lab No.	Asbestos Type	% Asbestos*	Other Fibrous Constituents %
1	White Fibers w/Black Tar in White Coating	89-11-374-1	Amosite Chrysotile	10 2-3	Cellulose (15) Fibrous Glass (10)
2	White Fibrous Powder with Paper Backing	89-11-374-2	None Detected	—	Cellulose (10)
3	White Cementitious Mix w/Fibers on Metal Backing	89-11-374-3	None Detected	—	Cellulose (10) Fibrous Glass (5-8)
4	White Cementitious Mix w/Fibers on Metal Backing	89-11-374-4	Amosite Chrysotile	5-8 5-8	Fibrous Glass (5-8) Cellulose (5-8)
5	White Cementitious Mix w/Fibers on Metal Backing	89-11-374-5	Amosite Chrysotile	15 5-8	Fibrous Glass (5)
6	White Cementitious Mix w/Fibers on Fabric Backing	89-11-374-6	Chrysotile	10	Fibrous Glass (15)

* The percentage of asbestos is microscopically visually estimated.

Method of Analysis: CFR-47, No. 103, Appendix A (Polarized Light Microscopy)

SwL Houston is an accredited laboratory for bulk asbestos analysis - Laboratory I.D. No. 1502 00.

Samples will be discarded after a storage period of 60 days, unless other arrangements are specified. Results presented pertain to only actual sample analyzed.


Technician: Charles Remkes

Copies: 3-Union Carbide Corporation


Reviewed By

cr

SOUTHWESTERN LABORATORIES


Terry J. Jackson, P.E., Asbestos Manager
Environmental/Analytical Services

Our letters and reports are for the exclusive use of the client to whom they are addressed. The letters and reports shall not be reproduced except in full without the approval of the testing laboratory. The use of our name must receive our prior written approval.

BRD 1268