MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KO 1909 LOT 33725

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2964	1	T 105		
	STUMP			

TOTAL NET WT. _____ PKG. N–CODE _____

PROD. SPVR.	DATE	WHSE. OPER.
JH	1/12/80	

N28587

DUP050095187

25

247

CG 04 CODE KO-909-D PKG. ____

→ JAN 10 33725

EST. WGT. 1674 862 LBS. OK KP

Note: Stump Press

2662

TOTAL WGT. 5274 (Req ____)

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KO-909-D (C)	EWK 1-27-78
		DCG 1-30-78
	TYPED BY	
	NSA 3-13-78	

MAKING NOTES

REMARKS

NAME: KROLOR® ORANGE Y NON-BLEEDING

INSTRUCTIONS – PRESSING – RECORD

VAT	247				
DATE	1-10-80				
TIME	330A				
RELEASED BY	JDC				
PRESS	2	22	23	24	
NO. OF CAKES	~~46~~	~~46~~	~~46~~	~~52~~ 26	

PRESS with AGITATION

WASH TO 2000 OHMS with 135-145° water

TEST AFTER HOURS

LOAD on 6 cars 3

SAMPLES 1-8 oz

DELIVER TO CTL for color

SW

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	630AM				
CAKES USED	96				
WATER ON	1 PM				
HRS. WASHED	6				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	173				

EXPLAIN LOSSES

SAMPLED BY #52 RELEASED BY WP

– DRYING –

DRY 22 HOURS AT 180°F –

LUMP: – OK – WET – SALTS – CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO. CARS PULLED 4 NO. DRUMS 9

SAMPLED BY LUMP WGT. 2698

RELEASED BY WP

– GRINDING –

MILL 938 HSP 1/8" RP SCREEN 3500 RPM

MAX. TEMP. 170°F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING


SAMPLES 1 ENV & 1 PT CAN

DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050095188



DUP050095189