

WRG 001828

GRACE

Construction Products Division

W.R. Grace & Co.
62 Whittemore Avenue
Cambridge, Mass. 02140

(617) 876-1400

May 1, 1986

PLAINTIFF'S
EXHIBIT
WRG-803


Mr. Richard See
Project Manager
Dresser Tower In Cullen Center
601 Jefferson, Suite 360
Houston, Texas 77002

Dear Dick:

We have completed the bulk sample analysis on the three samples you sent us. All three samples were alike and they have the following composition: 6% chrysotile, 67% binder as gypsum and 27% vermiculite by difference. Based on the analytical results, it is concluded that these samples are all alike, and resemble MK-3 composition, but the chrysotile fiber content is lower.

Please let me know if I can be of further assistance. I look forward to seeing the report on your air monitoring results.

Sincerely,



JSH/acd

John S. Hamilton
Manager, Sales/Technical Services

Px SEP. EX. NO. 8
FOR ID., AS OF 8/13/91 ny

TAMARA ELITE YELSON
deposition
EXHIBIT 151
3-8-91