CG 46 CODE YC-11-A PKG. ____

→ NOV -3 80 37695

EST. WGT. 2238 LBS.

MEMBRANE PRESS

106

#105 centrifugal pump

2 ge

88 - 180°F in VAT

PROCESSES	APPROVED B
(D) YC-11-A	EWK 9-28-7
	BBK 10-17-7
	DCG 11-29-7
TYPED BY	
JTC 12-8-77	

MAKING NOTES

REMARKS

no Back Pressure 49" left in vat no bleeds.

NAME: DALAMAR® YELLOW

BLEEDING

E.C. INSTRUCTIONS -PRESSING- RECORD

±20" in vat no A.P. no bleeds

VAT	106				
DATE	11-4-80				
TIME	7:50 Am				
RELEASED BY	PCH				
PRESS	32	33	35	M1	
NO. OF CAKES	60	62	60	62	

PRESS WITHOUT AGITATION

WASH TO 4000 OHMS WITH 35-75°F WATER

TEST AFTER 4 HOURS

LOAD IN METAL DRUMS AT 325# NET PER DRUM

~~AIR BLOW PRESSURE 15 MIN AT 40PSI~~

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	12 10 am	12 40 pm	1 10 pm		
CAKES USED	21	21	20		
WATER ON	2 05 pm				
HRS. WASHED	1				
OHMS	3000+				
HRS. WASHED	1½				
OHMS	5000				
HRS. WASHED	Start squeeze 3 45 pm				
OHMS	Finish squeeze 44 5 pm —				
CAKE CONDITION			197 PSI - 58# air -		
NO. CARS LOADED			Pump stalled out		
EXPLAIN LOSSES			±4 times - Ready to drop ±5 15 pm		

Back pressure up to ±20" when vat washed in

SAMPLES THIEF SAMPLE & FILL 1-8 oz. jar + 1 qt Sample

DELIVER TO CTL for color

SAMPLED BY J. Oster RELEASED BY

-DRYING-

DRY — HOURS AT — °F

DO NOT DRY

LUMP: - OK - WET - SALTS - CONTAMINAT

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS

SAMPLES

NO. CARS PULLED

LUMP WGT.

DELIVER TO

SAMPLED BY

RELEASED BY

-GRINDING-

MILL SCREEN RPM

MAX. TEMP. °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

DATE MIXED

SAMPLES

DELIVER TO C T L

SAMPLED BY

RELEASED BY

N35199

RW-252