

PLASTICIZER VOLATILITY FROM VINYL FILM

200 Cm² Surface Area
10 mil Thick, 70 phr Plasticizer.

<u>Plasticizer</u>	<u>Concentration (µg/Liter)</u>		
	<u>23°C</u>	<u>58°C</u>	<u>87°C</u>
Dibutyl Phthalate	-	3.7	-
Diisohexyl Phthalate	-	0.96	-
Santicizer 160	0.0027	0.23	-
Dioctyl Phthalate	0.001	0.085	2.9
Diisononyl Phthalate	-	0.020	1.5
Di-n-Octyl-n-Decyl Phthalate	-	-	1.3
Santicizer 711	-	0.015	0.70
Diisodecyl Phthalate	-	-	0.33
Ditridecyl Phthalate	-	-	≤0.019
Diundecyl Phthalate	-	-	≤0.005
Santicizer 79 TM	-	-	≤0.0009

DSW 587830

STLCOPCB4093166