Your guide to...



TOP-QUALITY PLASTICIZERS

Here are plasticizers and resin modifiers for any and every resin system!

No matter what the application or performance specification, one or a combination of the plasticizers offered here will do the job. As shown here, you can select from the widest choice of plasticizers available from any single source. They are recommended for use in compounding:

Flexible Film and Sheeting	Casting Compounds
Adhesives	Extrusions
Lacquers	Plastisols
Sealing Compounds	Fabric & Paper Coatings
Paints	

YOU CAN DEPEND UPON THESE PRODUCTS' QUALITY AND PERFORMANCE

open once for "Compatibility" guide • open fully for a listing of products and properties

0614521

TOWOLDMON0006065

PHTHALATES

		Dibutyl	Dicyclohexyl	Diethyl	Diisodecyl	Diisooctyl	Dimethyl	Di(n-octyl, n-decyl)	Dioctyl	Diphenyl	Ditridecyl	Santicizer® 160	Santicizer 165	Santicizer 213	Santicizer 214	Santicizer 215	Santicizer 262	Santicizer 278	Santicizer 602	Santicizer 603	Santicizer 630	Santicizer 631	Santicizer 632	Santicizer 636	Santicizer 681	Santicizer 683
VINYL TYPE	Polyvinyl Chloride	100	30	I	100	100	I	100	100	80	100	100	100	100	100	100	100	100	100	100	100	100	100	90	100	
	Polyvinyl Acetate	100	50	100	I	I	100	I	I	70	I	100	I	10	I	I	40	75	I	I	I	I	I	I	I	
	Polyvinyl Butyral	100	50	50	25	15	50	15	15	50	25	100	10	50	20	30	20	75	25	25	25	25	20	25	5	20
	Polyvinylidene Chloride	75	20	75	10	25	50	25	25	20	10	75	50	25	10	15	25	50	15	20	25	25	10	25	20	10
	Polystyrene	100	20	100	100	100	100	100	50	70	100	100	100	75	75	100	50	75	100	100	100	100	75	100	60	75
CELLULOSIC	Nitrocellulose	100	50	100	100	100	60	100	100	80	100	100	100	40	40	40	100	100	100	100	50	60	40	100	70	40
	Ethyl Cellulose	100	50	100	100	100	100	100	100	30	100	100	100	75	75	100	100	75	100	100	100	100	75	100	80	75
	Cellulose Acetate	25	I	85	I	I	80	I	I	I	I	10	I	I	I	I	I	I	I	I	I	I	I	I	I	I
	Cellulose Acetate Butyrate	100	20	100	50	50	100	50	50	20	50	100	50	40	20	40	50	75	50	40	25	30	20	50	35	20
	Cellulose Acetate Propionate	30	10	100	15	20	100	20	20	10	15	80	50	20	5	I	25	50	20	40	5	10	5	20	5	5
MISCELLANEOUS THERMOPLASTIC	Chlorinated Rubber	100	20	25	100	100	25	50	33	20	100	80	100	25	25	100	30	50	100	50	100	100	25	100	100	25
	High Styrene Butadiene	50	20	25	50	50	20	50	50	20	50	50	50	40	40	40	50	30	50	50	40	40	40	50	35	40
	Protein Compounds	20	I	20	I	I	20	I	I	I	I	10	I	I	I	I	I	I	I	I	I	I	I	I	I	I
	Shellac	I	I	5	I	I	5	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I
	Acrylic Type Resins	70	25	100	25	25	100	25	25	25	25	70	25	15	I	20	70	50	25	25	10	10	I	25	I	I
	Polyamides	25	10	I	20	25	I	25	25	10	20	25	25	I	I	5	20	10	20	20	I	I	I	20	25	I
THERMOSETTING	Polyester	20	20	10	15	20	5	20	20	20	15	20	20	5	5	5	15	10	10	15	5	5	5	10	5	5
	Epoxy	25	10	10	I	I	I	I	I	10	I	25	10	I	I	I	15	15	I	10	I	I	I	I	I	I
	Phenolic	50	25	25	25	25	25	25	25	30	25	50	50	25	25	25	25	30	25	25	25	25	25	25	25	25
	Alkyd	70	25	25	25	25	25	25	25	25	25	50	50	25	25	20	25	30	25	25	25	25	25	25	25	25
	Melamine	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I	I
	Polyurethane	25	10	15	25	25	15	25	25	10	25	25	25	20	20	20	25	15	25	25	20	20	20	25	20	20
	Nitrile & Neoprene Rubbers	100	50	100	33	100	100	100	50	50	33	100	50	50	50	40	70	60	50	50	50	50	50	50	65	50

I = Incompatible Figures = Compatibility, PHR

0614522

TOWOLDMON0006066

Compatibility Guide

ADIPATES			PHOSPHATES				PHOSPHATES					PHTHALYL GLYCOLLATES				Permanent									MISCELLANEOUS			
Diisodecyl	Dioctyl	Di(n-octyl, n-decyl)	Santicizer 140	Santicizer 141	Tributoxyethyl	Tricresyl	Triphenyl	Santicizer 1-H	Santicizer 3	Santicizer 8	Santicizer 9	Santolite® MHP	Santolite MS-80%	Santicizer E-15	Santicizer B-16	Santicizer M-17	Santicizer 405	Santicizer 406	Santicizer 409	Santicizer 411	Santicizer 462	Santicizer 480	Santicizer 481	Santicizer 482	Santicizer 483	Aroclor®	HB-40®	Mod-Epox®	Montar®	Triphenyl Phosphite
50	75	75	100	100	60	100	20	1	1	1	1	15	15	25	100	20	100	100	100	100	100	100	100	100	100	35	40	10	10	10
1	1	1	40	50	40	40	80	50	50	100	50	50	50	100	100	100	75	80	100	75	1	20	50	100	1	50	1	1	10	1
1	25	1	100	100	50	100	50	50	50	100	50	50	50	100	100	100	40	40	75	40	15	30	30	50	15	50	50	1	10	1
10	15	15	75	75	50	75	20	20	25	50	20	25	25	75	75	75	10	10	25	10	25	10	10	15	25	50	20	1	10	1
25	100	20	15	50	100	15	20	10	10	20	10	10	10	30	30	30	1	1	50	1	50	40	20	1	50	100	100	1	10	1
35	35	35	100	100	100	100	75	75	80	80	50	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	10	1	10	1
100	100	50	70	100	50	70	30	80	60	60	75	75	75	75	75	75	10	10	33	10	100	50	75	25	100	75	100	5	15	5
1	1	1	35	20	10	15	35	20	45	90	30	25	25	100	50	100	1	1	1	1	1	1	1	1	1	1	1	1	1	1
50	25	25	30	80	25	30	50	40	40	50	25	50	50	100	50	100	100	100	100	100	50	70	80	80	50	50	30	5	10	5
1	1	1	40	100	40	40	50	50	50	100	50	50	50	100	50	100	50	50	10	50	20	40	40	50	20	10	1	1	1	1
100	100	100	100	100	100	100	50	25	25	50	25	50	50	80	80	100	50	50	50	50	50	70	50	50	50	100	100	5	10	5
20	20	20	50	50	50	50	20	25	25	25	25	25	25	50	50	50	15	15	25	10	33	30	20	20	40	50	25	1	20	1
1	1	1	20	25	10	30	10	30	30	50	40	25	25	25	40	20	1	1	1	1	1	1	1	1	1	1	1	1	1	1
1	1	1	1	1	1	1	1	25	25	40	60	25	25	10	30	10	1	1	1	1	1	1	1	1	1	1	1	1	1	1
1	1	1	25	100	25	25	25	25	25	25	25	25	25	50	70	60	1	1	1	1	70	10	10	10	50	10	20	1	1	1
25	25	25	25	25	15	25	10	50	50	50	25	50	50	1	20	1	1	1	1	1	25	20	15	1	25	25	1	1	10	1
1	1	1	20	20	20	20	10	5	5	10	5	20	20	5	20	5	5	5	10	5	20	15	20	10	20	25	1	5	10	1
1	1	1	25	25	25	25	10	20	20	50	50	25	25	25	25	25	1	1	1	1	1	1	1	1	50	1	100	25	100	
25	25	25	50	50	50	50	50	50	50	50	50	50	50	50	50	50	15	15	25	15	25	25	15	15	25	25	25	25	25	25
25	50	25	70	70	50	70	50	40	30	25	25	25	25	70	70	70	20	20	25	20	25	20	25	20	25	25	15	5	25	0.5
1	1	1	1	1	1	1	1	25	25	50	80	25	25	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
15	15	15	25	25	25	25	10	10	10	20	10	25	25	25	25	25	10	10	15	10	25	25	15	10	25	25	15	1	10	1
33	20	33	33	40	50	55	50	50	50	50	50	50	50	50	50	50	25	25	50	25	50	25	25	30	50	50	50	25	50	25

0614523

TOWOLDMON0006067

Monsanto

PLASTICIZERS

For the Widest Choice in the World



We can ship you plasticizers and other chemicals promptly out of nearby stocks. You may find it economical and convenient to place combination orders for plasticizers and other chemicals for delivery at the same time.

Let us help you on all your needs for plasticizers and other chemicals for processing, formulation maintenance.

For further information contact the nearest Monsanto District Sales Office:

ATLANTA, GEORGIA 30326
Lenox Towers West, 3390 Peachtree Rd. N.E., Tel. (404) 231-4320

BOSTON, MASSACHUSETTS 02149
Everett Station, Tel. (617) 387-5010

CHICAGO, ILLINOIS
3158 Des Plaines Ave., Des Plaines, Illinois 60018, Tel. (312) 296-6688

CINCINNATI, OHIO 45206
1501 Madison Road, Tel. (513) 751-6707

CLEVELAND, OHIO 44122
3645 Warrensville Center Rd., Tel. (216) 991-5400

DETROIT, MICHIGAN 48235
500 Northland Towers, Tel. (313) 357-0910

HOUSTON, TEXAS 77002
1300 Main Street, Tel. (713) Capitol 3-4011

LOS ANGELES, CALIFORNIA 90022
6670 E. Flotilla St., Tel. (213) Raymond 3-2492

MINNEAPOLIS, MINNESOTA 55402
912 Northstar Center 110 S. Seventh St., Tel. (612) 339-4651

NEW YORK, NEW YORK 10017
277 Park Avenue, Tel. (212) 922-4111

PITTSBURGH, PENNSYLVANIA 15222
No. 4 Gateway Center Bldg. Room 534, Tel. (412) 261-2156

ST. LOUIS, MISSOURI 63166
800 N. Lindbergh Blvd., Tel. (314) Wydown 3-1000

SAN FRANCISCO BAY AREA
2710 Lafayette, Santa Clara, Calif. 95052, Tel. (408) 243-0414

SEATTLE, WASHINGTON 98104
911 Western Avenue, Tel. (206) Main 2-4203

SPRINGFIELD, MASSACHUSETTS 01101
730 Worcester Ave., Tel. (413) 788-6911

WILMINGTON, DELAWARE 19803
2005 Concord Pike, Fairfax, Tel. (302) Olympia 8-6531

U614524

2-22486-10M-62 LITHO IN U.S.A.

TOWOLDMON0006068

Plasticizer	Molecular Weight	Acidity (meq./100 gm max)	Appearance	Color (APHA) (maximum)	Moisture (K-F in methanol) (% maximum)	Odor	Refractive Index (at 25°C)	Specific Gravity (25°/25°C)	Density (at 25°C) (lb./gal.)	Crystallizing Point (°C)
PHTHALATES										
Dibutyl	278.34	* 0.12	* Clear, oily liquid	* 20	* 0.15	* Slight, characteristic	1.4895 to 1.4915	* 1.044 to 1.048	8.72	< -35
Dicyclohexyl	330.46	* 0.12	* White lumps or granules	* 300 (molten)	* 0.1	* Moderate, aromatic, slight phthalic, characteristic	—	1.29		
Diethyl	222.11	* 0.12	* Clear, oily liquid	* 10	* 0.15	* Slight, aromatic, mild	1.4990 to 1.5010	* 1.115 to 1.119	9.35	< 0.3
Dihexadecyl	446.65	* 0.12	* Clear, oily liquid	* 50	* 0.10	* Slight, characteristic	1.4784 to 1.4864	* 0.963 to 0.969	8.09	53 (with clear gel)
Dioctadecyl	390.53	* 0.12	* Clear, oily liquid	* 25	* 0.10	* Slight, characteristic, mild	1.4810 to 1.4880	* 0.980 to 0.985	8.21	45
Dimethyl	194.18	* 0.12	* Clear, oily liquid	* 10	* 0.25	* Slight, aromatic, mild	1.5123 to 1.5143	* 1.188 to 1.192	9.92	0.0 (or -2°C bath)
Dioctyl-octyldecyl	418 (average)	* 0.01	* Clear, oily liquid	* 50	* 0.10	* Slight, characteristic	* 1.4810 to 1.4840	* 0.9680 to 0.9770	8.1	30
Dioctyl	390.53	* 0.12	* Clear, oily liquid	* 25	* 0.10	* Slight, characteristic, mild	1.4845 to 1.4858	* 0.980 to 0.985	8.21	55 (very stiff gel)
Diphenyl	218.31	* 1.20	* Essentially white, fused solid with a slightly yellow or brown cast	* 160 (20ml. 50ml acetone)	0.25		1.572 @ 74°C	1.28		
Ditridecyl	530	* 0.12	* Clear, oily liquid	* 100	* 0.1	* Clear, characteristic	* 1.4813 to 1.4850	* 0.848 to 0.855	7.03	
Santicizer® 160	317.35	* 0.01	* Clear, oily liquid	* 40	* 0.15	* Slight, characteristic, mild	* 1.535 to 1.540	* 1.115 to 1.123	9.3	< -35
Santicizer 165	—	* 0.12	* Clear, oily liquid	* 40	* 0.12	* Slight (similar to DOP)	* 1.484 to 1.487	* 0.990 to 0.998	8.28	—
Santicizer 213	—	* 0.25	* Clear, oily liquid	* 75	* 0.15	Characteristic, very low	* 1.501 to 1.524	* 1.040 to 1.045	8.68	—
Santicizer 214	—	* 0.15	* Clear, oily liquid	* 100	* 0.15	Characteristic, very low	* 1.481 to 1.486	* 0.948 to 0.956	7.9	—
Santicizer 215	—	* 0.12	* Clear, oily liquid	* 100	* 0.10	Characteristic	* 1.508 to 1.516	* 0.974 to 0.980	8.14	—
Santicizer 262	396.5	* 0.07	* Clear, oily liquid	* 100	* 0.15	—	* 1.518 to 1.523	* 1.048 to 1.057	8.7	—
Santicizer 278	411	* 0.24	* Clear, oily liquid	* 100	* 0.15	Slight characteristic	* 1.5170 to 1.5203	* 1.096 to 1.101	9.18	below -33
Santicizer 402	—	* 0.18	* Clear, oily liquid	* 50	* 0.10	* Characteristic, mild	* 1.482 to 1.486	0.911 to 0.917	8.1	—
Santicizer 403	—	* 0.12	* Clear, oily liquid	* 100	* 0.10	Characteristic	* 1.4825 to 1.4895	* 0.937 to 0.967	8.18	—
Santicizer 430	—	* 0.12	* Clear, oily liquid	* 10	* 0.10	—	* 1.5095 to 1.5160	* 0.987 to 0.994	8.25	—
Santicizer 431	—	* 0.12	* Clear, oily liquid	* 40	* 0.20	—	* 1.4990 to 1.5045	* 0.984 to 0.990	8.27	—
Santicizer 437	—	* 0.12	* Clear, oily liquid	* 100	* 0.15	—	* 1.484 to 1.487	* 0.916 to 0.967	8.15	—
Santicizer 436	—	* 0.12	* Clear, oily liquid	* 75	* 0.10	—	* 1.478 to 1.488	* 0.969 to 0.977	8.11	—
Santicizer 601	—	* 0.20	* Clear, oily liquid	* 60	* 0.10	—	* 1.477 to 1.478	* 0.963 to 0.970	8.05	—
Santicizer 883	—	* 0.12	* Clear, oily liquid	* 40	* 0.10	—	* 1.488 to 1.489	* 0.973 to 0.981	8.09	—
ADIPATES										
Dioctyl	445.0	* 0.50	* Clear, oily liquid	* 50	* 0.10	* Mild	1.4485 to 1.4525	* 0.962 to 0.973	7.65	< -50
Dioctyl-octyldecyl	398 (average)	* 0.35	* Clear, oily liquid	* 50	* 0.10	Characteristic	* 1.444 to 1.450	* 0.914 to 0.922	7.63	-5
Dioctyl	370.56	* 0.25	* Clear, oily liquid	* 25	* 0.10	* Mild	1.444 to 1.448	* 0.921 to 0.931	7.72	-70
PHOSPHATES										
Tricresyl	368.38	* 0.20	* Clear, oily liquid	* 75	* 0.15	* No foreign odor	1.556	* 1.157 to 1.173	9.7	< -35
Triphenyl	326.31	* 0.06	* White flakes	20 (molten	—	* Very faint aromatic, mild	1.550 (66 80°C)	1.264 (60° 20°C)	10.5	49
Santicizer 140	340.2	* 0.20	* Clear, oily liquid	* 40	* 0.15	* Essentially odorless	1.550 to 1.570	* 1.203 to 1.213	10	< -35
Santicizer 141	362.40	* 0.20	* Clear, oily liquid	* 60	* 0.10	* Slight, sweet	* 1.507 to 1.510	* 1.089 to 1.093	9.1	—
Tributoxyethyl	398	* 1.0	* Clear, oily liquid	* 75	* 0.20	* Characteristic, mild	* 1.434 to 1.438	* 1.037 to 1.043	8.62	-70
Trilauryl	764.33	* 0.14	* Clear, oily liquid	* 25	* 0.20	* Characteristic	* 1.427 to 1.429	* 0.913 to 0.918	8.14	< -80
GLYCOLATES										hypergolic
Santicizer E-15	280.27	* 0.17	* Clear, oily liquid	* 20	* 0.15	* Slight, mint	1.496 to 1.500	* 1.180 to 1.185	9.85	-20 (supercools readily)
Santicizer B-16	336.37	* 0.33	* Clear, oily liquid	* 45	* 0.15	* Slight, characteristic	1.488 to 1.492	* 1.095 to 1.105	9.13	< -35
Santicizer M-17	266.24	* 0.33	* Clear, oily liquid	* 20	* 0.15	* Slight, characteristic, mild	1.504	* 1.217 to 1.221	10.20	< -35
SULFONAMIDES										
Santicizer 1-N	253.36	—	* Yellow-brown fused mass	* 300 (molten)	* 0.15	—	—	1.125		+6 (vacuum jacket) -0.5 wks
Santicizer 3	199.23	* 1.60	* Practically white solid	* 60 (molten)	* 0.25	—	1.532 to 1.532 (65°C)	1.166 to 1.176 (45° 65°C		* 54.0 min
Santicizer 8	199.22	* 0.80	* Light yellow, viscous liquid free of turbidity or extraneous matter	* 200 (molten)	—	* Slight, characteristic	1.540	1.190	9.92	< -40
Santicizer 9	171.1	pH 4.0 min.	* Fine, white to light cream, granular particles	* 85 -33% wt. % in acetone	* 1.0	Essentially none	—	1.353 (solid)		105
Santolink® MNP	—	meq. KOH g.	* Hard, practically colorless resin	* 50 -25g. 75g butyl acetate)	—	Faint formaldehyde	1.4275 to 1.4325 -25g. 75g butyl acetate)	1.35		62
Santolite MS 80%			* Light colored, viscous liquid. Free flowing above 20°C	* 80 -25g. 25g butyl acetate)				1.206	10.5	
PERMANENT										
Santicizer 405	—	* 2.0	* Clear, viscous liquid	* 250 -50ml. 50ml 95% ethanol)	* 0.15	* Characteristic	1.478	* 1.128 to 1.132	9.41	
Santicizer 406	—	* 2.0	* Clear, oily liquid	* 200 -50ml. 50ml 95% ethanol)	* 0.15	* Very characteristic	1.478	* 1.089 to 1.093	9.08	
Santicizer 408	—	* 1.0	* Clear, liquid	* 150 -50ml. 50ml 95% ethanol)	* 0.15	Very faint ester	1.4654	* 1.080 to 1.084	9.01	
Santicizer 411	—	* 1.0	* Slightly yellow, viscous liquid, some solids on standing	* 175 -50ml. 50ml 95% ethanol)	* 0.15	* Slight, characteristic	1.4772	* 1.104 to 1.110	9.20	
Santicizer 467	—	* 0.24	* Clear, oily liquid	* 150	* 0.15	Characteristic	* 1.500 to 1.510	* 1.072 to 1.077	8.95	
Santicizer 480	—	* 0.60	* Clear, oily liquid	* 200	* 0.15	Slight, characteristic	1.4943	* 1.039 to 1.046	8.72	
Santicizer 481	—	* 0.85	* Clear, oily liquid	* 300	* 0.15	Slight, characteristic	1.4795	* 1.077 to 1.078	8.96	
Santicizer 482	—	* 1.1	* Clear, oily liquid	* 325	* 0.15	Slight, characteristic	1.4783	* 1.087 to 1.103	9.16	
Santicizer 483	—	* 0.24	* Clear, oily liquid	* 125	* 0.15	Slight, characteristic	* 1.5015 to 1.5050	* 1.045 to 1.057	8.74	
OTHER										
HB 40®		* 0.08 meq KOH g.	Practically colorless, oily liquid	* 150	* 125 ppm	Faint characteristic	1.5600 to 1.5760	* 1.001 to 1.007 25° 15.5°C	8.37	
Mod. Lipo®			* Oily liquid or light yellow solid	* 50	—	—	* 1.507 to 1.590	* 1.176 to 1.182 30° 15.5°C	9.83	25
Phosgard® C 22 R	610.5	* 5	* Clear, viscous liquid	* 50	—	Essentially none	* 1.492 to 1.494	* 1.425 to 1.445	11.9	None glassy
Triphenyl Phosphite	310.28	* 0.10 meq KOH g.	* Oily liquid or light-yellow solid	* 50	—	—	* 1.587 to 1.590	* 1.176 to 1.182 30° 15.5°C	9.83	25

GENERAL PROPERTIES OF REPRESENTATIVE AROCLOR® PLASTICIZERS AND RESINS (*MONSANTO SPECIFICATIONS)

PROPERTY	AROCLOR 1221	AROCLOR 1232	AROCLOR 1242	AROCLOR 1248	AROCLOR 1254	AROCLOR 1260	AROCLOR 1262	AROCLOR 5442	AROCLOR 5460	AROCLOR 1268
Appearance	Clear, mobil oil	Clear, mobil oil	*Clear, mobil oil	*Clear, mobil oil	Light-yellow viscous oil	*Light-yellow soft sticky resin	*Light-yellow sticky resin	*Yellow clear, sticky resin	*Light-yellow, clear brittle resin	*White to off-white powder
Color, maximum	*50 APHA	*100 APHA	*100 APHA	*100 APHA	*100 APHA	*150 APHA	*150 APHA	*2 NPA (molten)	*2 NPA (molten)	*2 NPA (molten)	1.5 NPA (molten
Chlorine, per cent	20.5-21.5	31.5-32.5	42	48	54	60	61.5-62.5	42	65	58.5-60.5	68
Acidity, mg KOH g. maximum	*0.014	*0.014	*0.015	*0.010	*0.10	*0.014	*0.014	0.05	0.5	0.5	0.05
Moisture, ppm. maximum	—	—	*50	*50	*50	*50	—	—	—	—	—
Avg. Coefficient of Expansion cc/cc/°C	0.00077 (15°-60°C)	0.00073 (25°-100°C)	0.00068 (25°-65°C)	0.00070 (25°-65°C)	0.00066 (25°-65°C)	0.00063 (20°-100°C)	0.00064 (25°-65°C)	0.00073 (25°-90°C)	0.00061 (25°-65°C)	0.00079 (25°-24°C)	0.00067 (25°-100°C)
Specific Gravity	*1.182-1.192 (25°-25°C)	*1.270-1.280 (25°-15.5°C)	*1.381-1.392 (25°-15.5°C)	*1.455-1.465 (25°-15.5°C)	*1.495-1.505 (25°-15.5°C)	*1.555-1.566 (90°-15.5°C)	*1.377-1.383 (90°-15.5°C)	1.470 (25°-25°C)	1.670 (25°-25°C)	1.670 (25°-25°C)	1.804-1.807 (25°-25°C)
Density, pounds per gallon 25°C	9.85	10.55	11.50	12.04	12.82	13.50	13.72	12.24	13.91	13.91	15.09
Distillation Range °C, corrected -ASTM D 20 modified-	275-320	290-325	325-366	340-375	365-390	385-420	390-425	215-300 (4 mm. Hg)	230-320 (4 mm. Hg)	280-335 (5 mm. Hg)	425-450
Evaporation Loss, % 105°C, 6 hours -ASTM D 6, mod.; 163°C, 5 hours	1.0-1.5	1.0-1.5	0.0-1 3.0-3.6	0.0-3 3.0-4.0	0.0-2 2.1-2.9	0.0-1 0.5-0.8	0.0-1 0.5-0.6	0.01 0.2	0.0-20 0.2-0.3	0.03	0.0-06 0.1-0.7
Flash Point (Cleveland Open Cup), °C °F	141-150 286-302	152-154 305-310	176-180 348-356	193-196 379-384	NONE	NONE	NONE	241 471	NONE	NONE	NONE
Fire Point (Cleveland Open Cup), °C °F	176 349	238 460	NONE**	NONE	NONE	NONE	NONE	350 662	NONE	NONE	NONE
Pour Point (ASTM D-97), °C °F	1 (crystals) 34 (crystals)	-35.5 32	-19 2	-1 19.4	10 50	31 88	25-30 99	-46 115	—	—	—
Softening Point (ASTM E-28), °C °F	—	—	—	—	—	—	—	*46-52 115-126	*60-66 140-151	*88-105.5 190-222	*150-170 (Ball and Ring) 302-338 (Ball
Refractive Index, n $\frac{25}{D}$ @ 20°C	1.617-1.619	1.620-1.622	1.627-1.629	1.630-1.631	1.639-1.641	1.647-1.649	1.6501-1.6517	—	1.664-1.667	1.660-1.665	—
Viscosity, Seconds Saybolt Universal (ASTM D-88) 100°F (37.8°C) 210°F (98.9°C)	*56-63 31-33 30-31	*64-93 33-41 31-32	*92-92 49-56 34-35	185-240 *73-80 36-37	1800-2500 260-340 *44-48	3700-4500 *72-78	600-850 (160°F, 71°C) *86-100	— 300-400	90-150 (266°F, 130°C)	— —	— —

*Monsanto Company specifications
**NONE indicates no flash or fire up to boiling point

0614525

TOWOLDMON0006069

Pour Point (°C)	Boiling Point (at 760 mm. Hg) (°C)	Vapor Pressure (mm Hg) at 150°C	at 200°C	at 300°C	Viscosity (centistokes) at 0°C	at 25°C	at 98.9°C	Surface Tension at 20°C (dynes/cm.)	Thermal Expansion Coefficient (at 10° to 40°C) (cc/cc/°C)	* Specification Flash-Point (C.O.C.) (°F)	Fire Point (C.O.C.) (°F)	Assay (Ester Content) (%)	Sulfur (Copper-strip test)	Solubility in water (at 25°C) (%)
-40	360 D	1	9	200	55 0	15 6	2 4	35	0 00078	360	395	99 min	—	0 001 -30°C↑
	270 to 278 (8 mm. Hg)	0 09	1 1	—	—	—	—	36 4 (25°C a 1°)		405	445	* 99 0 min	—	< 0 01
60 (supercools readily)	298	8	50		31 0	9 6	1 8	33 3 (20 5°C)		305	335	99 min	Negative	0 1 (32°C
-46	250 to 257 (8 mm. Hg)	0 015	0 35		647 0	91 0	5 6	29	0 00074	450	520	—	—	< 0 005
-46	228 to 237 (4 mm. Hg)	< 0 05	1 0		327 0	55 0	4 3	—	0 00073	430	480	99 min to 101	Negative	< 0 01
-35 (supercools)	287	13	78		94	11 4	1 6	32	0 00097 (0° to 30°C)	300	315	99 0 min	Negative	0 4 (32°C
-35	232 to 237 (4 mm. Hg)	0 01	0 25			338	34	31	0 00071	435				
-47	384	0 06	1 7		348 0	54 0	4 3	33 (25°C)	0 00074	423	480	99 to 101	Negative	< 0 005
	404	0 15	1 7	55						435				< 0 01
-31	285 (33 mm. Hg)				1500	160	8			450				
-45	370	0 16	2	90		61 5		39 5 (25°C)	0 00080	390				0 0003 (30°C
-51		0 14	1 8		250 0	43 0	3 9			390			Negative	< 0 005
-45		18 6	20 4			17 0	—	33 6 (24°C)		335	335		—	Practically insoluble
-61		15 0	53 1			29 6 (37 8°C)	4 5	31 0 (24°C)	0 00051	375	395			Practically insoluble
-36						75	4 5			495				Practically insoluble
-73	29		0 33	34	900	97	5 7	34 3 (25°C)	0 00059	420	515			
-64			0 79	80	above 1 000	860	11 7	34 9 (25°C	0 00073	440	531			
-49						34 5 (37 8°C)	5 0			412				
-51					400 D	60 0	4 6	—	0 00078	395				
-60					450 D	61 0	4 3		0 00074	370				
-43					250 D	50 0	4 0		0 00074	385				
							—							
							—							
							—							
							—							
							—							
65	240 (4 mm. Hg)	0 02	0 58			14 5 (37 8°C)	3 6	30	0 00077					< 0 01
0		0 04	0 80			9 5 (37 8°C)	2 8	29	0 00076	401	480		Negative	< 0 01
65	214 (5 mm. Hg)	< 0 15	2 5			8 2 (37 8°C)	2 4	29	0 00078	377	450			< 0 01
	490	—	0 3	29	1256 0	89 0	4 0	44 5	0 00057	475	595			< 0 002 gm /100 ml
	370	0 15	1 9			31 0 (55°C)	2 9			437				0 003 (65°C
37	390	0 08	1	760 (90°C)	700 D	33 0	2 8	42	0 00057	450	none at 625			< 0 005
34	375	0 065	1 3		610	34 6	2 5	38 7 (23°C		435	460			0 003
70	218 228	< 0 10	1 8			12 0 (50°C)		30	0 00081	435	485			0 11
80	(20) 145	7 5	> 500			3 8 (50°C)		29	0 00095	380	400			0 1
	320	0 01	7	480	616 0	56 0	2 9			386			Negative	0 0015 (30°C
-40	345	0 1	1 8	180	279 0	46 0	3 6			390			Negative	0 0013 (30°C
-26	310	0 5	8	600	1676 0	82 0	2 8	43 6 (25°C)		380			Negative	0 09 (30°C
	350					—	—	—	—					0 00043 (30°C
340		0 8 (160°C)				—	—	—	—	371				Slight
	340	0 45	5 5		10 000	350 0	6 0	44 5 (25°C)		345				0 13 (23°C
	360 (approx)	0 25	3 2							470				1 (24°C
							—	—					—	Practically insoluble
							—	—					—	Nil
-11						10 500 to 13 500	—	—		555				Practically insoluble
+16						8 000 to 9 500	—	—		535				Practically insoluble
6						2 900 to 3 500	—	—	0 00071	530	570			Practically insoluble
+71						9 000 to 9 800	—	—	—	540	—			Practically insoluble
28						291	—	—	—					Practically insoluble
1						536	—	—	—	475	535			Practically insoluble
10						3,878	—	—	—	485	535			Practically insoluble
18						6 422	—	—	—	525	580	—	—	Practically insoluble
31						196	—	—	—	485	525			Practically insoluble
26	395 to 396	2	15	230	70 0	29 0 (37 8°C)	3 8	40 1 (25°C)	—	345	385			
	360		11 (220°C)			—	—	—	—	375	525			Hygroscopic
5	Not distillable				—	—	* 40 to 60	—		No self-supporting combustion		—	—	Nil
	360		11 (220°C)		—	17 5				375	525			Hygroscopic

FLAME-RETARDANT PLASTICIZERS

If you want products that resist burning, build your formulations with one or a combination of flame-retardant plasticizers. Monsanto's liquid and solid flame-retardant plasticizers offer a wide range of compatibilities. Other beneficial properties include permanence, chemical resistance, extraction resistance, flexibility and weatherability.

Santicizer® 140
Santicizer 141
Tricresyl Phosphate
Triphenyl Phosphate
11 Aroclor® Plasticizers
6 Montar® Compounds
Phosgard® C-22-R

FDA REGULATED PLASTICIZERS

Monsanto offers more FDA regulated plasticizers than any supplier for use in compositions related to food packaging and handling, and for articles that come into close contact with the human body. The following list of plasticizers offer you high specification standards of purity, low odor, minimum taste, flexibility, clearness and water resistance for applications such as: food-wrapping paper coatings, packaging films, label adhesives and inks, beverage and blood tubing:

Dioctyl Phthalate
(high-water-content foods only)
Diisooctyl Phthalate
(high-water-content foods only)
Diethyl Phthalate
Dioctyl (2-ethylhexyl) Adipate
Santicizer® 141
Santicizer E-15
Santicizer B-16
Santicizer 160

SOLID PLASTICIZERS

Choose from a variety of plasticizers for use in adhesives, coatings and lacquers, foams, rigid compositions and films. Solid plasticizers decrease your hot processing time at reduced cost. During solvent processing, they require fewer surface-building coats and at less cost. For use such as delayed-tack and heat-seal adhesives and coatings for non-blocking films, easier processing of rigid plastics products, toughness of rigid foams, for even flow and uniform filling of resinous impregnants, choose from the following:

	Melting Point (°C)	Softening Range (°C)
Aroclor® 5442		46 52
Triphenyl Phosphate	48.5	
Montar® 1	—	54-160
Santicizer® 3	58	
Aroclor 4465	—	60-66
Santolite® MHP	62	
Dicyclohexyl Phthalate	63	—
Diphenyl Phthalate	69	—
Montar 2		70-170
Santicizer 1-H	82.5	
Montar 3	—	86-168
Montar 4	—	92-206
Aroclor 5460	—	98-105
Santicizer 9	105	—
Montar 9	—	130-175
Aroclor 1268	—	150-170
Montar 5	—	155-195

0614526

TOWOLDMON0006070