POUNDS	GALLONS	MATERIAL NO.
Parallel Rx 466		

CUSTOMER Sherwin Williams Co.

TO MATCH 466

REASON FOR REVISION To show Rx 184 parallel to Rx 466.

VISCOSITY _____ AT _____ HRS. AFTER GRIND

VISCOSITY _____ AT _____ HRS. AFTER GRIND

% SOLIDS (RUN) _____

WT./GAL. 17.85

BAUME _____

STD. OF FINENESS _____

NORMAL OUTPUT _____

EST. MFG. LOSS _____

DEPARTMENT _____

PACKAGE _____

PARALLEL NO.'S _____

ROYALTY: YES ☐; NO ☐; X ☐; W ☐

LABEL ANALYSIS CHECKED-DATE _____

LABEL: NO. RED ☐; RED ☐

NEW STD. SAMPLE REQUIRED _____

DATE REC'D _____

MILL _____ BLEED? _____

LBS. OR GALS. PER HOUR _____

APPROVED

FORMULATOR D. Thompson

SUPT. 8-7-6

FORMULA RECORD 76C

CONTROL LAB Cleveland T.S. DATE 5/13/49 REV. NO. 184

NAME Ext. Paster Paint #84 CARD NO. 4

POUNDS	GALLONS	MATERIAL NO.
320	15.2	2203
160	6.7	2201
130	4	1403
260	9.6	2132
450	9.5	414 W *
100	1.8	18 9
6	.1	1128
4	.5	2270
169	21	(48) **
4	1/2	(12)W
33	4 1/2	(4230)
11	1 1/2	(543)
114	17 1/2	(348)
54	8	(141)
13	2	(5026)
* SEE	MFG. INSTRUCTIONS	
** SEE	MFG. INSTRUCTIONS	

CUSTOMER Sherwin Williams Co.

TO MATCH Standard

REASON FOR REVISION Using 18 dry to increase lead content.

VISCOSITY See Mfg. Inst. AT ____ HRS. AFTER GRIND

VISCOSITY ____ AT ____ HRS. AFTER GRIND

% SOLIDS (RUN) ____ ROYALTY: YES ☐; NO ☐; X ☐; ▽ ☐

WT./GAL. T 17.85 LABEL ANALYSIS CHECKED-DATE 5-18-49

BAUME ____ LABEL: NO. RED ☐; RED ☐

STD. OF FINENESS 2H NEW STD. SAMPLE REQUIRED ____

NORMAL OUTPUT 1 DATE REC'D ____

EST. [illegible] 2 Roller BLEED? ____

DEPARTMENT ____ LBS. OR GALS. PER HOUR ____

SEE CARD NO. 3

CLASSIFIED ASSIGN.

PARALLEL NO.'S ____ APPROVED ____

FORMULATOR [signature]

SUPT. [signature]

0007-SWP-061051

MANUFACTURING INSTRUCTIONS:

Application: Surface Interiors. No. Coats one
Undercoater Used wood, metal No. Coats
Primer for new work
Method 1 Brush
Reduction: Amount Reducer Used
Method 2
Reduction: Amount Reducer Used

Drying Time: Touch 1-2 hrs. Recoat 18-24 hrs. Stencil
Hard Sand Handle
Tack Free Rub Wrap
Baking Time and Temp.
Gloss Oil Film Rough
Special Tests

DATE	SLIP No.	AMOUNT

FACTORY	FORMULA	SPEC. CARD
Exec. Cost Dept.	10-31-41	
Cleveland A	"	
Kensington C		
Allied Research	"	
Kens. Tech. Serv.		
Kens. Lacquer		
Newark N	"	
Oakland O	"	
M. Senour M	"	
Detroit D	"	
Los Angeles P	"	
Dallas T	"	
Dayton B	"	
Gibbsboro F	"	
Pittsburgh H		
Cuba V	"	
Montreal	"	
Buenos Aires Z	"	

0007-SWP-061118

FORMULA RECORD

A135 WHITE

Exp. No. 1 Date 7/20/48 Class 17 Rex. No. 184

Name Exterior Paste Paint #84 Card No. Replaces No.

POUNDS	GALLONS	MATERIAL No.
320		2203
160		2201
130		1403
260		2132
525		414
4		2270
6		1128 #Pw 9-9-48
4	1/2	(12W)
168	21	(48)
33 3/4	4 1/2	(4230)
10 1/2	1 1/2	(543)
114	17 1/2	(348)
53 1/2	8	(141)
13	2	(5026)

Customer Sherwin Williams Co.

To Match Standard

Reason for Revision New Product

Viscosity at hrs. after grind

Viscosity hrs. after grind

% Solids (Run) 17.63

Wt./Gal.

Baume

Std. of Fineness 2H

Normal Output 100

Est. Mfg. Loss 2

Department

Package

Parallel No.'s

Royalty: Yes ☐; No ☒; X ☐; W

Label Analysis Checked-Date

Label: No Red ☐; Red ☒ Yes

New Std. Sample Required

Date Rec'd

Mill Roller Bleed?

Lbs. or Gals. per hour

Approved: E. Edaner

Formulator

Supt. 876

0007-SWP-061053

MANUFACTURING INSTRUCTIONS:

Application: Surface int.,ext. wood,metal No. Coats Solid 2

Undercoater Used No. Coats

Primer for new work

Method 1 Brush

Reduction: Amount Reducer Used

Method 2

Reduction: Amount Reducer Used

Drying Time: Touch 1-12 hrs. Recoat 12-24 hrs. Stencil

Hard Sand Handle

Tack Free Rub Wrap

Baking Time and Temp.

Gloss Oil Film Tough

Special Tests

DATE	SLIP No.	AMOUNT

FACTORY	FORMULA	SPEC. CARD
Exec. Cost Dept.	11-7-41	
Cleveland A	"	
Kensington C		
Allied Research	"	
Kens. Tech. Serv.		
Kens. Lacquer		
Newark N	"	
Oakland O	"	
M. Senour M	"	
Detroit D	"	
Los Angeles P	"	
Dallas T	"	
Dayton B	"	
Gibbsboro F	"	5
Pittsburgh H	"	"
Cuba V	"	
Montreal	"	
Buenos Aires Z	"	"

0007-SWP-061120

MANUFACTURING INSTRUCTIONS: When reversing
See Card # 7 Transfer Ltd

Reduction: Amount _____ Reducer Used _____
Application: Surface Wood or metal Method Brush
No. Coats Solid - 2 Undercoater Used _____
Drying Time: Touch 8-12 Hrs Handle _____ Recoat 18-24 Hrs.
Rub _____ Sand _____ Wrap _____ Stencil _____
Baking Time and Temp _____
Gloss Oil Film Tough
Special Tests _____

PRODUCTION		
Date	Slip No.	Amount

FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE	FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE
CLEVELAND	7-22-35	CA 3-21-41	11-30-43	ALLIED RESEARCH	7-22-35	CA 3-21-41	11-30-43
NEWARK	"	"	"	GIBBSBORO	"	"	"
KENSINGTON	"	"	"	DAYTON	3-8-38	"	"
OAKLAND	"	"	"	DETROIT			
DALLAS	"	"	"	LONDON			
LOS ANGELES	"	"	"	AUSTRALIA			
MONTREAL	"	"	"	Argentina	7-22-41		
COST DEPT.	"	"	"				

0007-SWP-061055