

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO A. Stasenko. AT Burl. Compound DATE September 16, 1969

FROM E. L. Kanyok AT Burlington COPY TO H. B. Carr

SUBJECT Firestone 250 Resin W. Champion

U. Carbide 250 Resin H. H. Duhamel

P. Gawason

P. R. Scarito

D. H. Weintraub

File ✓

The results of Firestone 250 resin received on 9/13/69
and Union Carbide 250 resin received on 9/12/69 are as follows:

<u>Properties</u>	<u>Firestone</u>	<u>U. Carbide</u>	<u>Burl. 250-12 Spec.</u>
Relative Viscosity	2.48	2.52	2.40 - 2.48
Gels	8	24	12 Maximum
Dry Blend	6.7	5.5	6.0 - 8.0
Screen +40	-	-	-
+60	Tr	Tr	0 - 3
+80	5	5	-
+100	42	55	50 - 80
+140	81	90	-
+200	95	98	-
Thru	5	2	0 - 5

E. L. Kanyok
E. L. Kanyok

ELK/rjl