

GRAPHICAL SYMBOLS FOR DRAWINGS

94. Thermostat
(Self Contained)95. Thermostat
(Remote Bulb)

96. Pressurestat



97. Hand Expansion Valve

98. Automatic
Expansion Valve99. Thermostatic
Expansion Valve

100. Evaporator Press. Regulating Valve, Throttling Type



101. Evaporator Press. Regulating Valve, Thermostatic Throttling Type



102. Evaporator Press. Regulating Valve, Snap-Action Valve



103. Compressor Suction Pressure Limiting Valve, Throttling Type



104. Hand Shut Off Valve



105. Thermal Bulb



106. Scale Trap



107. Dryer



108. Strainer



109. High Side Float




110. Low Side Float




111. Gage




112. Finned Type Cooling Unit, Natural Convection



113. Pipe Coil



114. Forced Convection Cooling Unit




115. Immersion Cooling Unit



116. Ice Making Unit




117. Heat Interchanger



118. Condensing Unit, Air Cooled



119. Condensing Unit, Water Cooled



120. Compressor




121. Cooling Tower




122. Evaporative Condenser



123. Solenoid Valve



124. Pressurestat With High Pressure Cut-Out



Refrigerating

SPECIFIC HEAT

TABLE 1. SPECIFIC HEAT OF SOLIDS^a

MATERIALS	TEMPERATURE F	SPECIFIC HEAT	AUTHORITY
Alloys			
Brass, Red	32	0.0899	S
Brass, Yellow	32	0.0883	S
Bronze (80Cu, 20Sn)	57-208	0.0862	S
Monel Metal	68-2370	0.127	S
Aluminum	80-212	0.212	S
Asbestos	68-208	0.195	S
Brickwork		0.195	H
Carbon (Graphite)	104-1637	0.314	I
Coal		0.278	H
Coke		0.201	H
Concrete		0.270	H
Copper	64-212	0.0928	S
Fire Clay Brick	77-1832	0.258	I
Glass			
Crown	50-122	0.161	S
Flint	50-122	0.117	S
Gold	64	0.0312	S
Gypsum		0.259	H
Ice	32	0.457	S
Ice	-40	0.434	S
Iron, Pure	32	0.1043	S
Iron, Pure	32-600	0.127	M
Iron, Cast	68-212	0.1189	H
Iron, Wrought	59-212	0.1152	H
Lead	32	0.0297	S
Nickel	32	0.1032	S
Masonry		0.2159	H
Plaster		0.2	H
Platinum	58-212	0.0319	S
Rocks			
Gneiss	63-210	0.196	S
Granite	54-212	0.192	S
Limestone	59-212	0.216	S
Marble	32-212	0.21	S
Sandstone		0.22	S
Silver	32	0.0536	S
Steel		0.1175	H
Sulphur	240-320	0.220	S
Silica Brick	77-1832	0.263	S
Tin	77	0.0548	S
Woods (Average)	68	0.327	S
Zinc	32	0.0913	S

TABLE 2. SPECIFIC HEAT OF LIQUIDS

LIQUID	TEMPERATURE F	SPECIFIC HEAT	AUTHORITY
Alcohol, Ethyl	32	0.548	S
Alcohol, Methyl	59-68	0.601	S
Glycerine	59-122	0.576	S
Lead (Molten)	360	0.041	H
Mercury	68	0.03325	S
Petroleum	70-136	0.511	S
Sea Water			
Sp. Gr. 1.0043	64	0.980	S
Sp. Gr. 1.0463	64	0.903	S
Water	59	1.000	S

TABLE 3. SPECIFIC HEAT OF GASES AND VAPORS

SUBSTANCE	TEMPERATURE F	SPECIFIC HEAT AT CONSTANT PRESSURE	RATIO OF SPECIFIC HEAT C_p/C_v	SPECIFIC HEAT AT CONSTANT VOLUME (COMPUTED)	AUTHORITY
Air	32-392	0.2375	1.405	0.169	S
Ammonia	80-392	0.5356	1.277	0.419	S
Carbon Dioxide	52-417	0.2169	1.3003	0.1668	S
Carbon Monoxide	79-388	0.2426	1.395	0.1736	S
Coal Gas	68-1900	0.3145			S
Flue Gas		0.24 (Approx.)			H
Hydrogen	70-212	3.41	1.419	2.402	S
Nitrogen	32-392	0.2438	1.41	0.1729	S
Oxygen	55-404	0.2175	1.3977	0.155	S
Water Vapor	212	0.421	1.305	0.322	S
Water Vapor	356	0.51			S

^aSee also The Specific Heat of Thermal Insulating Materials, by Gordon B. Wilkes and Carl O. Wood (A.S.H.V.E. TRANSACTIONS, Vol. 48, 1942, p. 493).

NOTES: When one temperature is given the true specific heat is given, otherwise the value is the mean specific heat between the given limits.

AUTHORITIES: S—Smithsonian Physical Tables, 1933; I—International Critical Tables; H—Heating, Ventilation and Air Conditioning, by L. A. Harding and A. C. Willard; M—Engineers' Handbook, by Lionel S. Marks.