

THE SARANAC LABORATORY

OF THE EDWARD L. TRUBBEN FOUNDATION

SARANAC LAKE, N. Y.

ARTHUR J. VORWALD, M.D.
DIRECTOR

August 5, 1952

THE INDUSTRIAL COMMISSION

(Sample of Talcoold non-sil. particle compound, manufactured by Talco Products, Inc., 3800 Rogers St., Milwaukee 14, Wisconsin. Submitted under Don Bailey's letter dated July 21, 1952).

X-ray Diffraction and Petrographic Analysis

Portion of sample taken for X-ray diffraction was first treated with hydrochloric acid for purposes of concentration. All figures reported below are in terms of the material as received.

Quartz	1.45 %
Mica	trace
Loss on treatment (hydrochloric acid)	20.00 %

Donald Bailey
Donald Bailey
Petrographer

DO:170

3