MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Br-284-2 LOT F-1578

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	11	2010	26	
STUMP				

TOTAL NET WT. 2010 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	5/17/82	305

```
C
C
  133.+
  137.+
  135.+
  214.+
  136.+
  175.+
  134.+
  137.+
  131.+
  137.+
  191.+
 2010.T
C
```

DUP050097367

FINISHING Note: Co-PULY WITH N-65.A & MFS

CG 20 CODE BT-284D PKG. E1578

EST. WGT. 2254 LBS.

9 Bld

11

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	TYPED BY	

MAKING NOTES

REMARKS

NAME: MONASTRAL® BLUE B NON-BLEEDING

INSTRUCTIONS — -PRESSING- — RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT						STARTED					
DATE						CAKES USED					
TIME						WATER ON					
RELEASED BY						HRS. WASHED					
PRESS						OHMS					
NO. OF CAKES						HRS. WASHED					
PRESS		AGITATION				OHMS					
WASH TO		OHMS				HRS. WASHED					
TEST AFTER		HOURS				OHMS					
LOAD PANLOAD						CAKE CONDITION					
						NO. CARS LOADED	1+1+1				
						EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY RELEASED BY RF

-DRYING-

HOURS	L.V.	H.V.
TEMP.	°F	°F
DRY 20 HRS. AT 220°F		

LUMP: - OK - WET - SALTS - CONTAMINATE ✓

P/L from drums no Record of any Losses

ADDITIONAL DRYING HOURS REQUIRED

11 drs

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 1935

SAMPLED BY RELEASED BY Jel

-GRINDING-

MILL 70R8L3P 3/32" SCREEN 1785 RPM
MAX. TEMP. 150 °F

CO-PULY WITH 150 # N-65-A

SAMPLE AFTER / [redacted] MIXING
SAMPLES 1 ENV + 2 PINTS

SCREEN	RPM
MAX. TEMP.	°F

EXPLAIN LOSSES

DATE MIXED 5/30/81

DUP050097368

CG 20 CODE BT-284-D PKG.

→ MAY 20 1980

E1578

EST. WGT. _____ LBS.

NOTE: MAKING — FILL IN EST WGT FROM BATCH CARD

PROCESSING INSTRUCTIONS: BATCH ON

PROCESSES	APPROVED
BT-284-D (P	AJG 05 10 7,
	DCG 07 12 7
TYPED BY	
emw070279	

MAKING NOTES

REMARKS

NAME: MONASTRAL® BLUE B

NON-BLEEDING

INSTRUCTIONS					-PRESSING- RECORD					
AT					PRESSLOAD	1ST	2ND	3RD	4TH	5
DATE					STARTED					
TIME					CAKES USED					
RELEASED BY					HRS TO FILL					
PRESS	9 + 10		17 + 18							
NO. OF CAKES	2 x 119 + 43		3 x 84 + 28							
PRESS with AGITATION										
WASH TO _____ OHMS										
TEST AFTER _____ HOURS										
LOAD on 8 cars										
					CAKE CONDITION					
					NO. CARS LOADED					
					EXPLAIN LOSSES					
SAMPLES										
DELIVER TO					SAMPLED BY		RELEASED BY			


-DRYING-

Dry 18 hrs at 220°F	LUMP: - OK - WET - SALTS - CONTAMINA
	ADDITIONAL DRYING HOURS REQUIRED
	NO DRUMS
SAMPLES	NO. CARS PULLED LUMP WGT.
DELIVER TO	SAMPLED BY RELEASED BY

-GRINDING-

MILL 7 or 8 LSP 3/32" RP SCREEN 1785 RPM	SCREEN RPM
MAX. TEMP. 200 °F	MAX. TEMP. °F
	EXPLAIN LOSSES
SAMPLE WITHOUT MIXING	DATE MIXED
SAMPLES 1 Env & 1 Pt Can	
DELIVER TO C T L	SAMPLED BY RELEASED BY

DUP050097369



B4.284-D

1578
51
158

0.00 *

11.95 +
2.06 +
0.12 -
2.16 +
0.12 -
2.00 +
0.12 -
1.66 +
0.12 -
19.35 *

4

1.95 +
0.14 -
1.91 +
0.14 -
1.90 +
0.14 -
1.96 +
0.14 -
1.96 +
0.14 -
1.86 +
0.14 -
1.89 +
0.14 -
11.95 *

7

DUP050097370