VISCOSITY WORK SHEET

Item _____ P.T.No. – Date 2-3-55

Worker NH Jackie Harrison Polymer Lucite Solvent EDC

For Martin Charge 1290 Temperature 25°C

Viscometer No. 1 Efflux Time 224.3 Weight: Gross 3.1147

Viscometer No. I Efflux Time 221.2 Tare 2.9897

Viscometer No. 2 Efflux Time 219.8 Net .1250

III 248.3

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Inh. visc. Visc. or M.W.	
5769	e	1	292.8, 294.9, 292.0, 293.7 293.7	1.240	101,000 very fine gel. .430
"	M50	I	276.1, 278.6, 273.5, 275.2 275.8	1.248	104,000 very fine gel. .439
5773	J-5	2	272.3, 273.9, 272.1, 272.8	1.242	102,000 .434
	E	III	304.0, 304.1, 304.1	1.221	90,500 .400
			Solvent filtered thru screens		

PC-1

2.3
3.8
3.1
2.8
4)11.0
2.7

6)
8.6
5.3
5.2
4)23.2
5.8