MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KL-787 LOT E1505

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	66	3300		
	STUMP	3289		

TOTAL NET WT. 3300 PKG. N–CODE 1002

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	5/12/81	

2
44

CG 03 CODE KY-787-D PKG. ____

→

EST. WGT. ~~XXXXX 932~~ LBS.

012
HP

E1565

Total Wgt. ~~3332#~~ ~~3490#~~ 3464

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (R)	FWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NF 2/12/77	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
AT	244				
DATE	5-22-81				
TIME	2:25 P				
RELEASED BY	C. [illegible]				
PRESS	22	23	24	24	
NO. OF CAKES	46	46	46	52	

PRESS with AGITATION

WASH TO 2000 OHMS with 35-75°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

SAMPLES 1-8 oz JAR

DELIVER TO ctl for color

RECORD					
PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	1:37 P				
CAKES USED	5-2				
WATER ON	9 PM				
HRS. WASHED	5				
OHMS	4000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	5				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

No. Drums 13

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 3289

SAMPLED BY RELEASED BY

-GRINDING-

MILL [illegible] 3/32" [illegible] SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 [illegible]

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050096609

1565
41
17

0.00 *

2.63 +
0.12 -
2.74 +
0.12 -
2.81 +
0.12 -
2.89 +
0.12 -
2.77 +
0.12 -
2.62 +
0.12 -
2.75 +
0.12 -
2.70 +
0.12 -
2.80 +
0.12 -
2.75 +
0.12 -
2.74 +
0.12 -
2.52 +
0.12 -
1.73 +
0.12 -
32.89 *

DUP050096610