

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
------------	---------	-----------	----------	----

© 2006 The Authors
 Journal compilation © 2006 Blackwell Publishing Ltd

STUMP

PROD. SPVR.	DATE	WHSE. OPER.
-------------	------	-------------

3/2/50

95
1222

CG 03 CODE KY-787-D PKG. _____
MAF-5 34725
EST. WGT. 1090 990 LBS.

OK
HP

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-787-D (R)	FWK 9/22/76
	Alternate	DCG 9/27/76
	TYPED BY	
	NE 2/12/77	
MAKING NOTES		
REMARKS		

Total Wgt. 3490# 3390

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	262					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	3-6-80					STARTED	9A				
TIME	8:30A					CAKES USED	40				
RELEASED BY	WJL	GW				WATER ON	10 PM				
PRESS	22	23	24	24	95	HRS. WASHED	10 1/2				
NO. OF CAKES	46	46	46	52	40	OHMS	2000				
PRESS with						HRS. WASHED					
WASH TO	2000					OHMS					
TEST AFTER	2					HRS. WASHED					
LOAD	on 6 cars					OHMS					
						CAKE CONDITION	6				
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

WJL

SAMPLES 1-8 oz JAR
DELIVER TO ctl for color

SAMPLED BY 472 RELEASED BY JBL

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

No. Drums 15
NO. CARS PULLED
LUMP WGT. 3500
SAMPLED BY
RELEASED BY D.L.L.

-GRINDING-

MILL 939 HSP 3/32" RD SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 Pt. can
DELIVER TO C.T.L.

DATE MIXED
SAMPLED BY
RELEASED BY

DUP050093699

N 26287.01

N 26287.01

2 Cars used

10 Drive

200 T
2.41 -
2.50 -
2.77 -
2.57 -
2.58 -
2.52 -
2.55 -
2.50 -
2.55 -
2.38 -
23.74 T

23.74 +
2.68 +
0.14 -
2.65 +
0.14 -
2.64 +
0.14 -
2.39 +
0.14 -
1.58 +
0.12 -
35.00 *