O'BRIEN'S

TTO

THERMOLYZED TUNG OIL

PAINT

WHITE



made with patented *Pre-Shrunk* Thermolyzed Tung Oil

MADE IN U.S.A. • MANUFACTURED BY THE O'BRIEN CORPORATION • SOUTH BEND, INDIANA

THERMOLYZED OIL PAINT

Made with patented (U. S. Pat. No. 2,113,358) Thermolyzed Pre-Shrunk Tung Oil—T.T.O. Paint may be used on any exterior surface—wood, metal, brick, concrete, etc. T.T.O. Paint works easily under the brush, covers exceptionally well and provides a high lustre, porcelain-like finish that looks like enamel, washes like glass and wears like iron. Available in seven colors and White.

T. T. O. WHITE PRIMER

A specially designed primer for use on all exterior surfaces under O'Brien's T.T.O. Paint and other house paints. Made with Pre-Shrunk Oils, T.T.O. Primer controls the penetration of the oils in the paints put over it and thus assures a well balanced, long-wearing paint film. Dries to a dull finish permitting fast and sure application of the finish coat. Comes in White only but may be tinted with O'Brien Oil Colors.

T. T. O. ALUMINUM PAINT
(CHROME DELUXE)

A top-quality Aluminum Paint for use on almost any interior or exterior surfaces—on tanks, metal roofs, wire fence, machinery, pipes, walls, signs, railings, fence posts, etc. T.T.O. Aluminum assures maximum durability, fine coverage and hiding plus a finish highly resistant to moisture, heat and industrial fumes.

DIRECTIONS FOR USE

Stir the paint occasionally during use.

Allow sufficient drying time between coats.

Apply only over clean surfaces—free of grease, wax, oil and loose dirt or dust.

THE O'BRIEN CORPORATION
South Bend, Indiana Since 1875

REGISTERED
REGN. No. 2573
DATE 6-18-52

49 TOC 001137

DIRECTIONS FOR USE

FOR NEW UNPAINTED SURFACES

1st Coat—O'Brien's T.T.O. White Primer thinned with two or three pints of raw linseed oil.

2nd Coat—Mixture of one-half T.T.O. White Primer and one-half T.T.O. Paint of the finish color.*

3rd Coat—O'Brien's T.T.O. Paint.

* This coat may be eliminated where time and cost necessitate a two-coat job.

FOR OLD PAINTED SURFACES

1st Coat—O'Brien's T.T.O. White Primer. Tint to the approximate color of the finish coat**.

2nd Coat—O'Brien's T.T.O. Paint.

** For light colors tint T. T. O. Primer with O'Brien's Oil Colors. For dark colors mix one-half T.T.O. Primer and one-half T.T.O. Paint of the finish color.

GENERAL RECOMMENDATIONS

WEATHER—Outside painting should never be done when the weather is damp or the temperature below 60° F.

SURFACES—Surfaces to be painted should be perfectly dry and free of grease, oil, dust and loose dirt.

SPRAYING—T.T.O. Paints may be sprayed by an experienced operator. Thin as necessary with turpentine.

DRYING—Allow at least 48 hours good drying weather between coats. When temperature is low, add two fluid ounces of O'Brien's No. 1188 Drier to each gallon.

Stir Paint Well Before and During Use
When Necessary — Thin with Turpentine

Inflammable—Keep Away From Fire