

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY 907 LOT F1571

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>1.710</u>	<u>1</u>	<u>T-</u>	<u>249</u>	
<u>1.685</u>	<u>1</u>	<u>T-</u>	<u>159</u>	

STUMP

1.249 3398

TOTAL NET WT. 3.395 PKG. N-CODE _____

PROD. SPVR. _____ DATE _____ WHSE. OPER. _____

5/30/85

PRODUCT NAME = KROLOR YELLOW - MEDIUM

NON-BLEEDING

CG 03 CODE KY-907-D PKG

PROCESSES

APPROVED BY

KY907D(D)

FWP 05/13/81

ALTERNATE

TYPED BY WRT/JMW

MAKING NOTES

TOTAL EST'D WGT=3451 LBS (CRT ENTRY)

INSTRUCTIONS

= PRESSING =

RECORD

VAT - 240						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE 5/23/81						STARTED	4:00 PM				
TIME 11:30 AM						CAKES USED	32				
RELEASED BY						WATER ON	3 PM				
PRESS 2	22	23	24	95		HRS. WASHED	3				
NO.OF CAKES 46	46	46	52			OHMS	13000				
PRESS WITH						HRS. WASHED					
WASH TO 2000 OHMS - 135-145 F WATER						OHMS					
TEST AFTER 3 HOURS						HRS. WASHED					
LOAD ON 6 CARS						OHMS					
						CAKE CONDITION					
						NO CARS LOADED	6				
						EXPLAIN LOSSES					

SAMPLES 8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY
RELEASED BY RH

= DRYING =

DRY 24 HOURS AT 180 F
NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

LUMP: - DK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY S36

NO DRUMS
LUMP WGT 3398

= GRINDING =

MILL 939 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1571
41
17

0.00 *

3.42 +
0.12 -
3.46 +
0.12 -
3.55 +
0.12 -
3.33 +
0.12 -
3.41 +
0.12 -
3.58 +
0.12 -
3.51 +
0.12 -
3.35 +
0.12 -
3.45 +
0.12 -
2.89 +
0.12 -
1.35 +
0.12 -
33.98 *