Goods Endurance Shade White Base — Formula No. Y 1804 G

Consistency Liquid — Date 2/7/033 — Lab. No.

For Use on — Cost Classification

Code Number	Gal.	Drum		ANALYSIS		Manufacturing Specifications
O-1			32 GAL	Pigment	62%	Grind C
O-64			3	Vehicle	38	Kind of Mill Stone or pebble
O-131			35		100%	Rate per hour
D-15			5	Pigment -		Strainer
S-43			2	White Lead Carbonate	15%	Weight per gallon 15½#
6779			3	" " Sulphate	20	Is Agitator Package Required
				Zinc Oxide	35	Remarks
W-76			150#	Lithopone	15	Steel Pails - 5's
W-6			550#	Silica & Silicates	15%	Round cans 1's - ½'s
W-69			150#		100%	"Endurance Paint Prepared"
W-16			75#	Vehicle -		Spec. Label
W-11			75#	Linseed Oil	92%	
				Liquid Drier	8%	
* V-715			1 GAL		100%	
* Add only is needed for Body						
Yield						

N12049

GLD059012

FORMULA SPECIFICATION AND TEST RECORD

Name of Material		Formula	
Vis. (F. B.)	Bake min. at °F	Type Oven	
Vis. Red. with	Air dry to:	Pitting	Feathering
Be (F. B.)	Dust free	Floating	Silking
Be as used	Recoat	Crinkling	Odor
Mobilometer Reading	Handle	Body on work	Clarity
Method of use	Sand	Orange Peel	Blushing
Wt. per gal.	Pack	Porosity	Lacq pick up
G. H. Tube Body	Rub	Will material draw	
Hiding (Cryptometer)	Toughness	Dielectric Strength	
Acid No.	Test Adhesion	Blooming	Patching
Sheen	Color of Liq.	Mist Coat	Pig. Separation
Resistence to: Acid	Cleanliness	Bleeding	Settling
Alkali	Flow Test	Skinning	Livering
Gasoline	Neutrality	Printing	Color Match
Alcohol	Naphtha Dil'n	Match For	
Heat	Covering	Customers	
Water	N. V.	Remarks:	
Lub. Oil	Boiling Range		
Salt Spray	Flash		
Cold	Bend Test		
U. V. Light	Rub with	Reduction for Use	
Humidity	Sand with		
Hardness	Polish with		

GLD059013