MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE YT 714 LOT 38297


NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	21	2143	50	
	STUMP	LUMP WT	226	

TOTAL NET WT. 2143 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

2/9/1

N 31795



N 31795.01

DUP050292084

FIRE PORTION: SPLIT OFF 115# TO LOT

[redacted].00220

CG 50 CODE YT-714-D PKG. ____

→ DEC 29 80 38297 JAN 15 81

EST. WGT. 2224 LBS.

FIRE BATCH 99's

FIRED ON 1/31/81

@ 7:30 PM

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YT-714-D (G)	BBK 12-1-77
	DCG 12-1-77
TYPED BY	
NSA 3-28-78	

MAKING NOTES

REMARKS

NAME: GREEN GOLD

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					RECORD					
VAT	105				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	1-15-81				STARTED	7:30P				
TIME	7:PM				CAKES USED	60 P				
RELEASED BY	S.B.				WATER ON	5:0 P				
PRESS	32	33	35	36	HRS. WASHED	1 HR				
NO. OF CAKES	60	60	60	64	OHMS	5000				
PRESS without AGITATION					HRS. WASHED					
WASH TO 1500 OHMS with 35-75°F water					OHMS					
TEST AFTER 10 HOURS					HRS. WASHED					
LOAD on 7 cars					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	4+4				
					EXPLAIN LOSSES					

SAMPLES 8 oz. —

DELIVER TO Hold for PE

SAMPLED BY RELEASED BY

-DRYING-

DRY 22 Hrs at 200°F

LUMP: — OK — WET — SALTS — CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 13

SAMPLES 8 oz. + 2 gal —

DELIVER TO Hold for PE

NO. CARS PULLED

LUMP WGT. 2266

SAMPLED BY

RELEASED BY

-GRINDING-

MILL 8 HSP 1/8"RP SCREEN 3560 RPM

MAX. TEMP. 150 °F

If grinding after Palaman — change bag on Mill

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 Env & 1 Pt Can + 2 gal


DELIVER TO C T L

DATE MIXED

SAMPLED BY 1200 1/31/81 RELEASED BY

DUP050292085

N 31795.02



N 31795.03

DUP050292086

38297
5100
18

0.00 *
0.00M+

1.72 +
0.12 −
1.76 +
0.12 −
1.76 +
0.12 −
1.84 +
0.12 −
1.84 +
0.12 −
1.81 +
0.12 −
2.20 +
0.12 −
12.09 *
12.09M+

N 31795.04

DUP050292087