

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO A. Stasenko . At Burl. Compound DATE August 27, 1969

FROM E. L. Kanyok At Burlington COPY TO H. B. Carr

SUBJECT Olin-Mathieson 225 Resin H. H. Duhamel

P. Gawason

P. R. Scarito

File ✓

The results of the first shipment of Olin-Mathieson 225 resin, lot no. 8510, received on 8/26/69 are as follows:

| <u>Properties</u>  | <u>8510</u> | <u>Burl. 225 Spec.</u> |
|--------------------|-------------|------------------------|
| Relative Viscosity | 2.32        | 2.26 - 2.33            |
| Gels               | 44 R/R 46   | 13 maximum             |
| Dry Blend          | 6.2         | 6.0 - 8.0              |
| Screen             |             |                        |
| +40                | -           | -                      |
| +60                | 4           | 0 - Tr                 |
| +80                | 12          | -                      |
| +100               | 42          | 40 - 70                |
| +140               | 80          | -                      |
| +200               | 94          | -                      |
| Thru               | 6           | 0 - 5                  |

The gel count is well above our spec. and should be monitored by the Compound plant for quality of the end product.

*E. L. Kanyok*  
E. L. Kanyok

ELK/rjl