

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY 908 LOT E 1155

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>2000</u>	<u>1</u>	<u>T-37</u>		
<u>1740</u>	<u>1</u>	<u>T-66</u>		

STUMP

Lump 3737TOTAL NET WT. 3740 PKG. N-CODE _____PROD. SPVR. _____ DATE 5/27/81 WHSE. OPER. _____

22
244
SUBJECT NAME = RECOLOR YELLOW-LIGHT

03 CODE KY-908-D PKG

LOT MAY -0.81-Σ1155

EST'D WGT 949 LBS

TOTAL EST'D WGT=3549 LBS (CRT ENTRY)

NON-BLEEDING

PROCESSES

KY908D(D)

ALTERNATE

TYPED BY

APPROVED BY

FWP 01/27/81

MAKING NOTES

JOB NAME: 03KY908DPD

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 2 22 23 24
NO. OF CAKES 46 46 46 52
PRESS WITH AGITATION
WASH TO 2000 OHMS - 135-145 F WATER
TEST AFTER 2 HOURS
LOAD ON 6 CARS

PRESSLOAD

STARTED

CAKES USED

WATER ON

HRS. WASHED

OHMS

HRS. WASHED

OHMS

HRS. WASHED

OHMS

CAKE CONDITION

NO CARS LOADED

EXPLAIN LOSSES

1ST 2ND 3RD 4TH 5TH

100

52

2A

2 1/2

2500

6

SAMPLES 8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY

RELEASED BY

= DRYING =

DRY 24 HOURS AT 180 F
NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED

SAMPLED BY

RELEASED BY

NO DRUMS

LUMP WGT 3737

= GRINDING =

MILL 939 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SCREEN

MAX. TEMP.

RPM

F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO ETL

DATE MIXED

SAMPLED BY

RELEASED BY

1155
41
231

0.00 *
3.25 +
0.12 -
3.10 +
0.12 -
3.05 +
0.12 -
3.15 +
0.12 -
3.05 +
0.12 -
3.08 +
0.12 -
3.05 +
0.12 -
3.10 +
0.12 -
3.05 +
0.12 -
3.10 +
0.12 -
3.20 +
0.12 -
3.10 +
0.12 -
1.65 +
0.12 -
37.37 *