

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

101

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PO

STUMP

TOTAL NET WT.

PKG. N-CODE

PROD/SPVB

DATE _____

WHSE. OPER.

156
151
161
154
147
137
140
77
147
140
145
149
154
154
146
08

151T

37
105

CG 46 CODE YT-858-D PKG.

→ FEEL-7 34273

EST. WGT. ~~2250~~ 2250 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
YT-858-D (A) APPROVED BY
EWK 09-30-76
DCG 05-30-78

TYPED BY
emw080878

MAKING NOTES

REMARKS

NOTE: DRY 48 HRS @ 150°F

• TAKE 1 QT SAMPLE MOTHER LIQUOR WHEN FILLING

AME: DALAMAR® YELLOW

BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

AT		105			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		2-7-80			STARTED	230 AM				
TIME		100 AM			CAKES USED	60				
RELEASED BY		ARM			WATER ON	9 AM				
PRESS	32	33	35		HRS. WASHED	6			4	
NO. OF CAKES	60	60	60		OHMS	5000				
PRESS	without	AGITATION			HRS. WASHED					
WASH TO	4000	OHMS with 35-7501 water			OHMS					
EST AFTER	6	HOURS			HRS. WASHED					
LOAD on 10 cars					OHMS					
TAKE 1 QT SAMPLE MOTHER LIQUOR WHEN FILLING					CAKE CONDITION	10				
DO NOT LOAD BOTTOM 2 ROWS OF CARS					NO. CARS LOADED	10				
					EXPLAIN LOSSES					

AMPLES
DELIVER TO

1 QT

SAMPLED BY #152 RELEASED BY A.H.

-DRYING-

Dry 48 hrs at 150°F

LUMP: - OK - WRT - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

AMPLES
DELIVER TO

1 QT

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 25
LUMP WGT. 2166
RELEASED BY

-GRINDING-

MILL 4 or 10 HSP. 1/8" RP SCREEN 3500 RPM

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED

AMPLE WITHOUT MIXING

AMPLES 1 Env & 1 PE Can + 1 gallon

DELIVER TO CTL

SAMPLED BY 127

RELEASED BY

DUP050293151

N33058.02

1.72
1.7
1.73
1.7
1.7
1.52
1.67
1.67
1.64
1.70
1.60
1.57
1.66
1.63
1.54
1.17
1.1
1.1
21.66T