

TECHNICAL SPECIFICATIONS

CertainTeedCertainTeed Corporation
Pipe and Plastics Group

SPECIFICATIONS CLASSIFICATION:

A/C Standard Formulations and Yields

T.C.O. REF. NO.

28

SPECIFICATION NO:

1

PAGE NO.:

3

SUPERSEDES:

February 1, 1983

DATE OF ISSUE:

March 30, 1984

DESCRIPTION:

Fluid-Tite A/C Pressure Pipe, Couplings and Accessories
Classes 100, 150 and 200 - Fluid-Tite BFURNISH DETAILS

Plant	E of F And Blend	Fiber		Cement Lbs.	Silica Lbs.	Fines		Total Weight Lbs.
		%	Lbs.			%	Lbs.	
257	1400B	12.97	381	1374	916	9	264	2935
257	1450B	13.45	397	1374	916	9	266	2953
257	1550B	14.40	431	1374	916	9	269	2990
257	1600B	14.88	448	1374	916	9	270	3008

PREPARED BY:

M. R. Streeter

APPROVED BY:

R & D

MFG.

SALES

I.E.

Q.C.

OTHERS

RCS 18

CTD030276

TECHNICAL SPECIFICATIONS

CertainTeed

CertainTeed Corporation
Pipe and Plastics Group

SPECIFICATIONS CLASSIFICATION:

A/C Standard Formulations and Yields

T.C.O. REF. NO.

44

SPECIFICATION NO:

2

PAGE NO.:

2

SUPERSEDES:

February 1, 1983

DATE OF ISSUE:

March 30, 1984

DESCRIPTION:

Fluid-Tite A/C Sewer Pipe, Couplings and Accessories
Classes 1500 through 7000 - Sections A and B

FURNISH DETAILS

Plant	E of F and Blend	Fiber		Cement Lbs.	Silica Lbs.	Fines		Total Weight Lbs.
		%	Lbs.			%	Lbs.	
257	1050B1	9.57	272	1374	916	10	285	2847
	1150B1	10.53	303	1374	916	10	289	2882
	1200B1	11.01	319	1374	916	10	290	2899
	1250B1	11.48	335	1374	916	10	291	2916
	1300B1	11.96	351	1374	916	10	293	2934
	1500B1	13.88	418	1374	916	10	300	3008
	1550B1	14.36	435	1374	916	10	302	3027
	1600B1	14.83	452	1374	916	10	304	3046
	1400B1	12.92	384	1374	916	10	297	2971
	1450B1	13.40	401	1374	916	10	299	2990
260	1150C1	10.70	309	1374	916	10	289	2888
	1200C1	11.19	325	1374	916	10	291	2906
	1250C1	11.68	342	1374	916	10	292	2924
	1400C1	13.13	391	1374	916	10	298	2979
	1450C1	13.62	408	1374	916	10	300	2998
	1500C1	14.11	426	1374	916	10	302	3018
	1550C1	14.59	443	1374	916	10	304	3037
	1600C1	15.08	461	1374	916	10	306	3057

CTD030277

PREPARED BY:

M. R. Steffy

APPROVED BY:

R & D

MFG.

SALES

I.E.

Q.C.

OTHERS

REPLACES OR MODIFIES PREVIOUS

TECHNICAL SPECIFICATIONS

CertainTeed

CertainTeed Corporation
Pipe and Plastics Group

SPECIFICATIONS CLASSIFICATION:

A/C Standard Formulations and Yields

T.C.O. REF. NO.

28

SPECIFICATION NO:

3A

PAGE NO.:

2

SUPERSEDES:

February 1, 1983

DATE OF ISSUE:

March 30, 1984

DESCRIPTION:

Fluid-Tite Pressure Pipe, Couplings and Accessories
Classes 100, 150 and 200 - Common Groove

FURNISH DETAILS

Plant	E of F and Blend	Fiber		Cement, Lbs.	Silica, Lbs.	Fines		Total Weight Lbs.
		%	Lbs.			%	Lbs.	
257	1400B	12.97	381	1374	916	9	264	2935
	1450B	13.45	397	1374	916	9	266	2953
	1500B	13.92	414	1374	916	9	269	2971
	1550B	14.40	431	1374	916	9	269	2990
	1575B	14.64	439	1374	916	9	270	2999
	1600B	14.88	448	1374	916	9	270	3008
	1675B	15.60	474	1374	916	9	273	3037
	1700B	15.84	483	1374	916	9	274	3047
	1800B	16.80	518	1374	916	9	278	3086
	1850B	17.27	536	1374	916	9	280	3106
	2000B	18.71	593	1374	916	9	285	3168
260	1500C	14.16	422	1374	916	9	268	2980
	1550C	14.64	439	1374	916	9	270	2999
	1600C	15.13	457	1374	916	9	271	3018
	1675C	15.86	483	1374	916	9	275	3048
	1800C	17.08	529	1374	916	9	279	3098
	1950C	18.53	586	1374	916	9	284	3160
	2000C	19.02	605	1374	916	9	286	3181

CTD030278

PREPARED BY:

M. R. [Signature]

APPROVED BY:

R & O

MFG.

SALES

I.E.

Q.C.

OTHERS

RSH

TECHNICAL SPECIFICATIONS

CertainTeed

CertainTeed Corporation
Pipe and Plastics Group

SPECIFICATIONS CLASSIFICATION:

A/C Standard Formulations and Yields

T.C.O. REF. NO.

22

SPECIFICATION NO:

4A

PAGE NO.:

2

SUPERSEDES:

February 1, 1983

DATE OF ISSUE:

March 30, 1984

DESCRIPTION:

Agri-Perm for Agricultural Irrigation Systems

FURNISH DETAILS

Plant	E of F and Blend	Fiber %	Lbs.	Cement, Lbs.	Silica, Lbs.	Fines %	Lbs.	Total Weight, Lbs.
257	1150B	10.58	301	1374	916	9	257	2848
257	1250B	11.53	332	1374	916	9	260	2882
257	1450B	13.45	397	1374	916	9	266	2953
257	1550B	14.40	431	1374	916	9	269	2990
257	1650B	15.36	465	1374	916	9	272	3027
260	1150C	10.75	307	1374	916	9	257	2854
260	1250C	11.72	338	1374	916	9	260	2888
260	1450C	13.67	405	1374	916	9	266	2961
260	1550C	14.64	439	1374	916	9	270	2999
260	1650C	15.62	475	1374	916	9	273	3038

CTD030279

PREPARED BY:

M. R. [Signature]

APPROVED BY:

R & D	MFG.	SALES	I.E.	Q.C.	OTHERS
	<i>RSK</i>				

TECHNICAL SPECIFICATIONS

CertainTeed

CertainTeed Corporation
Pipe and Plastics Group

SPECIFICATIONS CLASSIFICATION:

A/C Standard Formulations and Yields

T.C.O. REF. NO.

15

SPECIFICATION NO:

13

PAGE NO.:

3

SUPERSEDES:

February 1, 1983

DATE OF ISSUE:

March 30, 1984

DESCRIPTION:

A/C Storm Drain Pipe, Couplings and Accessories

FURNISH DETAILS

Plant	E of F and Blend	Fiber		Cement, Lbs.	Silica, Lbs.	Fines		Total Weight Lbs.
		%	Lbs.			%	Lbs.	
257	1150B1	10.53	303	1374	916	10	289	2882
	1200B1	11.01	319	1374	916	10	290	2899
	1300B1	11.96	351	1374	916	10	293	2934
	1400B1	12.92	384	1374	916	10	297	2971
	1450B1	13.40	401	1374	916	10	299	2990
	1500B1	13.88	418	1374	916	10	300	3008
	1550B1	14.36	435	1374	916	10	302	3027
260	1150C1	10.70	309	1374	916	10	289	2888
	1200C1	11.19	325	1374	916	10	291	2906
	1300C1	12.16	358	1374	916	10	294	2942
	1400C1	13.13	391	1374	916	10	298	2979
	1450C1	13.62	408	1374	916	10	300	2998
	1500C1	14.11	426	1374	916	10	302	3018
	1550C1	14.59	443	1374	916	10	304	3037

CTD030280

PREPARED BY:

M. R. Steady

APPROVED BY:

R & D

MFG.

SALES

I.E.

O.C.

OTHERS

RSB

TECHNICAL SPECIFICATIONS

CertainTeed

CertainTeed Corporation
Pipe and Plastics Group

SPECIFICATIONS CLASSIFICATION:

A/C Standard Formulations and Yields

T.C.O. REF. NO.

SPECIFICATION NO:

PAGE NO.:

20

15B

2

SUPERSEDES:

DATE OF ISSUE:

February 1, 1983

March 30, 1984

DESCRIPTION:

A/C Bureau of Reclamation/Fluid Transmission Pipe,
Couplings and Accessories

FURNISH DETAILS

Plant	E of F and Blend	Fiber		Cement, Lbs.	Silica, Lbs.	Fines,		Total Weight Lbs.
		%	Lbs.			%	Lbs.	
257	1400B	12.97	381	1374	916	9	264	2935
	1450B	13.45	397	1374	916	9	266	2953
	1500B	13.92	414	1374	916	9	267	2971
	1550B	14.40	431	1374	916	9	269	2990
	1575B	14.64	439	1374	916	9	270	2999
	1600B	14.88	448	1374	916	9	270	3008
	1625B	15.12	456	1374	916	9	272	3018
	1675B	15.60	474	1374	916	9	273	3037
	1700B	15.84	483	1374	916	9	274	3047
	1800B	16.80	518	1374	916	9	278	3086
	1850B	17.27	536	1374	916	9	280	3106
	1950B	18.23	574	1374	916	9	283	3147
	2000B	18.71	593	1374	916	9	285	3168
260	1400C	13.18	388	1374	916	9	265	2943
	1500C	14.16	422	1374	916	9	268	2980
	1550C	14.64	439	1374	916	9	270	2999
	1600C	15.13	457	1374	916	9	271	3018
	1675C	15.86	483	1374	916	9	275	3048
	1700C	16.10	492	1374	916	9	275	3057
	1800C	17.08	529	1374	916	9	279	3098
	1850C	17.56	548	1374	916	9	280	3118
	1950C	18.53	586	1374	916	9	284	3160
	2000C	19.02	605	1374	916	9	286	3181

CTD030281

PREPARED BY:

M. R. Seefry

APPROVED BY:

R & D

MPG.

SALES

I.E.

Q.C.

OTHERS

RSJH

TECHNICAL SPECIFICATIONS

CertainTeed

CertainTeed Corporation
Pipe and Plastics Group

SPECIFICATIONS CLASSIFICATION:

A/C Standard Formulations and Yields

T.C.O. REF. NO.

7

SPECIFICATION NO:

18

PAGE NO.:

3

SUPERSEDES:

February 1, 1983

DATE OF ISSUE:

March 30, 1984

DESCRIPTION:

A/C Products for PVC Use

FURNISH DETAILS

Plant	E of F and Blend	Fiber		Cement, Lbs.	Silica, Lbs.	Fines		Total Weight, Lbs.
		%	Lbs.			%	Lbs.	
257	1050B1	9.57	272	1374	916	10	285	2847
	1150B1	10.53	303	1374	916	10	289	2882
	1200B1	11.01	319	1374	916	10	290	2899
	1250B1	11.48	335	1374	916	10	291	2916
	1400B1	12.92	384	1374	916	10	297	2971
	1500B1	13.88	418	1374	916	10	300	3008
	1450B	13.45	397	1374	916	9	266	2953
	1500B	13.92	414	1374	916	9	267	2971
	1550B	14.40	431	1374	916	9	269	2990
	1600B	14.88	448	1374	916	9	270	3008
	1675B	15.60	474	1374	916	9	273	3037
	1700B	15.84	483	1374	916	9	274	3047
	1800B	16.80	518	1374	916	9	278	3086
	1850B	17.27	536	1374	916	9	280	3106
260	1050C1	9.73	278	1374	916	10	285	2853
	1150C1	10.70	309	1374	916	10	289	2888
	1200C1	11.19	325	1374	916	10	291	2906
	1400C1	13.13	391	1374	916	10	298	2979
	1500C1	14.11	426	1374	916	10	302	3018
	1450C	13.67	405	1374	916	9	266	2961
	1500C	14.16	422	1374	916	9	268	2980
	1550C	14.64	439	1374	916	9	270	2999
	1600C	15.13	457	1374	916	9	271	3018
	1675C	15.86	483	1374	916	9	275	3048
	1700C	16.10	492	1374	916	9	275	3057
	1800C	17.08	529	1374	916	9	279	3098
	1950C	18.53	586	1374	916	9	284	3160

CTD030282

PREPARED BY:

M. R. Steffy

APPROVED BY:

R & D

MFG.

SALES

I.E.

Q.C.

OTHERS

RSK