

①

✓ 15284-89
 ✓ 15033-34
 15029-32
 15025-28

VISCOSITY WORK SHEET

Item ✓ 15080-88 P.T.No. Date 11/15/55
 Worker Stanley Polymer Lucite Solvent EDC
 For Carnation Charge 1290 Temperature 25°C
 Viscometer No. C Efflux Time ^{210.1} 187.2 } 210.1 Weight: Gross 3.6124
 Viscometer No. M Efflux Time 187.2 } 187.2 Tare 3.4874
 Viscometer No. L Efflux Time ^{180.6} 167.8 } 180.6 Net 0.1250
 S

Visc. Rel. Inh. visc.
 Sample Flask No. Solution Efflux Times Visc. or M.W.

5146-8A	14	C	258.7; 258.9; 258.2	1.230	95,500
8B	TP	M	225.2; 225.3; 225.4	1.203	81,000
7C	N	L	221.4; 221.5; 221.5	1.227	94,500
7D	N	S	204.6; 204.7; 204.8	1.221	90,500
5146-5A	BY	L	222.9; 222.9; 221.9	1.235	98,800
5B	BZ	S	205.2; 206.6; 206.7	1.232	96,500
5C	T1	C	257.7; 257.5; 257.7	1.224	92,000
5D	H-18	M	224.5; 224.5	1.201	79,500
5146-6A	BU	L	223.1; 222.9; 223.1	1.236	99,000
6B	GU	S	206.1; 206.2; 206.3	1.229	95,500
6C	106	C	258.2; 258.9; 258.6	1.231	96,000
6D	M-39	M	227.2; 227.1; 227.2	1.212	85,000
5146-7A	107	L	221.5; 221.6; 221.7	1.225	93,000
7B	L12	S	205.6; 205.6	1.224	92,000
✓ 5146-8C	23	S	257.2; 257.1; 257.3	1.223	91,500
8D	NAC	M	221.5; 221.5	1.182	70,000

PC-1 cont.

May 11-15-55

N38845