MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY 187 LOT 37348

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
1704	1	T. 102		
1700	1	T. 144		
	STUMP	Lump 3408		

TOTAL NET WT. 3404 PKG. N--CODE

PROD. SPVR. DATE WHSE. OPER.

10/13/80

N35009

23
24

CG 103 CODE KY-787-D PKG. ____

OCT - 6 80 37348

EST. WGT. 1000 LBS.

OK
KP

TOTAL WGT 3332#

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (Q)	EWK 9/22/76
	DCG 9/27/76
RETYPED BY	
CJH 4/2/80	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
VAT	244				
DATE	10-7-80				
TIME	11:55P				
RELEASED BY	[illegible]				
PRESS	22	23	24	25	
NO. OF CAKES	46	46	52	48	

PRESS WITH AGITATION

WASH TO 2000 OHMS WITH 35-75 F WATER

TEST AFTER 2 HOURS

LOAD ON 6 CARS

SAMPLES 1-8 OZ JAR

DELIVER TO CTL FOR COLOR

RECORD					
PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	244				
CAKES USED	54				
WATER ON	100				
HRS. WASHED	3				
OHMS	2500				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	7				

EXPLAIN LOSSES

SAMPLED BY 401 RELEASED BY [illegible]

-DRYING-

DRY 12 HRS AT 220 °F
THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 15

SAMPLES

DELIVER TO

NO. CARS PULLED

LUMP WGT. 3408

SAMPLED BY

RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

SAMPLES 1 ENV & 1 PT. CAN

DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050106166

37348
41
17

0.00 *

2.53 +
0.12 -
2.41 +
0.12 -
2.53 +
0.12 -
2.48 +
0.12 -
2.43 +
0.12 -
2.33 +
0.12 -
2.51 +
0.12 -
2.57 +
0.12 -
2.45 +
0.12 -
2.48 +
0.12 -
2.50 +
0.12 -
2.47 +
0.12 -
2.47 +
0.12 -
2.37 +
0.12 -
1.35 +
0.12 -
34.08 *

DUP050106167