

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Y1E698 LOT 40049

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
------------	---------	-----------	----------	----

<u>50</u>	<u>67</u>	<u>3350</u>		
-----------	-----------	-------------	--	--

--	--	--	--	--

--	--	--	--	--

--	--	--	--	--

--	--	--	--	--

--	--	--	--	--

--	--	--	--	--

TOTAL NET WT. 3350 PKG. N-CODE 1000

PROD. SPVR. 5/20/81 DATE 5/20/81 WHSE. OPER.

2 CG 01 CODE YF-698-D PRG.
11- APR -0-81- 40049
EST. WGT. 3371 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
YF-698-D (R)
(E) YC-10-B

APPROVED BY
JMC 11-18-76
DCG 11-18-76

TYPED BY
JLC 11-24-76
MAKING NOTES

REMARKS

MOLYBDATE ORANGE

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

USED BY	2	91	92	93	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
CAKES	32	42	32	32	STARTED	4.8				
With AGITATION					CAKES USED	3.8				
FO 2000					WATER ON	1.5				
AFTER 2					HRS. WASHED	3				
on 4 cars					OHMS	2000				
					HRS. WASHED					
					OHMS					
					HRS. WASHED					
					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	4				
					EXPLAIN LOSSES					

ES
ER TO

SAMPLED BY

RELEASED BY

-DRYING-

DED) DRY 12 HOURS AT 240°F
EXTRUDED) DRY 14 HOURS AT 240°F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

No. Drums

ES
ER TO

NO. CARS PULLED

LUMP WGT. 3492

SAMPLED BY

RELEASED BY

-GRINDING-

Mikroatomize SCREEN RPM
EMP. °F
SET ROOF BLAST GATE AT "9" FOR
HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

E A-1 / WITHOUT MIXING

DATE MIXED

ES 1 Env

ER TO C T L

SAMPLED BY

RELEASED BY

DUP050095753

YE-698

40049

41

225

0.00 *

3.40 +

0.12 -

3.53 +

0.12 -

3.66 +

0.12 -

3.35 +

0.12 -

3.46 +

0.12 -

3.58 +

0.12 -

3.68 +

0.12 -

3.42 +

0.12 -

3.55 +

0.12 -

3.75 +

0.12 -

0.86 +

0.12 -

34.92 *

DUP050095754