

Characteristics and Method of Using		Cost Data		Customers
Type of Goods				
Color				
Luster				
Match for				
Kind of Reducer				
Amount of Reduction for				
Brushing				
Spraying	Pressure			
Dipping	Drip Time	Pigment Analysis 63.4		Pig. Vol. 32.2%
Floccing	Drip Time	Vehicle 36.1		
Tumbling		100.0%		
Air dry to recoat		Pigment		All Plants } 3-17-4
To Sand or Rub		Basic Carb. White Lead	35.2	H & L } NORTH BERGEN
Bake Time	Temp.	Zinc Oxide	34.8	St. Louis 8-15-4
Rub with		Ethopone	15.0	
Polish with		Silica	7.5	
Schedule		Magnesium Silicate	7.5	
		Vehicle	100.0%	
		Linseed Oil	43.5	
		Bodied Linseed	26.7	
		Liquid Drier	6.1	
		Mineral Spirits	23.7	100%

GLD059003