MD-3-A

PACKAGE TICKET

CODE KO-909 LOT F2H78

PO	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
[redacted]	1800	1	T	73
	1800	1	T	120
	1804	1	T	80

STUMP

TOTAL NET WT. 5404

LUMP WT. 5317 PKG. N-CODE

PROD. SUPV. [illegible] DATE 6/8/82 OPERATOR

N39328

PRODUCT NAME = KROLOR ORANGE - Y

NON-BLEEDING
PROCESSES APPROVED BY
KO-909-D (C) FWP 12/10/81

CG 04 CODE KO-909-D PKG ____

LOT F2H78 JUN 3 1982

EST. WT. 5243* LBS. 25 7947

MAKING NOTES _____

JOB NAME: 04KO909DPC

INSTRUCTIONS = PRESSING =					RECORD					
VAT	247				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	6-10				STARTED	9:00 AM				
TIME	9:15 AM				CAKES USED	50				
RELEASED BY	A.G				WATER ON	120				
PRESS	22	23	24	25	HRS. WASHED	24				
NO.OF CAKES	46	46	52	48	OHMS	233				
PRESS WITH AGITATION					HRS. WASHED					
WASH TO 2000 OHMS - 135-145 F WATER					OHMS					
TEST AFTER 3 HOURS					HRS. WASHED					
LOAD ON 6 CARS					OHMS					
					CAKE CONDITION					
					NO CARS LOADED	8				
					EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY BLF

= DRYING =

DRY 24 HOURS AT 180 F
NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 8 OZ. JAR
DELIVER TO CTL

NO CARS PULLED
SAMPLED BY
RELEASED BY TDS

NO DRUMS 19
LUMP WGT 5317

= GRINDING =

MILL 939 HSP 3/32"RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE W/O MIXING 1 ENV & 2 PT CANS
IF PACKED IN BAGS SAMPLE AS FOLLOWS:
FIRST BAG: 1 ENV.
40TH BAG: 1 ENV. & 2 PINT CANS
LAST BAG: 1 ENV.
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

DUP050046871

KO 909
F2H78

19 drums
8 cars

3.00	+
0.12	-
2.97	+
0.12	-
2.91	+
0.12	-
2.89	+
0.12	-
2.91	+
0.12	-
2.97	+
0.12	-
2.98	+
0.12	-
2.75	+
0.12	-
3.01	+
0.12	-
3.05	+
0.12	-
2.92	+
0.12	-
3.01	+
0.12	-
2.97	+
0.12	-
2.83	+
0.12	-
2.83	+
0.12	-
3.05	+
0.12	-
2.83	+
0.12	-
2.84	+
0.12	-
2.70	+
0.12	-
33.17	+

DUP050046872