

SECTION II-B-3.1

INSULATION MATERIALS

MASTICS AND COATINGS

SOLVENT TYPE

Flashing and Sealing Mastics

30-45 - Foamseal

Composition

A non-drying, non-shrinking, flexible vapor barrier mastic containing inorganic fillers, non-drying oils, aluminum pigment, and a minimum amount of organic solvent or drying oil to form a tough skin over the surface of the mastic to enable it to function as a sealer and resist moisture penetration.

30-45 will not adhere to oily, greasy, damp, dusty, or powdery surfaces.

Should not be applied when temperature is below 40°F ambient.

Color

30-45: Aluminum gray

Viscosity

30-45: Soft paste

Application Method

30-45: Trowel or caulking gun

Coverage

Caulking gun: 200 lin. in./cartridge-3/8" thick bead
Trowel: 180 lin. ft./gal. - 3/8" thick bead

Drying Time

Touch: 1 hour
Through: Does not dry thru

Temperature Limits

Insulation surface: - 100°F to + 250°F