

PARR INC.
SUBSIDIARY OF KOPPERS COMPANY, INC.
AUTOMOTIVE DIVISION

11661 CEDAR AVENUE / CLEVELAND, OHIO 44106, U. S. A. / 216-721-7100

May 6, 1980

Mr. Maurice Hatten
INDUSTRIAL COMMISSION OF OHIO
P.O. Box 16512
246 North High Street
Columbus, Ohio 43215

Dear Mr. Hatten:

Confirming your telephone conversation with Dan Moore last week,
enclosed please find a copy of our Product Information sheet
covering our 820-1917 rust preventive.

Sincerely,

PARR INC.



Mary McCrea,
Administrative Assistant



Product Information

820-1917 RUST PREVENTIVE

18400 SYRACUSE AVENUE • CLEVELAND, OHIO 44118
218 • 832-1000

PHYSICAL PROPERTIES

Color	Shaded Black
Weight per Gallon	Approximately 7 pounds
Solids by Weight	52.5 ± 2
Solids by Volume	46.5 ± 2
Flash Point	ASTM D-92 105°F.
Solvent	Exceeds the requirements of Rule #66
Viscosity - Stormer	55 - 70 Krebs Units at 77°F.
High Temperature Flow Point	325°F - 4 hour air dry; no sag at 325°F.
Drying Time	Under production application at 4 mils wet - 2 mils dry. Will pass detergent wash in 1.5 hours.
Application	Air or airless spray - brush.
Corrosion Resistance on Oiled Steel and Painted Steel Panels	Salt spray 750 hours ASTM B-117-64T and GM-4298P
Resistance to Weathering	Passed 10 cycles in accordance with G.M. specification
Detergent Resistance	Passes 1-1/2 hours - 4 hours - 6 hours 24 hours - no effect.
Flexibility	-20°F to 200°F - no effect upon adhesion.
Compatibility	Is protective and non-injurious to materials such as acrylic lacquers, vinyl coated fabrics, Thiokol, neoprene and repair sealers with which it may come in contact.
Toxicity	TLV 500 PPM

WARRANTY, DISCLAIMER AND REMEDY:

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR HIS INTENDED USE. Since the conditions of use and the method and all of applications are beyond our control, no warranty or guarantee is made by Parr regarding the effectiveness of the product. Parr's only warranty is that the product shall meet (within 2% or less) the specifications included on the product data sheet. NO OTHER EXPRESS OR IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, IS MADE BY PARR IN CONNECTION WITH THE USE OR SALE OF THE PRODUCT. All claims under this warranty must be made within 60 months after the date of purchase or be waived. Upon receipt of a timely claim, Parr shall inspect the product and it shall replace free of charge, or at its option, refund the purchase price of any product which (a) in its reasonable judgment, determines to be in breach of this warranty; inspection will be performed at Parr's plant; and freight for returning the product to the plant for inspection will be paid by the purchaser. The foregoing states the sole and exclusive remedy for any breach of warranty or for any other claim in respect of the product, whether sounding in contract, warranty or negligence. Without limiting the generality of the foregoing, Parr shall under no circumstances be liable for any incidental or consequential loss or damage whatsoever arising out of, or in any way relating to, the use or sale of the product, including any labor costs or expenses relating to the application or removal thereof.