FILE NAME: DAP (DAP)

DATE: 1973 July 11

DOC#: DAP016

DOCUMENT DESCRIPTION: Letter with Asbestos Samples

F

July 11, 1973

Dr. Marvin W. Sage
D.A.P., Inc.
P.O. Box 277
Dayton, Ohio 45401

Dear Dr. Sage:

With reference to your letter of July 3, 1973, we are continuing to investigate the possibilities of using a liquid such as Mineral Spirits 66 to eliminate asbestos dust problems at your plant.

As I indicated in our earlier conversations, the use of such a material is not particularly compatible with the volume production of asbestos fiber. However, your suggestion of using the special bag with a valve for addition of a liquid opens a number of possible solutions. We will investigate the availability and suitability of using such a bag and report to you within the next few weeks.

In the interim, we are submitting four samples of asbestos to you as potential replacements for the 6D01 and 7R33 which you are now using. The samples are identified as 6D02, 7RF02, 7R05, and 7R02. We have attached typical comparative data for the Johns-Manville and Carey fiber grades. Except for color the 6D02 is an excellent match for 6D01. In the case of the 7R33, we can match the color with a more efficient fiber such as 7R02 or we can match the physical properties with a grade such as 7R05. Although the 7R02 is not a pound for pound replacement for 7R33, changes in your formulas might easily allow it to be used.

We thank you for your continued interest and look forward to being of further service to you.

Very truly yours,

JFR

James F. Reis
Product Manager
Asbestos Fiber Sales

JFR/sck

D.A.P., INC.

	Carey 6D01	J-M 6D02	Carey 7R33	7R05	J-M 7R02	7RF02
Q.S. Test (oz.)						
1/2						
4						
10	8.0	6.5	.5	.2		
Pan	8.0	9.5	15.5	15.8	16.0	16.0
McNett (%)						
14	4.9	3.0	1.7	.7	0.4	
35	12.2	6.1	5.4	1.6	1.9	T
100			16.5	9.7	15.5	2.1
200	39.3	32.2	16.7	14.5	14.1	6.0
Pan	43.6	58.7	59.7	73.5	68.1	91.9
Color	73	66	67.5	58	63.5	59
Penetration Index			91.1	120	155	137
Loose Density	13.4	10.4	17.2	13.4	12.6	12.4