

REPORT OF CALL

CC: E. J. Kleber - Niagara Falls
 T. P. Morris - Chicago
 H. B. Rhodes - Niagara Falls
 W. C. Thurber - NY 38
 KC Files
 NF Files

Calabria ASSISTS

UNION CARBIDE CORPORATION

P.O. Box 579 Niagara Falls, N.Y. 14302

By J. E. WalshDate 8/7/74

Full Name	Georgia Pacific	Interviewed
Address	Marietta, Georgia	Bob Favero, Plant Manager
Mfrs. of	Tape joint muds	George Fowler, Tech Service

Call made on SG-210 carload account to run a dust count.

GP's mud business is way down, according to Bob, as they are now running only one shift as compared to three a year ago at this time. The carload we are shipping this month is the first since May as they now have only a 5-6 order backlog to work on compared to a 4-6 week backlog last year. An asbestos warning sign now greets you as you enter the plant, and Bob showed me the warning stickers they now put on their redi-mix cans. He also showed me some dry mix vinyl topping compound with "asbestos free" in big letters. Right now it is shipped into the Chicago area only, he said. George and I got into an interesting discussion re why they couldn't use an all 210 mud formula. George knew of no reason other than, maybe, we hadn't pushed at Tigard. After reviewing the economics now since the latest Canadian increase, it looks like we could save them 1 2/3¢/lb before figuring in the cost of limestone to make up the volume. George said his lab is all set up now, and he was going to whip up some all 210 muds, and if they are favorable, send a report to Tigard. He seemed interested in doing the work here because if it is workable, he could pick up some "brownie points" based on the amount of money he could save them.

EJK The dust samples taken were as follows:

#I-41 - on 10:25 A.M. Personal sample attached to operator, Larry James,
 off 10:30 A.M. during the addition of 212 lbs of Carey 7RF-9 and 87½ lbs
 of SG-210.

#J-15 - on 10:30 A.M. Attached to operator, Larry James, during the addition of
 off 10:37 A.M. the following ingredients to complete the makeup of all dry
 materials in the batch: muscovite mica 350 lbs, Gelvatol 20 lb
 Natrosol 37½ lbs, Calgon T 12½ lbs, Troyson 5 lbs.

#H-17 - on 10:51 A.M. repeat of sample I-41 on the next asbestos dump.
 off 10:58 A.M.

#I-17 - on 10:58 A.M. repeat of sample J-15 on the next batch of other dry
off 11:02 A.M ingredients dumped.

EJK Please phone me the results before mailing the report to Favero.

JW Follow up on next call with Fowler re his all 210 mud work.

J. Kleber - Niagara Falls
P. Morris - Chicago
H. B. Rhodes - Niagara Falls
H. C. Thurber - NY 38

Calidria ASSOCIATES

19 1374
CALIDRIA ASSOCIATES

Files
Files

UNION CARBIDE CORPORATION

P.O. Box 579 Niagara Falls, N.Y. 14302

By J. E. Walsh

Date 8/7/74

Full Name	Georgia Pacific	Interviewed
Address	Marietta, Georgia	Bob Favero, Plant Manager
Mfrs. of	Tape joint muds	George Fowler, Tech Service

Call made on SG-210 carload account to run a dust count.

GP's mud business is way down, according to Bob, as they are now running only one shift as compared to three a year ago at this time. The carload we are shipping this month is the first since May as they now have only a 5-6 order backlog to work on compared to a 4-6 week backlog last year. An asbestos warning sign now greets you as you enter the plant, and Bob showed me the warning stickers they now put on their redi-mix cans. He also showed me some dry mix vinyl topping compound with "asbestos free" in big letters. Right now it is shipped into the Chicago area only, he said. George and I got into an interesting discussion re why they couldn't use an all 210 mud formula. George knew of no reason other than, maybe, we hadn't pushed at Tigard. After reviewing the economics now since the latest Canadian increase, it looks like we could save them 1 2/3¢/lb before figuring in the cost of limestone to make up the volume. George said his lab is all set up now, and he was going to whip up some all 210 muds, and if they are favorable, send a report to Tigard. He seemed interested in doing the work here because if it is workable, he could pick up some "brownie points" based on the amount of money he could save them.

JK The dust samples taken were as follows:

- #I-41 - on 10:25 A.M. Personal sample attached to operator, Larry James, off 10:30 A.M. during the addition of 212 lbs of Carey 7RF-9 and 87½ lbs of SG-210.
- #J-15 - on 10:30 A.M. Attached to operator, Larry James, during the addition of off 10:37 A.M. the following ingredients to complete the makeup of all dry materials in the batch: muscovite mica 350 lbs, Gelvatol 20 lb Natrosol 37½ lbs, Calgon T 12½ lbs, Troyson 5 lbs.
- #H-17 - on 10:51 A.M. repeat of sample I-41 on the next asbestos dump. off 10:58 A.M.

I-17 - on 10:58 A.M.
off 11:02 A.M

repeat of sample J-15 on the next batch of other dry
ingredients dumped.

Please phone me the results before mailing the report to Favero.

JW

Follow up on next call with Fowler re his all 210 mud work.

