

92
242

CG 01 CODE YC-16-B PKG. 93

→ MAY -0-81-1237

EST. WGT. 3130 LBS.

OK
PP

PROCESSING INSTRUCTIONS. BATCH UNIT

PROCESSES	APPROVED BY
(A) YC-16-B	A.C. 4-7-75
	JFH 5-5-75
	DCG 5-4-75
TYPED BY	

MAKING NOTES

REMARKS

NAME: MOLYBDATE ORANGE

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	342					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5-2-81					STARTED	8:14 AM				
TIME	2:40 PM					CAKES USED	8.14				
RELEASED BY	E.M.					WATER ON	1000				
PRESS	91	92	93	2	25	HRS. WASHED	5				
NO. OF CAKES	42	32	32	32	32	OHMS	2.00				
PRESS						HRS. WASHED					
WASH TO	2000					OHMS					
TEST AFTER	2					HRS. WASHED					
LOAD ON 4 CARS						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	4				
						EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY

RELEASED BY JH

-DRYING-

DRY 16 HOURS AT 220 F LUMP: - OK - WET - SALTS - CONTAMINATED
DRYER SECTIONS USED:

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 10
LUMP WGT. 3063
RELEASED BY JH

-GRINDING-

MICROATOMIZE	SCREEN	RPM
SET ROOF GATE AT 5 INCHES AIR FLOW	MAX. TEMP.	°F
MAGNETIC READING ON ATOMIZER PANEL 1.0"		
	EXPLAIN LOSSES	
SAMPLE WITHOUT MIXING	DATE MIXED	
SAMPLES 1 ENV		
DELIVER TO C T L	SAMPLED BY	RELEASED BY

1237
41
17

0.00 *
3.15 +
0.12 -
3.14 +
0.12 -
3.08 +
0.12 -
3.22 +
0.12 -
3.22 +
0.12 -
3.17 +
0.12 -
3.28 +
0.12 -
3.18 +
0.12 -
3.23 +
0.12 -
3.16 +
0.12 -
30.63 *