

CODE	<u>LC-16-B</u>		LOT	<u>E1289</u>	
NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PD	
<u>50</u>	<u>58</u>	<u>2900</u>			
STUMP			<u>Lump 3060</u>		
TOTAL NET WT.	<u>2900</u>		PKG. N-CODE	<u>000</u>	
PROD. SPVR.	DATE	WHSE. OPER.			
<u>01/18</u>	<u>5/13/51</u>				

93
942
CG 01 CODE YC-16-B PKG. 93
MAY -0-81-E1229
EST. WGT. 3130 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

(A) YC-16-B	APPROVED BY
	A-C 4-7-75
	JFH 5-5-75
	DCG 5-4-75
TYPED BY	

MAKING NOTES

REMARKS

NAME: MOLYBDATE ORANGE

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE						STARTED	4:PM				
TIME						CAKES USED	32				
RELEASED BY						WATER ON	8 PM				
PRESS	91	92	93	2	25	HRS. WASHED	2 1/2				
NO. OF CAKES	42	32	32	32	32	OHMS	2000				
PRESS						HRS. WASHED					
WASH TO	2000					OHMS					
TEST AFTER	2					HRS. WASHED					
LOAD ON	4 CARS					OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	4				
						EXPLAIN LOSSES					

BLL

SAMPLES
DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

DRY 16 HOURS AT 220 F LUMP: -- OK - WET - SALTS - CONTAMINAT

DRYER SECTIONS USED:

No record of any processing
losses have occurred

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 10

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYLUMP WGT. 3060
RELEASED BY RH

-GRINDING-

MICROATOMIZE	SCREEN	RPM
SET ROOF GATE AT 5 INCHES AIR FLOW	MAX. TEMP.	° F
MAGNETIC READING ON ATOMIZER PANEL 1.0"		
	EXPLAIN LOSSES	

SAMPLE WITHOUT MIXING

DATE MIXED

SAMPLES 1 ENV

DELIVER TO C.T.L.

SAMPLED BY

RELEASED BY

1229
12
365

3.51 +
0.12 -
3.37 +
0.12 -
2.99 +
0.12 -
2.98 +
0.12 -
3.14 +
0.12 -
3.12 +
0.12 -
3.23 +
0.12 -
3.34 +
0.12 -
3.09 +
0.12 -
3.03 +
0.12 -
30.60 *