

PRODUCT NAME = MOLYBDATE ORANGE

CG 01 CODE YE-698-D PKG

LOT F2J47 JUN 1 1982

EST. WT. 5547* LBS.

92
245

NON-BLEEDING

4/22/82

PROCESSES APPROVED BY
YE-698-D (S) F. POST 10/09/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY A.G.
PRESS 2 92 93
NO. OF Cakes 54 54 54
PRESS WITH AGITATION
WASH TO 500 M MHOS WITH 35-75* WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

1ST	2ND	3RD	4TH	5TH
PRESSLOAD				
STARTED				
CAKES USED				
WATER ON				
HRS. WASHED				
M MHOS				
HRS. WASHED				
M MHOS				
HRS. WASHED				
M MHOS				
CAKE CONDITION				
NO CARS LOADED				
EXPLAIN LOSSES				

SAMPLES 8 OZ
DELIVER TO CTL.

SAMPLED BY
RELEASED BY

Blk

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 19
LUMP WGT 5732

DELIVER

CO-GROUND PER CTL INSTRUCTIONS
MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT '9' FOR
HIGH AIR FLOW

GRINDING

RPM SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE
SAMPLES 1 ENV IF GROUND SEPARATELY
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

N39438

47
41
427
0
304
12
307
12
306
12
329
12
323
12
309
12
313
12
325
12
330
12
321
12
135
12
3170

47
41
52
3170
3170
317
12
333
12
350
12
335
12
337
12
332
12
330
12
324
12
5732