

cc: V. J. Labrecque
S. M. Lillis
J. A. Johnson

March 6, 1969

File

Mr. Van Sebastian
Smith & Kanaler Company
1414 East Linden Avenue
Linden, New Jersey 07036

Dear Van:

Confirming our telephone conversation of March 3, 1969, we have agreed to the following experiment on 6222 in .058"/.066" gauge:

Add Butyl Zimate, 1.0 phr
to three batches

Add Butyl Zimate, 1.5 phr
to three batches

You will be sending samples to us for evaluation.

Samples of material made with extra Methyl Tuads were examined and show an improvement in tensile strength when compared with standard production sample, (1100 psi increased to 1300 psi). Samples made with increased binder showed no improvement in flexibility characteristics.

Congratulations on the new daughter. I was glad to hear about her and that she and your wife are doing well.

Very truly yours,

VICTOR GASKET DIVISION
DANA CORPORATION

CH
Carl I. Hayden
Materials Development Laboratory

pt

VPD-153-0002545