MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE RT261 LOT 37464

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	12	2525	28	
	STUMP	LUMP WT	2521	

TOTAL NET WT. 2525 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
	10/22	252

N35141



DUP050107873

96/90-3

OCT 13 1980

CO 32 CODE RT-761-D PKG.

DCT 13 80 37464

EST. WGT. 2669 LBS.

99

PROCESSING INSTRUCTIONS. BATCH UNIT

PROCESSES	APPROVED BY
RT-761-D (J)	JJG 4-4-78
	DCG 4-5-78
TYPED BY NSA 4-19-78	

MAKING NOTES

REMARKS

NAME: WATCHUNG® RED B

NON-BLEEDING

INSTRUCTIONS — PRESSING — RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT		903				STARTED	7P				
DATE		10-20				CAKES USED	80				
TIME		3:PM				WATER ON	18 MIN				
RELEASED BY		~~EB~~				HRS. WASHED	34				
PRESS	95	~~96~~				OHMS	3000				
NO. OF CAKES	74	80				HRS. WASHED					
PRESS without AGITATION						OHMS					
WASH TO 3000 OHMS with 35-75°F water						HRS. WASHED					
TEST AFTER 3 HOURS						OHMS					
LOAD on 9 cars						CAKE CONDITION					
PRESS IMMEDIATELY CODE						NO. CARS LOADED	9+3				
Instruct making area to add 10# N-588-D half-way thru pressing						EXPLAIN LOSSES					
Clean magnetic separator after pressing											
Cleaned By 933 Time Cleaned 12:15 P											
SAMPLES											
DELIVER TO						SAMPLED BY		RELEASED BY			

-DRYING-

DRY 24 Hours at 220°F °F	LUMP: - OK - WET - SALTS - CONTAMINATED
Hold on track 30 min before dumping pans	
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS 14
SAMPLES	NO. CARS PULLED LUMP WGT. 2521
DELIVER TO	SAMPLED BY RELEASED BY

-GRINDING-

MILL 2 LSP 1/8" RP SCREEN 1750 RPM	SCREEN RPM
MAX. TEMP. 150 °F	MAX. TEMP. °F
	EXPLAIN LOSSES
SAMPLE / WITHOUT MIXING	DATE MIXED
SAMPLES 2 Env & 2 Pt Cans	
DELIVER TO C T L	SAMPLED BY RELEASED BY

DUP050107874

17464
51
52

0.00 *

2.04 +
0.14 -
2.06 +
0.14 -
2.13 +
0.14 -
1.98 +
0.14 -
2.04 +
0.14 -
1.76 +
0.14 -
2.07 +
0.14 -
1.71 +
0.14 -
14.67 *
14.67M+

14.67 +
2.15 +
0.14 -
2.07 +
0.14 -
2.29 +
0.14 -
1.99 +
0.14 -
1.94 +
0.14 -
0.94 +
0.14 -
25.21 *
25.21M+

DUP050107875