

MEMORANDUM

cc: D.E. Frazier-BBR
C.A. Homan-BBQ
T.E. Miller, Jr.

In Reply to _____ Date 4/6/76 From K. Sutton To C.R. Dickinson
Subject FS FELT

Three sample rolls of Shreveport plain saturated felt were received by P.J.L. The unrolling characteristics of both rolls were excellent. One sample weighed 62.5# (125.6% sat.), while the others weighed 62.0# (123.4% sat.). Felt weight, after desaturation, was observed to be 6.53 and 6.66 #/100 sq. ft.

KS/jd

5/6/76

$$6.53 \text{ #/100} = 31.3 \text{ #/480}$$

$$6.66 \text{ " } = 31.97 \text{ #/480}$$

REC'D AT MAIN ROOM

76 APR -7 PM 1:38

BIRD & SON, Inc.