

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Ky 787 LOT 35176

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>1796</u>	<u>1</u>	<u>.</u>	<u>T-95</u>	
<u>1608</u>	<u>1</u>		<u>T 102</u>	

STUMP

TOTAL NET WT. 3404 PKG. N-CODE _____

PROD. SPVR. WK DATE 4.1.80 WHSE. OPER. _____

N 26261

DUP050093602

PROCESSING INSTRUCTIONS: BATCH UNIT

CG 03 CODE KY-787-D PKG.

MAR 29 35176

EST. WGT. 1090 LBS.

PROCESSES	APPROVED BY
KY-787-D (R)	FWK 9/22/76
Alternate	DCG 9/27/76

TYPED BY

NE 2/12/77

MAKING NOTES

REMARKS

Total Wgt. 3490#

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	243					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	3-30-80					STARTED	1030 PM				
TIME	10:15 PM					CAKES USED	12				
RELEASED BY	C. J. H.					WATER ON	3 PM				
PRESS	22	23	24	24		HRS. WASHED	6				
NO. OF CAKES	46	46	46	52		OHMS	2000				
PRESS with						HRS. WASHED					
WASH TO	2000					OHMS					
TEST AFTER	2					HRS. WASHED					
LOAD	on 6 cars					OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
 DELIVER TO ctl for color

SAMPLED BY 315 RELEASED BY 702

-DRYING-

Dry 12 hrs at 220°F.
 Then Dry 8 hrs at 160°F.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
 DELIVER TO

NO. CARS PULLED
 SAMPLED BY

LUMP WGT. 3855
 RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" BP SCREEN 3500 RPM
 MAX. TEMP. 150 °F

SCREEN
 MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
 SAMPLES 1 ENV & 1 Pt. can
 DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050093603

N 26261.01

35176 #

.51 #

2.31 #

.00 T

2.60

.12 -

2.80

.12 -

2.60

.12 -

2.85

.12 -

2.65

.12 -

2.75

.12 -

2.60

.12 -

2.73

.12 -

2.65

.12 -

2.70

.12 -

2.85

.12 -

2.80

.12 -

2.65

.12 -

1.00

.12 -

3.455 T