

MD-3-A

## PACKAGE TICKET

CODE

K0-789

LOT

L2J58

| PO | NET WT/PKG. | NO. PKG. | PACK WT. | LOCATION |
|----|-------------|----------|----------|----------|
|    | 2770        | 1        | T-86     |          |
|    | 2880        | 1        | T-17     |          |
|    |             |          |          |          |
|    |             |          |          |          |
|    |             |          |          |          |
|    |             |          |          |          |
|    |             |          |          |          |
|    |             |          |          |          |
|    |             |          |          |          |

STUMP

TOTAL NET WT.

5650

LUMP WT.

5159

PKG. N-CODE

PROD. SUPV.

DHI

DATE

11 23

OPERATOR

DATE PRINTED: 2/03/82

PRODUCT NAME = "KROLOR" ORANGE Y

NON-BLEEDING

CG 04 CODE KO-789-D PKG

PROCESSES APPROVED BY  
KO-789-D (I) FWP 01/29/82

LOT L2J58

NOV 12 1982

TYPED BY JMH

MAKING NOTES

EST. WT. 5179\* LBS.

JOB NAME: 04KO789DPI

| INSTRUCTIONS |       |         |             | = PRESSING = | RECORD       |                      |                                      |                    |                |           |         |            |          |             |        |             |        |             |        |                |                |                |       |
|--------------|-------|---------|-------------|--------------|--------------|----------------------|--------------------------------------|--------------------|----------------|-----------|---------|------------|----------|-------------|--------|-------------|--------|-------------|--------|----------------|----------------|----------------|-------|
| VAT          | DATE  | TIME    | RELEASED BY | PRESS        | NO. OF CAKES | PRESS WITH AGITATION | WASH TO 200 M MHOS WITH 35-75* WATER | TEST AFTER 6 HOURS | LOAD ON 5 CARS | PRESSLOAD | STARTED | CAKES USED | WATER ON | HRS. WASHED | M MHOS | HRS. WASHED | M MHOS | HRS. WASHED | M MHOS | CAKE CONDITION | NO CARS LOADED | EXPLAIN LOSSES |       |
| 246          | 11-15 | 4:15 AM | 237         | 22           | 23           | 24                   | 25                                   | 48                 | 50             | 720       | 11/80   | 11/80      | 11/80    | 11/80       | 11/80  | 11/80       | 11/80  | 11/80       | 11/80  | 11/80          | 11/80          | 11/80          | 11/80 |

SAMPLES  
DELIVER TOSAMPLED BY  
RELEASED BY

| = DRYING =                       |                                             |
|----------------------------------|---------------------------------------------|
| DRY 18 HOURS AT 220 DEG F        | LUMP: - OK - WET - SALTS - CONTAMINATD      |
| ADDITIONAL DRYING HOURS REQUIRED |                                             |
| SAMPLES<br>DELIVER TO            | NO CARS PULLED<br>SAMPLED BY<br>RELEASED BY |
|                                  | NO DRUMS<br>LUMP WGT                        |

| = GRINDING =                       |            |
|------------------------------------|------------|
| MILL 938 HSP 3/32" SCREEN 3500 RPM | SCREEN     |
| MAX. TEMP 210 DEG F                | MAX. TEMP. |
| EXPLAIN LOSSES                     |            |
| DATE MIXED                         |            |
| SAMPLED BY                         |            |
| RELEASED BY                        |            |

SAMPLE W/O MIXING 1 ENV & 2 PT CANS  
IF PACKED IN BAGS SAMPLE AS FOLLOWS:  
FIRST BAG: 1 ENV.  
40TH BAG: 1 ENV. & 2 PINT CANS  
LAST BAG: 1 ENV.  
DELIVER TO CTL

DUP050060186

N41057.01

58  
124  
41

1  
2.88 ✓  
0.14 -  
2.80 ✓  
0.14 -  
2.84 ✓  
0.14 -  
2.90 ✓  
0.14 -  
2.94 ✓  
0.14 -  
2.80 ✓  
0.14 -  
2.76 ✓  
0.14 -  
2.80 ✓  
0.14 -  
2.72 ✓  
0.14 -  
2.77 ✓  
0.14 -  
3.01 ✓  
0.14 -  
2.96 ✓  
0.14 -  
3.06 ✓  
0.14 -  
2.80 ✓  
0.14 -  
2.95 ✓  
0.14 -  
2.79 ✓  
0.14 -  
2.85 ✓  
0.14 -  
2.90 ✓  
0.14 -  
2.72 ✓  
0.14 -  
51.59 \*  
0.00 \*

19